
TOPPAN

PXTTOPSL

BOPP FILMS

WHITE CAVITATED NON TOP COATED PRESSURE SENSITIVE BOPP FACESTOCK FILM



DESCRIPTION

White Cavitated **BOPP** Film is with one side treated Matt surface and other side treated glossy surface. The film has Glossy side for Print receptive surface and Matt side for Adhesive anchorage for Pressure sensitive Labelling conversion

PRODUCT FEATURES

- Robust machinability
- Outstanding opacity and whiteness
- Excellent gloss on printing side
- Corona treated Silky matte surface suitable for adhesive receptivity
- Good antistatic property
- Excellent web flatness

APPLICATIONS

- Labels

	PROPERTIES	POSITION	PX50TTOPSL	PX58TTOPSL	PX60TTOPSL	PX63TTOPSL	UNIT	METHOD
GENERAL	Nominal Thickness Grammage Yield	-	36.0	41.76	43.2	63 45.36 22.04	g/cc	Internal Method Internal Method Internal Method
OPTICAL	Gloss Transmittance	Glossy Surface			70 : 18			ASTM D 2457 ASTM D 1003
SURFACE	C O F Wetting Tension	Gloss/Matt Gloss/Matt).30 88			ASTM D 1894 ASTM D 2578
MECHANICAL	_	- MD - TD - MD		1	900 800 80			ASTM D 882
	(at break) Elastic Modulus	- TD - MD - TD		5	3000-14000 4000			ASTM D 882 ASTM D 882
THERMAL	Linear Shrinkage (max)	- MD - TD		4 2			%	ASTM D 1204

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30° C & humidity $55\pm5\%$ in storage areas and material should be consumed within three months of receipt. OPP films should be allowed to reach operating room temperature 24 hours before use.

FOOD CONTACT

OPP films complies with the requirements of FDA, EC & REACH regulations. Specific documentation is available on request

SAFETY

Compliance with industrial health and safety standards. OPP films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of manufacturing
- Printing, coating & lamination: Online corona treatment is strongly recommended before processing the material.