

TLS

BOPP FILMS

TRANSPARENT SEALABLE SHRINK WRAP 20 μ BOPP FILM SPECIAL LOW STATICS GRADE FOR OVERWRAPING



DESCRIPTION

OPP TLS is transparent heat sealable on either side **BOPP** film. It is specially designed for high speed unprinted overwrapping applications where machinability is a key factor. TLS is high shrink film for wrinkle-free optimum package tightness which provides better moisture barrier and enhanced shelf life.

PRODUCT FEATURES

- Specially formulated for unprinted overwrap application
- Outstanding shrink properties for wrinkle free appearance
- Consistent and stable slip
- Excellent stiffness and mechanical properties
- Good performance on high speed machines
- Good anti-static
- Good optical properties
- Good seal strength
- Good anti-blocking for smooth operation with no jamming

APPLICATIONS

Unprinted overwrap

- Tobacco (cigarettes/cigars)
- CD's & DVD's
- Household and industrial

	PROPERTIES	POSITION	TLS18	TLS20	UNIT	METHOD
GENERAL	Nominal Thickness	-	18	20	μ	Internal Method
	Density	-	0.91	0.91	g/cc	Internal Method
	Grammage	-	16.38	18.2	g/m ²	Internal Method
	Yield	-	61.05	55	m ² /kg	Internal Method
OPTICAL	Haze	-	2.5		%	ASTM D 1003
	Gloss	-	95		GU	ASTM D 2457
SURFACE	COF (Dynamic)	Film/Metal	0.15		-	ASTM D 1894
		Film/Film	0.18		-	ASTM D 1894
	Static charge	-	< 1.0		kv	Internal Method
MECHANICAL	Tensile Strength (at break)	- MD	1600		kg/cm ²	ASTM D 882
		- TD	2800			
	Elongation (at break)	- MD	160		%	ASTM D 882
		- TD	60			
THERMAL	Elastic Modulus	- MD	22000		kg/cm ²	ASTM D 882
		- TD	44000			
	Linear Shrinkage	- MD/TD	8 - 8		%	ASTM D 1204
	Seal Initiation Temp.	Inside Layer	105		°C	Internal Method
	Heat Seal Strength	-	350		g/25mm	Internal Method (130°C/1sec/30psi)

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed within three months of receipt. OPP films should be allowed to reach operating room temperature 24 hours before use.

FOOD CONTACT

OPP films complies with the requirements of FDA, EC & REACH regulations. Specific documentation is available on request.

SAFETY

Compliance with industrial health and safety standards. OPP films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of invoicing