

PROVISIONAL

WX65TILS-CPP

WHITE OPAQUE MATTY SIDE CORONA TREATED & OTHER SIDE HEAT SEALABLE CPP FILM FOR CONVERSION



Corona treated Matty Surface
Tie Layer
White PP Core layer
Tie Layer
Non CT, Glossy Heat Sealable surface



AVAILABLE
CALIPERS

DESCRIPTION

It is a co-extruded white opaque cast polypropylene film having one side corona treatment Matty surface and other side is heat sealable Glossy surface. This opaque film is ideal for VFFS & HFFS machines.

PRODUCT FEATURES

- Solid White appearance
- Excellent sealing properties in term of strength, hot-tack and integrity
- Excellent surface gloss & Opacity
- Good processibility
- Good Moisture Barrier

APPLICATIONS

- Suitable for use in multilayer laminate
- Bundle Overwrap
- Frozen food & Noodles
- Confectionary (chocolate/gum/sugar)
- Bakery (Biscuits/cookie/crackers)
- Household and detergents
- Health and beauty care

NOMENCLATURE

WXTILS-CPP...Wetting tension Surface Inside, Heal Seal Surface Outside

WXTOLS-CPP...Wetting tension Surface Outside, Heal Seal Surface Inside

PROVISIONAL

	PROPERTIES	POSITION	WX65TILS-CPP	UNITS	TEST METHOD
GENERAL	Nominal Thick.	-	65	μ	Internal Method
	Density	-	0.95	g/cc	Internal Method
	GSM	-	61.8	g/m ²	Internal Method
	Yield	-	16.2	m ² /kg	Internal Method
OPTICAL	Opacity	-	65	%	Internal Method
	Gloss	-	50	GU	ASTM D 2457
SURFACE	Dynamic COF	Film/Film	0.40	-	Internal Method
	Wetting Tension	-	38*	dy/cm	ASTM D 2578
MECHANICAL	Tensile Strength (at break)	-MD	500	kg/cm ²	ASTM D 882
		-TD	250		
	Elongation (at break)	-MD	500	%	ASTM D 882
		-TD	650		
THERMAL	SIT	-	115	°C	Internal Method
	HSS	-	2500	g/in	Internal Method (130°C/0.5sec/30psi)

* 38 dyne/cm guaranteed for 3 months & 36 dyne/cm guaranteed for 6 months from the invoice date in controlled ambient condition as mentioned in storage guidelines

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed within three months of receipt. CPP films should be allowed to reach operating room temperature 24 hours before use

FOOD CONTACT

CPP films complies with the requirements of FDA, EC & REACH regulations. Specific documentation is available on request.

SAFETY

Compliance with industrial health and safety standards. CPP films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of invoicing