


PROVISIONAL

COCXPSLM

COATED FILMS

WHITE CAVITATED TOP COATED PRESSURE SENSITIVE BOPP FACESTOCK FILM



DESCRIPTION

White Cavitated **BOPP** Film with one side Print Receptive Coated **Matte** Surface and other side Treated **Glossy** surface for Pressure sensitive Labels

PRODUCT FEATURES

- Excellent ink adhesion with a broad range of ink systems, including UV curing inks on Print receptive coated matte surface.
- Corona treated glossy surface suitable for adhesive anchorage
- High speed press performance.
- Coating adhesion is maintained in hot and cold water immersion without clouding
- Superior performance of print surface in humid environment
- Outstanding opacity and whiteness
- Excellent stiffness and mechanical properties
- Good dimensional stability
- Good die cutting performance

APPLICATIONS

- Labels

COATING SIDE

COCX PSL M: Outside Print Receptive Coated Matte surface

PROVISIONAL

PROPERTIES		POSITION	COCX60PSLM	UNIT	METHOD
GENERAL	Nominal Thickness	-	60	μ	Internal Method
	Grammage	-	45.1	g/m ²	Internal Method
	Yield	-	22.2	m ² /kg	Internal Method
OPTICAL	Transmittance	-	16	%	ASTM D 1003
	Wetting Tension (Uncoated side)	-	38	dy/cm	ASTM D 2578
MECHANICAL	Tensile Strength (at break)	- MD - TD	900 1800	kg/cm ²	ASTM D 882
	Elongation (at break)	- MD - TD	200 60	%	ASTM D 882
	Elastic Modulus	- MD - TD	16000 28000	kg/cm ²	ASTM D 882
	Linear Shrinkage (max)	- MD - TD	4 2	%	ASTM D 1204

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed within three months of receipt. Coated films should be allowed to reach operating room temperature 24 hours before use.

FOOD CONTACT

Coated films complies with the requirements of FDA, EC & REACH regulations. Specific documentation is available on request

SAFETY

Compliance with industrial health and safety standards. Coated films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of manufacturing
- Coated reels must not be stacked