

PROVISIONAL

TDQ20TOGD

TRANSPARENT VERY LOW HEAT SEAL TEMPERATURE, HIGH HOT-TACK & HIGH SEAL STRENGTH CORONA TREATED ONE SIDE WITH IMPROVED DIMENSIONAL PROPERTIES FOR HIGH SPEED PACKAGING APPLICATIONS



Corona Treated Heat Seal Layer

OPP Core

Untreated Very Low SIT Heat Seal Layer



AVAILABLE
CALIPERS

DESCRIPTION

TDQ20TOGD is transparent co-extruded **BOPP** film, one side very low seal initiation temperature (SIT ~ 85°C). Especially designed for high speed packaging where its wide seal operating window can be used on high speed machines. This film is specially developed for improved Dimensional properties.

PRODUCT FEATURES

- Wide sealing range with low seal initiation temperature (SIT ~ 85°C)
- Excellent sealing properties in term of strength, hot-tack and integrity
- Good dimensional properties
- Good runnability on HFFS and VFFS machines
- Excellent seal integrity in presence of contaminants and humidity
- Good optical properties
- Good stiffness and mechanical properties
- Lap sealable

APPLICATIONS

Can be used as a single web or laminate structures;

- Confectionary (Chocolate/ Gum/ Sugar)
- Health & beauty care
- Bakery (Biscuits/cookie/crackers)
- Chips/ Snacks/ Pasta
- Household & detergent

NOMENCLATURE

- TDQ20TIGD - Corona treated surface is Inside & Untreated High Heat seal surface is Outside
 TDQ20TOGD - Corona treated surface is Outside & Untreated High Heat seal surface is Inside

TOPPAN SPECIALITY FILMS

PROVISIONAL

	PROPERTIES	REF.	TDQ20TOGD	UNITS	TEST METHOD
GENERAL	Thickness	-	20	μ	Internal Method
	Density	-	0.91	g/cc	Internal Method
	GSM	-	18.2	gm/m ²	Internal Method
	Yield	-	54.9	m ² /kg	Internal Method
OPTICAL	Haze	-	2.0	%	ASTM D 1003
	Gloss	-	90	GU	ASTM D 2457
SURFACE	Wetting Tension	-	38*	%	ASTM D 2578
	COF (Dynamic)	UT/UT	0.30	-	ASTM D 1894
MECHANICAL	Tensile Strength (at break)	MD TD	1300 2700	Kg/cm ²	ASTM D 882
	Elongation (at break)	MD TD	170 60	%	ASTM D 882
	Modulus	MD TD	20000 40000	Kg/cm ²	ASTM D 882
THERMAL	Thermal Shrinkage	MD TD	1.5 0.5	%	ASTM D 1204 (120°C, 5min)
	Heat seal range	-	85 - 145	°C	Internal Method
	Heat Seal Strength (1.0sec, 170N, 130°C)	-	500	g/25mm	Internal Method

*38 dyne/cm guaranteed for 6 months from the invoice date in controlled ambient condition as mentioned in storage guidelines.

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed within three months of receipt. OPP films should be allowed to reach operating room temperature 24 hours before use.

FOOD CONTACT

OPP films complies with the requirements of FDA, EC & REACH regulations. Specific documentation is available on request.

SAFETY

Compliance with industrial health and safety standards. OPP films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of invoicing
- Please make sure printing surface is well dried before lamination