


PROVISIONAL

COWSXPSLO-U

COATED FILMS

SOLID WHITE TOP COATED PRESSURE SENSITIVE BOPP FACESTOCK FILM



DESCRIPTION

COWSXPSLO-U is Solid white BOPP film with one side special print receptive coated surface and other side treated matt surface for excellent anchorage with wide range of adhesives.

PRODUCT FEATURES

- Excellent ink adhesion with a broad range of ink systems, including UV curing inks on Print receptive coated surface.
- Corona treated matt surface suitable for adhesive anchorage
- High speed press performance.
- Superior performance of print surface in humid environment
- Outstanding opacity and whiteness
- Excellent stiffness and mechanical properties
- Good dimensional stability
- Good heat resistance
- Good die cutting performance

APPLICATIONS

- Pressure Sensitive Labels

COATING SIDE

COWSXPSLO-U - Outside Print receptive coated glossy surface

PROVISIONAL

	PROPERTIES	POSITION	CO WSX58PSLO-U	UNIT	METHOD
GENERAL	Nominal Thickness	-	2.26	mils	Internal Method
	Grammage	-	11.06	lb/1000ft ²	Internal Method
	Yield	-	13035	in ² /lb	Internal Method
SURFACE OPTICAL	Transmittance	-	22	%	ASTM D 1003
	Gloss	-	65	GU	ASTM D 2457
	Wetting Tension	Matt Surface	40	dy/cm	ASTM D 2578
MECHANICAL	Tensile Strength (at break)	- MD - TD	15642 34128	psi	ASTM D 882
	Elongation (at break)	- MD - TD	180 60	%	ASTM D 882
	Elastic Modulus	- MD - TD	241740 426600	psi	ASTM D 882
	Linear Shrinkage (max)	- MD - TD	4 2	%	ASTM D 1204

The figures and above properties refer to typical values which are indicative only. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a product specification.

GUIDELINES FOR STORAGE

Temperature should preferably be less than 30°C & humidity 55±5% in storage areas and material should be consumed within three months of receipt. Coated films should be allowed to reach operating room temperature 24 hours before use.

SAFETY

Compliance with industrial health and safety standards. Coated films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed. Relevant guidelines can be found in our MSDS (available upon request).

CAUTIONS

- Film characteristics are maintained for six months from the date of invoicing
- Please make sure printing surface is well dried before lamination