

# EMBEDDED SENSING IN ELASTIC PASSIVE ACTUATORS



The City College  
of New York




**Presentation by: Sarah Liu PI: Inigo Sanz Pena**


**20 May 2024**

# OBJECTIVE

Method of incorporating  
conductive material into an  
elastic material to reduce the  
need of an external sensor  
Determining an elastic +  
conductive material that can  
easily composited into a  
passive actuator for hip  
assistance during active  
motion



*Liquid latex molding Image source <https://www.artnews.com>*




*Silicon Rubber. Image source:  
<http://www.teximinternational.com/product/silicon-rubber/>*

## DEVELOPING METHODOLOGY:

Review of existing technology for passive actuations and current embedded sensing technology to develop a novel prototype of both elements. A basic setup to achieve such goal will be developed to create a prototype as well as a method to test mechanical and conductive properties.

## CURRENT TECHNOLOGY

- Passive Actuators: use of elastic bands to support movement
- Use of external sensors for monitoring the assistance of an elastic band. Increases weight + cost of actuator



*Exoband components and their working principle. Waist belt (a) and thigh part Image source from Panizzolo, F., et. al.*

# CURRENT TECHNOLOGY

- Embedded sensors in an elastic material. Goal is to increase the force assistance of such material to be viable in use for walking.
- Active Actuators: more often explored. Use of powered actuators Ways to improve user experience by size/placements as well as ways to be more efficient in use of actuators has been and is still being explored



*Natural rubber/Pristine 2.8E-7 graphene composite strain sensor. Image source from Liu, H., Gao H., Hu, G.*



*Load Cell. Image source <https://www.vetek.com/>*

## MATERIALS SELECTIONS: 3D PRINTING

FDM printing – Creating molds to utilize different materials



SLA Printer – allows for more detailed designs to be of high quality while allowing direct integration of conductive materials. Limited by properties of available resins



*Ultimaker Connect 2+ image source  
<https://ultimaker.com/3d-printers/s-series/ultimaker-2-connect/>*



*Saturn 3 Ultra image source  
<https://www.elegoo.com>*



## PROTOTYPING

The use of 3D Printing as a means of rapid prototyping. Mold used to easily change dimensions of the band. Future works include changing geometry within the molding process


## MATERIAL SELECTION: ELASTIC MATERIALS

<b>Material</b>	<b>Elongation at Break</b>	<b>Max Tensile Strength (MPa)</b>	<b>Elastic modulus (GPa)</b>	<b>Tear Strength (N/mm)</b>	<b>Shore Hardness (A)</b>
TPU	200-1000 %	48-83	.001-.05	50-100	60-95
TPE	8-2000 %	2-56.5	0.0130-2.25	20-70	65-99
Elastic Resin	100-160%	1.61-3.4	0.03	10-30	40-85
Silicon Rubber	300-1500 %	0.135-165	0.0005-0.06	15-50	10-95
Latex	700-1100%	15-30	0.001-0.01	15-30	30-90



## ASSISTIVE FORCE TESTING

- Testing without Graphene determining the necessary band for required force. Serves as comparison for change due to graphene additives.
- Assumed parameters: provide an assisted for of 50 N



# INITIAL MECHANICAL PROPERTIES TESTING

Stiffness coefficient (K): 0.07384  
N/mm


Elastic modulus (E): 0.08111 MPa

Elongation needed (Maximum  
flexure):  
14 mm

Hooke's Law:  $\sigma = E\varepsilon$


$$\frac{F}{A} = E \frac{\Delta L}{L}$$

Stiffness vs Elongation



Plot of slopes of Stiffness vs Elongation giving an average stiffness of 0.07384 N/mm

Elastic modulus vs Strain




Plot of slopes of Elastic Modulus vs Strain giving an average Elastic Modulus: 0.08111 MPa

# CONDUCTIVE ADDITIVE - GRAPHENE

Changes properties of elastic materials – possible to increase mechanical properties the strongest, most electrically conductive

Different graphene loading will be tested to determine optimal mechanical and conductive properties

$$GF = \frac{\Delta R/R}{\varepsilon}$$



*Conductivity of G/SR composites with different graphene wt. %, . Image source Kuriana, A. S., Mohana V. B., Bhattacharyya, D.*




## FUTURE WORK

- Conductive testing of the composite materials and finding optimal graphene loading concentration.
- Variation in band configuration to change mechanical properties (assistive force based on geometry)

# CONDUCTIVITY TESTING


- Materials:
- Digital Voltage Meter
- Copper wiring
- Conductive adhesive



Conductive adhesive testing with digital voltage meter. Image source: Stockwell.com

# CONDUCTIVITY TESTING

- Conductive testing to determine proper graphene concentration.
- Use of adhesive for accounting for the stretching of passive actuator.
- Configuration setup to achieve linearity for analyzing the data.



Setup for future conductive testing of the graphene/latex band

PRESENTATION ENDING

Thank You



References >>

## REFERENCES

- *Blackwell Plastics, Custom Plastic Injection Molding & Extrusion Professionals* , Available at:  
<http://www.blackwellplastics.com/TPU.html#:~:text=Physical%20Properties%3A&text=Tensile%20Strength%20%2D%206960%20to%2012000,to%2010.1%20ft%2Dlb%2Fin> (Accessed: 02 May 2024).
- Che, W.M. *et al.* , “The effect of graphene loading on natural rubber latex/graphene stretchable conductive material,” *IOP Conference Series: Materials Science and Engineering*, 670(1), p. 012041, 2019, doi:10.1088/1757-899x/670/1/012041.
- Jones, J. , *The properties of TPU material and its application in 3D printing, Affordable 3D Printing Filaments and Resins*. Available at:  
<https://www.sunlu.com/blogs/products-knowledge/the-properties-of-tpu-material-and-its-application-in-3d-printing#:~:text=Flexibility%20and%20Elasticity&text=During%20stretching%2C%20TPU's%20soft%20segments,far%20surpassing%20that%20of%20PLA>. (Accessed: 02 May 2024).
- Kurian, A., Mohan, V.B. and Bhattacharyya, D. , “Embedded large strain sensors with graphene-carbon black-silicone rubber composites,” *Sensors and Actuators A: Physical*, 282, pp. 206–214, 2018, doi:10.1016/j.sna.2018.09.017.
- Kowalczyk, K., Mukherjee, M. and Malcolm, P., “Can a passive unilateral hip exosuit diminish walking asymmetry? A randomized trial,” *Journal of NeuroEngineering and Rehabilitation*, 20(1), 2023, doi:10.1186/s12984-023-01212-w.



## REFERENCES

- Liu, H., Gao, H. and Hu, G., “Highly sensitive natural rubber/pristine graphene strain sensor prepared by a simple method,” *Composites Part B: Engineering*, 171, pp. 138–145, 2019, doi:10.1016/j.compositesb.2019.04.032.
- Mao, Y., Wang, C. and Liu, L., “Preparation of graphene oxide/natural rubber composites by latex co-coagulation: Relationship between microstructure and reinforcement,” *Chinese Journal of Chemical Engineering*, 28(4), pp. 1187–1193, 2020, doi:10.1016/j.cjche.2020.01.015.
- Pagac, M. *et al.*, “A review of VAT photopolymerization technology: Materials, applications, challenges, and future trends of 3D printing,” *Polymers*, 13(4), p. 598, 2021, doi:10.3390/polym13040598.
- Panizzolo, F.A. *et al.*, "Reducing the energy cost of walking in older adults using a passive hip flexion device", *Journal of NeuroEngineering and Rehabilitation*, 16(1), 2019, doi:10.1186/s12984-019-0599-4.
- Sanz-Pena, I., Hopkins, M., Carrero, N. R., Xu H., "Embedded Pressure Sensing Metamaterials Using TPU-Graphene Composites and Additive Manufacturing," in *IEEE Sensors Journal*, vol. 23, no. 15, pp. 16656-16664, 1 Aug.1, 2023, doi: 10.1109/JSEN.2023.3283460.