## Internal Specification for Glazed, Rectified, Polished Porcelain tiles.

| Sr# | Characteristics / Size | **60.0x120.0X1.0** | | | |
|---|---|---|---|---|---|
| 1 | Nominal Size in mm | 600.0x1200.0x10 | | | |
| 2 | Work size in mm | 596x1196x10 | | | |
| | Standard | ISO 13006 | | SCC | |
| 3 | Max Length & width mm | - | | 599.9 - 600.4<br>1199.9-1200.4 | |
| 4 | Max deviation in diagonal mm | - | | 0.8 | |
| 5 | Thickness deviation % | ± 5.0 | | ± 5.0 | |
| 5.1 | Thickness Range mm | | | 9.5 - 10.5 | |
| 6 | Centre curvature mm | | | | |
| 6.1 | a) Convex + | + 1.80 | | + 1.80 | |
| 6.2 | b) Concave- | - 1.80 | | - 0.90 | |
| 7 | Warpage mm | ± 1.80 | | ± 1.80 | |
| 8 | Edge curvature mm | | | | |
| 8.1 | a) Convex + | + 1.80 | | + 1.60 | |
| 8.2 | b) Concave- | - 1.80 | | - 0.80 | |
| 9 | Max deviation from straightness mm | ± 0.80 | | ± 0.50 | |
| 10 | Max deviation from rectangularity mm | ± 1.50 | | ± 1.50 | |
| 11 | Group | B1a | B1b | B1a | B1b |
| 12 | Water absorption % | ≤0.5 | 0.5<E≤3 | ≤0.5 | 0.5<E≤3 |
| 13 | Breaking strength (N) | ≥ 1300 | ≥ 1100 | ≥ 1300 | ≥ 1100 |
| 14 | Modulus of rupture $N/mm^2$ | ≥35 | ≥27 | ≥35 | ≥27 |
| 15 | Resistance to surface abrasion class | Manufacturer to state | | 3 – 5 | |
| 16.1 | Scratch resistance Moh's scale Glossy) | - | | ≥ 3 | |
| 16.2 | Scratch resistance Moh's scale (Matt) | - | | ≥ 6 | |
| 17 | Coefficient of linear thermal expansion ($x10^{-6}K^{-1}$) | - | | ≤ 9 | |
| 18 | Resistance to thermal shock | Required | | Resistant | |
| 19 | Crazing resistance (5bar / 2hr cycle) | Required | | Resistant | |
| 20 | Frost Resistance | Required | | Resistant | |
| 21 | Staining resistance G (min class) | 3 | | 3 | |
| 22 | Chemical resistance to acids & alkalis (min Class) | Required if agreed | | B | |
| 23 | Color resistance to UV light | - | | No change in color | |
| 24 | Resistance to household chemicals (minimum class) | B | | B | |