INTERNAL SPECIFICATION FOR RECTIFIED CERAMIC TILES

Sr. No.	CHARACTERISTICS	SF (Rectified) 15.0X90.0x1.0 cm		SF(Die effect)/Rectified 15.0X90.0x1.0 cm	
1	Nominal size **(mm)**	150.0x9000.0x1.0		150.0x9000.0x1.0	
2	Work size **(mm)**	147.0x900.0X1.0		147.0x900.0X1.0	
		ISO 13006	**SCC. spec.**	**ISO 13006**	**SCC. spec.**
3	Size variation from work size **(%)**	± 0.30	± 0.30	± 0.30	± 0.30
	In **mm**	± 0.40 ± 1.00	± 0.40 ± 0.50	± 0.40 ± 1.00	± 0.40 ± 0.50
3.1	Size range in **mm**	146.6 – 147.4 899.0 – 901.0	146.6 – 147.4 899.9 – 900.4	146.6 – 147.4 899.0 – 901.0	146.6 – 147.4 899.9 – 900.4
3.2	Max. deviation in diagonal9mm)		0.8		0.8
4	Thickness deviation **(%)**	± 10.0	± 5.0	± 10.0	± 5.0
5	Thickness Range **(mm)**		9.50 - 10.50		9.50 - 10.50
6	Centre Curvature	mm	mm	mm	mm
6.1	a) Convex **(+)**	+ 1.80	+ 1.60	+ 1.80	+ 1.60
6.2	b) Concave **(-)**	- 1.80	- 0.30	- 1.80	- 0.30
7	Warpage	± 1.80	± 1.60	± 1.80	± 1.60
8	Edge Curvature				
8.1	a) Convex **(+)**	+ 1.80	+ 1.50	+ 1.80	+ 1.50
8.2	b) Concave **(-)**	- 1.80	- 0.40	- 1.80	- 0.40
9	Max deviation from Straightness (**mm)**	± 0.80	± 0.50	± 0.80	± 0.50
10	Max deviation from Rectangularity (**mm)**	± 1.50	± 1.20	± 1.50	± 1.20
11	Water Absorption **(%)**	> 10	16 ± 2	> 10	16 ± 2
12	Coefficient to Linear thermal expansion **($x10^{-6}K^{-1}$)**	-	≤ 8	-	≤ 8
13	Resistance to surface abrasion **(Class)**	Manufacturer to state class	2 - 5	Manufacturer to state class	2 - 5
14	Breaking strength **(N)**	≥ 600	≥ 800	≥ 600	≥ 800
15	Modulus of Rupture **(N/mm^2)**	Min 12	Min 15	Min 12	Min 15
16	Crazing resistance **(5bar/2 hr cycle)**	Required	Resistant	Required	Resistant
17	Scratch resistance **(Moh's Scale)**	Required	Min.3 (Glossy) Min.6 (Matt)	Required	Min.3 (Glossy) Min.6 (Matt)
18	Staining resistance **(Min.Class)**	3	3	3	3
19	Chemical resistance to Acids and alkalis **(Min.Class)**	Required if agreed	B	Required if agreed	B
20	Resistance to household Chemicals (Min.**Class)**	B	B	B	B