INTERNAL SPECIFICATION FOR **RECTIFIED CERAMIC TILES**

Sr. No	CHARACTERISTICS	DIE-EFFECT 30.0X90.0x1.0 cm		30.0X90.0x1.0 cm	
1	Nominal size **(mm)**	300.0x900.0x1.0		300.0x900.0x1.0	
2	Work size **(mm)**	300.0x900.0x1.0		300.0x900.0x1.0	
		ISO 13006	**SCC. spec.**	**ISO 13006**	**SCC. spec.**
3.1	Size variation from work size **(%)**	± 0.30	± 0.30	± 0.30	± 0.30
3.2	In **mm**	± 0.90 ± 1.00	± 0.50 ± 0.50	± 0.90 ± 1.00	± 0.50 ± 0.50
3.3	Size range in **mm**	299.1 – 300.9 899.0 – 901.0	299.9 – 300.4 899.9 – 900.4	299.1 – 300.9 899.0 – 901.0	299.9 – 300.4 899.9 – 900.4
3.4	Max.deviation in Diagonal (mm)	-	0.8	-	0.8
4	Thickness **(mm)**		10		10
4.1	Thickness deviation **(%)**	± 10.0	± 5.0	± 10.0	± 5.0
4.2	Thickness Range (mm)		9.50 – 10.50		9.50 – 10.50
5	Centre Curvature	mm	mm	mm	mm
5.1	a) Convex **(+)**	+ 1.80	+ 1.80	+ 1.80	+ 1.80
5.2	b) Concave **(-)**	- 1.80	- 0.30	- 1.80	- 0.30
6	Warpage	± 1.80	± 1.80	± 1.80	± 1.80
7	Edge Curvature				
7.1	a) Convex **(+)**	+ 1.80	+ 1.60	+ 1.80	+ 1.60
7.2	b) Concave **(-)**	- 1.80	- 0.40	- 1.80	- 0.40
8	Max deviation from Straightness **(mm)**	± 0.8	± 0.5	± 0.8	± 0.5
9	Max deviation from Rectangularity **(mm)**	± 1.5	± 1.2	± 1.5	± 1.2
10	Water Absorption **(%)**	> 10	16 ± 2	> 10	16 ± 2
11	Coefficient to Linear thermal expansion **($x10^{-6}K^{-1}$)**	-	≤ 8	-	≤ 8
12	Resistance to surface abrasion **(Class)**	Manufacturer to state class	2 - 5	Manufacturer to state class	2 - 5
13	Breaking strength **(N)**	≥600	≥800	≥600	≥800
14	Modulus of Rupture **MPa (Kg/cm^2)**	Min. 12 (120)	Min. 15 (150)	Min. 12 (120)	Min. 15 (150)
15	Crazing resistance **(5bar/2 hr cycle)**	Required	Resistant	Required	Resistant
16	Scratch resistance Moh's Scale (Glossy)	-	≥3	-	≥3
17	Scratch resistance Moh's Scale (Matte)	-	≥6	-	≥6
18	Staining resistance **(Class)**	Min. 3	Min. 3	Min. 3	Min. 3
19	Chemical resistance to Acids and alkalis **(Class)**	Required if agreed	B	Required if agreed	B
20	Resistance to household Chemicals **(Class)**	Min. B	B	Min. B	B