INTERNAL SPECIFICATION FOR **CERAMIC TILES**

Sr. No	CHARACTERISTICS	SF 40.0X80.0x1.0 cm		(Die effect) 40.0X80.0x1.0 cm	
1	Nominal size **(mm)**	400.0x800.0x10.0		400.0x800.0x10.0	
2	Work size **(mm)**	400.0x800.0X10.0		400.0x800.0X10.0	
		ISO 13006	**SCC Spec**	**ISO 13006**	**SCC. spec.**
3.1	Size variation from work size **(%)**	± 0.30	± 0.30	± 0.60	± 0.60
	Deviation from work size (**mm**)	± 1.00 ± 1.00	± 0.50 ± 0.50	± 1.00 ± 1.00	± 0.50 ± 0.50
3.2	Size range in **mm**	399.9 – 401.0 799.0 – 801.0	399.9 – 400.4 799.9 – 800.4	399.9 – 401.0 799.0 – 801.0	399.9 – 400.4 799.9 – 800.4
3.3	Max. deviation in diagonal (mm)		0.8		0.8
4	Thickness (mm)		10		10
4.1	Thickness deviation **(%)**	± 10.0	± 5.0	± 10.0	± 5.0
5	Thickness Range **(mm)**		9.50 - 10.50		9.50 - 10.5
6	Centre Curvature	mm	mm	Mm	mm
6.1	a) Convex **(+)**	+1.80	+1.80	+1.80	+1.80
6.2	b) Concave **(-)**	-1.80	-0.30	-1.80	-0.30
7	Warpage	± 1.80	±1.80	± 1.80	±1.80
8	Edge Curvature				
8.1	a) Convex **(+)**	+1.80	+1.60	+1.80	+1.60
8.2	b) Concave **(-)**	-1.80	-0.40	-1.80	-0.40
9	Max deviation from Straightness (**mm)**	±0.80	±0.50	±0.80	±0.50
10	Max deviation from Rectangularity (**mm)**	±1.50	±1.20	±1.50	±1.20
11	Water Absorption **(%)**	>10	16 ± 2	>10	16 ± 2
12	Coefficient to Linear thermal expansion **($x10^{-6}K^{-1}$)**	-	≤ 8	-	≤ 8
13	Resistance to surface abrasion **(Class)**	Manufacturer to state class	2 – 5	Manufacturer to state class	2 – 5
14	Breaking strength **(N)**	≥ 600	≥ 800	≥ 600	≥ 800
15	Modulus of Rupture **(N/mm^2)**	Min. 12	Min.15	Min.12	Min.15
16	Crazing resistance **(5bar/2 hr cycle)**	Required	Resistant	Required	Resistant
17	Scratch resistance **(Moh's Scale)**	-	Min.3 (Glossy) Min.6 (Matt)	-	Min.3 (Glossy) Min.6 (Matt)
18	Staining resistance **(Min.Class)**	3	3	3	3
19	Chemical resistance to Acids and alkalis **(Min.Class)**	Required if agreed	B	Required if agreed	B
20	Resistance to household Chemicals **(Min.Class)**	B	B	B	B