INTERNAL SPECIFICATION FOR Ceramic tiles

Sr. No	CHARACTERISTICS	43.0x43.0x1.2 cm	
1	Nominal size **(mm)**	430.0x430.0x1.2	
2	Work size **(mm)**	429.0x429.0x1.2	
		ISO 13006	**SCC. spec.**
3.1	Size variation from work size **(%)**	± 0.30	± 0.30
3.2	In **mm**	± 2.0	± 2.0
3.3	Size range in **mm**	427.0 – 431.0	427.0 – 431.0
	Size code 05		427.0 – 428.0
	Size code 03		428.1 – 429.0
	Size code 01		429.1 – 430.0
	Size code 00 **(Normal)**		430.1 – 431.0
4	Thickness **(mm)**		12.0
4.1	Thickness deviation **(%)**	± 10.0	± 5.0
4.2	Thickness Range (mm)		11.50 – 12.50
5	Centre Curvature	mm	mm
5.1	a) Convex **(+)**	+ 2.00	+ 1.80
5.2	b) Concave **(-)**	- 2.00	- 0.30
6	Warpage	± 2.00	± 1.60
7	Edge Curvature		
7.1	a) Convex **(+)**	+ 2.00	+ 1.30
7.2	b) Concave **(-)**	- 2.00	- 0.40
8	Max deviation from Straightness **(mm)**	± 1.5	± 1.06
9	Max deviation from Rectangularity **(mm)**	± 2.00	± 1.6
10	Water Absorption **(%)**	> 10	16 ± 2
11	Coefficient to Linear thermal expansion **($x10^{-6}K^{-1}$)**	-	≤ 8
12	Resistance to surface abrasion **(Class)**	Manufacturer to state class	2 - 5
13	Breaking strength **(N)**	≥600	≥800
14	Modulus of Rupture **MPa (Kg/cm^2)**	Min. 12 (120)	Min. 15 (150)
15	Crazing resistance **(5bar/2 hr cycle)**	Required	Resistant
16	Scratch resistance **Moh's Scale (Glossy)**	-	≥3
17	Scratch resistance **Moh's Scale (Matte)**	-	≤6
18	Staining resistance **(Class)**	Min. 3	Min. 3
19	Chemical resistance to Acids and alkalis **(Class)**	Required if agreed	B
20	Resistance to household Chemicals **(Class)**	Min. B	B