INTERNAL SPECIFICATION FOR **CERAMIC TILES**

Sr. No	CHARACTERISTICS	60x120x1.0 cm	
1	Nominal size **(mm)**	600.0x1200.0x10	
2	Work size **(mm)**	600.0x1200.0x10	
	Standard	**ISO 13006**	**SCC. spec.**
3.1	Deviation from work size **(%)**	± 0.30	± 0.30
	Deviation from work size **(mm)**	±1.00 ±1.00	±0.50 ±0.50
3.2	Size range in **mm**	599.0 – 601.0 1199.0 – 1201.0	599.9 – 600.4 1199.9 – 1200.4
3.3	Max. deviation in diagonal **(mm)**	-	0.8
4	Thickness (mm)		10
4.1	Thickness deviation **(%)**	± 10.0	± 5.0
5	Thickness Range **(mm)**		9.50 - 10.50
6	Centre Curvature	mm	mm
6.1	a) Convex **(+)**	+ 1.80	+ 1.80
6.2	b) Concave **(-)**	- 1.80	- 0.30
7	Warpage	± 1.80	± 1.80
8	Edge Curvature		
8.1	a) Convex **(+)**	+ 1.80	+ 1.60
8.2	b) Concave **(-)**	- 1.80	- 0.40
9	Max deviation from Straightness (**mm**)	± 0.80	± 0.50
10	Max deviation from Rectangularity (**mm**)	± 1.50	± 1.50
11	Water Absorption **(%)**	>10	16 ± 2
12	Coefficient to Linear thermal expansion **($x10^{-6}K^{-1}$)**	-	≤ 8
13	Resistance to surface abrasion **(Class)**	Manufacturer to state class	2 - 5
14	Breaking strength **(N)**	≥ 600	≥ 800
15	Modulus of Rupture N/mm² (**kg/cm²**)	Min. 12 (120)	Min 15 (150)
16	Crazing resistance **(5bar/2 hr cycle)**	Required	Resistant
17	Scratch resistance **(Moh's Scale)**	-	Min.3 (Glossy) Min.6 (Matt)
18	Staining resistance **(Min.Class)**	3	3
19	Chemical resistance to Acids and alkalis **(Min.Class)**	Required if agreed	B
20	Resistance to household Chemicals **(Min.Class)**	B	B