INTERNAL SPECIFICATION FOR **CERAMIC DIE-EFFECT TILES (MONOCOTTURA)**

Sr. No	CHARACTERISTICS	SF 60.0x60.0x1.5 cm	
1	Nominal size **(mm)**	600.0x600.0x15.0	
2	Work size **(mm)**	595.0x595.0X15.0	
	Standard	**ISO 13006**	**SCC. spec.**
3.1	Size variation from work size **(%)**	± 0.30	± 0.30
	Size Variation within work size(mm)	±1.00	±0.50
3.2	Size range in **mm**	594.0 - 596.0	594.5 – 595.0
3.3	Max. deviation in diagonal(mm)	-	0.8
4	Thickness deviation **(%)**	± 5.0	± 5.0
5	Thickness Range **(mm)**		14.5 - 15.5
6	Centre Curvature	mm	mm
6.1	a) Convex **(+)**	+ 1.80	+ 1.80
6.2	b) Concave **(-)**	- 1.80	- 0.40
7	Warpage	± 1.80	± 1.80
8	Edge Curvature		
8.1	a) Convex **(+)**	+ 1.80	+ 1.50
8.2	b) Concave **(-)**	- 1.80	- 0.40
9	Max deviation from Straightness (**mm)**	± 0.80	± 0.50
10	Max deviation from Rectangularity (**mm)**	± 1.50	± 1.50
11	Water Absorption **(%)**	6 - 10	6 - 10
12	Coefficient to Linear thermal expansion **($x10^{-6}K^{-1}$)**	-	≤ 9
13	Resistance to surface abrasion **(Class)**	Manufacturer to state class	2 - 5
14	Breaking strength **(N)**	≥ 800	≥ 800
15	Modulus of Rupture (**N/mm^2)**	Min. 18	Min 18
16	Crazing resistance **(5bar/2 hr cycle)**	Required	Resistant
17	Scratch resistance **(Moh's Scale)**	-	Min.3 (Glossy) Min.6 (Matt)
18	Staining resistance **(Min. Class)**	3	3
19	Chemical resistance to Acids and alkalis **(Min. Class)**	Required if agreed	B
20	Resistance to household Chemicals **(Min. Class)**	B	B