Internal Specification for Glazed, Rectified, Porcelain tiles.

Sr#	Characteristics / Size	60.0x60.0x2.0 cm		60.0x60.0x2.0 Die effect	
1	Nominal Size in mm	600.0 x 600.0 x 20		600.0 x 600.0 x 20	
2	Work size in mm	600.0 x 600.0 x 20		600.0 x 600.0 x 20	
	Standard	ISO 13006	SCC	ISO 13006	SCC
3	Max Length & width mm	-	599.9 – 600.4	-	599.9 – 600.4
4	Max deviation in diagonal mm	-	0.8	-	0.8
5	Thickness (mm)		20		20
5.1	Thickness Range mm		19.5 – 20.5		19.5 – 20.5
6	Centre curvature	mm	mm	mm	mm
6.1	a) Convex +	+ 1.80	+ 1.80	+ 1.80	+ 1.80
6.2	b) Concave-	- 1.80	- 0.80	- 1.80	- 0.80
7	Warpage mm	± 1.80	± 1.80	± 1.80	± 1.80
8	Edge curvature mm				
8.1	a) Convex +	+ 1.80	+ 1.40	+ 1.80	+ 1.40
8.2	b) Concave-	- 1.80	- 0.60	- 1.80	- 0.60
9	Max deviation from straightness mm	± 0.80	± 0.50	± 0.80	± 0.50
10	Max deviation from rectangularity mm	± 1.50	± 1.20	± 1.50	± 1.20
11	Group	B1a	B1a	B1a	B1a
12	Water absorption %	≤0.5	≤0.5	≤0.5	≤0.5
13	Breaking strength (N)	≥1300	≥1400	≥1300	≥1400
14	Modulus of rupture N/mm^2	≥35	≥35	≥35	≥35
15	Resistance to surface abrasion class	Manufacturer to state	3 – 5	Manufacturer to state	3 – 5
16.1	Scratch resistance Moh's scale Glossy)	-	≥ 3	-	≥ 3
16.2	Scratch resistance Moh's scale (Matt)	-	≥ 6	-	≥ 6
17	Coefficient of linear thermal expansion ($x10^{-6}K^{-1}$)	-	≤ 9	-	≤ 9
18	Resistance to thermal shock	Required	Resistant	Required	Resistant
19	Crazing resistance (5bar / 2hr cycle)	Required	Resistant	Required	Resistant
20	Frost Resistance	Required	Resistant	Required	Resistant
21	Staining resistance G (min class)	3	3	3	3
22	Chemical resistance to acids & alkalis (min Class)	Required if agreed	B	Required if agreed	B
23	Surface quality	-	95% tiles without defects	-	95% tiles without defects
24	Resistance to household chemicals (minimum class)	B	B	B	B