Internal Specification for Glazed Rectified Porcelain tiles.

Sr#	Characteristics / Size	80x160X1.0 cm		80x160X1.0 cm Die effect	
1	Nominal Size in mm	800.0x1600.0x10		800.0x1600.0x10	
2	Work size in mm	800x1600x10		800x1600x10	
	Standard	ISO 13006	SCC	ISO 13006	SCC
3	Max Length & width mm	-	799.5 – 800.5 1599.5 – 1600.5	-	799.5 – 800.5 1599.5 – 1600.5
4	Max deviation in diagonal mm	-	0.8	-	0.8
5	Thickness mm		10		10
5.1	Thickness Range (mm)		9.50 – 10.50		9.50 – 10.50
6	Centre curvature	mm	mm	mm	mm
6.1	a) Convex +	+ 1.80	+ 1.80	+ 1.80	+ 1.80
6.2	b) Concave-	- 1.80	- 1.80	- 1.80	- 1.80
7	Warpage mm	± 1.80	± 1.80	± 1.80	± 1.80
8	Edge curvature mm				
8.1	a) Convex +	+ 1.80	+ 1.80	+ 1.80	+ 1.80
8.2	b) Concave-	- 1.80	- 1.80	- 1.80	- 1.80
9	Max deviation from straightness mm	± 0.80	± 0.50	± 0.80	± 0.50
10	Max deviation from rectangularity mm	± 1.50	± 1.50	± 1.50	± 1.50
11	Group	B1a	B1a	B1a	B1a
12	Water absorption %	≤0.5	≤0.5	≤0.5	≤0.5
13	Breaking strength (N)	≥ 1300	≥ 1400	≥1300	≥ 1400
14	Modulus of rupture N/mm^2	≥35	≥35	≥35	≥35
15	Resistance to surface abrasion class	Manufacturer to state	3 - 5	Manufacturer to state	3 – 5
16	Coefficient of linear thermal expansion ($x10^{-6}K^{-1}$)	-	≤ 9	-	≤ 9
17.1	Scratch resistance Moh's scale (Glossy)	-	≥ 3	-	≥ 3
17.2	Scratch resistance Moh's scale (Matt)	-	≥ 6	-	≥ 6
18	Resistance to thermal shock	Required	Required	Required	Required
19	Crazing resistance (5bar / 2hr cycle)	Required	Required	Required	Required
20	Frost Resistance	Required	Required	Required	Required
21	Staining resistance G (min class)	3	3	3	3
22	Chemical resistance to acid & alkalis (min Class)	Required if agreed	B	Required if agreed	
23	Surface quality	-	95% tiles without defects	-	95% tiles without defects
24	Resistance to household chemicals (minimum class)	B	B	B	B