3.7 Dry Etching

Status: 1.4.2011

Outline

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.7.1 Introduction

Dry etching techniques are those that use plasmas to drive chemical reactions and/or employ energetic ion beams to remove material.

Goal: **Pattern transfer from mask to layer**

Dry etching methods:

- **Glow discharge methods**
  - Dry physical etching (Sputter etching, ion etching)
  - Plasma assisted etching
    - Dry chemical etching (Plasma etching)
    - Reactive ion etching (RIE)
- **Ion beam methods**
  - Ion milling
  - Reactive ion beam etching
  - Chemical assisted ion milling



Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Common materials to dry etch: **Si, SiO_2, Si_3N_4, Al, W, Ti, TiN, $TiSi_2$, Photoresist**

Difficult materials to dry etch: **Cu, Al_2O_3,** Fe, Ni, Co, $LiNbO_3$, ...

Degree of Anisotropy:

$$A_f \equiv 1 - \frac{l}{h_f} = 1 - \frac{R_l t}{R_v t} = 1 - \frac{R_l}{R_v}$$



For isotropic etching: ***$R_l = R_v$ and $A_f = 0$***



For completely anisotropic etching: ***$R_l = 0$ and $A_f = 1$***



Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Comparison of dry etching methods

Technique	***Mechanism***	***Etching particles***	***Pressure [Pa]***	***Directional behavior***
Barrel Etching	chemical	reactive radicals	100	isotropic
Plasma Etching (PE)	phys. & chem.	reactive radicals, weakly ion assisted	10 - 100	isotropic with anisotropic component
Reactive Ion Etching (RIE)	phys. & chem.	reactive radicals, strongly ion assisted	1 - 10	anisotropic with isotropic component
Reactive Ion Beam Etching (RIBE)	phys. & chem.	reactive ions	≤ 0,01	anisotropic with isotropic component
Sputter Etching	physical	inert ions	1 - 10	anisotropic
Ion Beam Etching (IBE)	physical	inert ions	≤ 0.01	anisotropic

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.7.2 Chemistry

3.7.2.1 Overview

Typical or representative plasma etch gases for films used in IC fabrication		
Material	**Etchant**	**Comments**
Polysilicon	SF_6, CF_4 CF_4/H_2, CHF_3 CF_4/O_2 HBr, Cl_2, $Cl_4/HBr/O_2$	Isotropic or near isotropic (significant undercutting); poor or no selectivity over SiO_2. Very anisotropic; nonselective over SiO_2. Isotropic; more selective over SiO_2. Very anisotropic; most selective over SiO_2.
Single-crystal Si	same etchants as Polysilicon	
SiO_2 PSG BPSG	SF_6, NF_3, CF_4/O_2, CF_4 CF_4/H_2, CHF_3/O_2, C_2F_6, C_3F_8 $CHF_3/C_4F_8/CO$	Can be near isotropic (significant undercutting); anisotiopy can be improved with higher ion energy and lawer pressure; poor or no selectivity over Si. Very anisotropic; selective over Si. Anisotropic;selective over Si_3N_4.
Si_3N_4	CF_4/O_2 CF_4/H_2 CHF_3/O_2, CH_2F_2	Isotropic; selective over SiO_2 but not over Si. Very anisotropic; selective over Si but not over SiO_2. Very anisotropic; selective over Si and SiO_2.
Al	Cl_2 $Cl_2/CHCl_3$, Cl_2/N_2	Near isotropic (significant undercutting). Very anisotropic; BCl_3 often added to scavenge oxygen.
Tungsten (W)	CF_4, SF_6 Cl_2	High etch rate; nonselective:over SiO_2. Selective over SiO_2.
Ti	Cl_2, $Cl_2/CHCl_3$, CF_4	
TiN	Cl_2, $Cl_2/CHCl_3$, CF_4	
$TiSi_2$	Cl_2, $Cl_2/CHCl_3$, CF_4/O_2	
Photoresist	O_2	Very selective over other films.

3.7.2.2 Control of Selectivity

Dependence of etch rates of Si and SiO_2 in CF_4 plasmas on the content of O_2 and H_2



Schumicki, Abb. 5.6

Addition of O_2:

Even with plasma the etch rate is slow (insufficient F concentration)

Adding O_2 to the plasma can increase F concentration

$O + CF_3 \rightarrow COF_2 + F$ then
$O + COF_2 \rightarrow CO_2 + 2F$

and consumes CF_x
--> Etch rate of Si increases faster than of SiO_2

Concentration of F increases further because recombination of CF_x and F becomes increasingly unlikely.

Also: Less adsorption of C on Si because CF_x is not sufficiently available (reactions (5) and (6))

Etch rate decreases at higher O_2 concentrations: Dilution of F conc. with overly abundant O_2

Similar trend is for SiO_2

Etch rate is higher for Si

Si/SiO_2 selectivity is good

Isotropic etching

Adding H_2 *drastically lowers Si etch rate by formation of stable HF*
$H^+ + F + e^- \rightarrow HF$
However, etch rate of SiO_2 remains longer constant
Allows SiO_2/Si etch selectivity to be increased tremendously

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.7.2.3 Control of Anisotropy

Formation of Sidewall Passivating Films



- Formation of nonvolatile fluorocarbons that deposit on the surfaces **(Polymerization)**
- The deposit can only be removed by physical collisions with incident ions
- Fluorocarbon films deposits on all surfaces, but the ion velocity is nearly vertical. As a result, as the etching proceeds there is little ion bombardment of the sidewalls and the fluorocarbon film accumulates
- Adding hydrogen encourages the formation of the fluorocarbon films because hydrogen scavenge fluorine, creating a carbon-rich plasma (same thing happened when C_2F_6 is used instead of CF_4)
- Less accumulation is observed on SiO_2 than Si surfaces
- Tradeoff between ***Si/SiO2 selectivity*** and ***Anisotropy***

Source: Lecture Advanced Topics in Fabrication and Microengineering, John Hopkins University, Baltimore

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Controlling Polymerization



- Higher F/C-ratio leads to more etching
- Lower F/C-ratio leads to more polymerization
- Can be determined by the gas used
- Adding H_2 consumes F
  – leads to polymerization
- Adding O_2 consumes C
  – leads to etching

J.W.Coburn, H.F.Winters, J. Vac. Sci. Technol. 16 (1979) 391.

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.7.3 Processes and Equipment

3.7.3.1 "Pure" Chemical Etching

Barrel Reactor

- Plasma and substrate in two different places.
- Chemical etch by reactive radicals (only neutrals reach the wafers)
- Very selective
- Isotropic
- Many wafers in a batch
- Application: Stripping resist in oxygen plasma



Downstream Reactor

- Generation of long-living reactive particles in RF (13,56 MHz) or MW (2,45 GHz) plasma apart from the wafer
- Kink blinds out radiation, no damage
- Very soft process



/Schumicki, S.115/

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Advanced Integrated Circuit Technology

3.7.3.2 Plasma Etching

Parallel Plate (Planar) Reactor

- Substrate in the plasma
- Low throughput
- **PE mode:** - Wafer, anode & reactor grounded (large electrode)
  - Cathode HF driven (small electrode)



- Prevalent chemical etching by neutral radicals
- Low-energy ion bombardment at wafer (plasma potential V_p ~ 10 eV)



Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.7.3.3 Reactive Ion Etching

Parallel Plate (Planar) Reactor

p < 10 Pa

- Subtrate in the plasma
- Low throughput
- **RIE mode:** - Wafer HF driven (cathode, small electrode)
  - Reactor & anode grounded (large electrode)



- Ion bombardment at wafer, physical component can be tuned from low to high by voltage (Cathode voltage V_o depends on RF power and external DC bias, 0.1 - 1 keV)
- RIE combines the benefits of chemical etching along with that of directional ion milling
- The combination etch results in a selectivity ratio between SiO_2 and Si of 35 compared with 10 in plasma only etching
- "RIE has become the choice for all advanced processes" (AMAT)



Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

High Density Plasma (HDP) Reactors

- High Density Plasma: **ICP**, TCP, DPS, MERIE, µW, MORIE, **ECR**
  High efficient transfer of electromagnetic energy into the plasma
  --> high density of reactive particles

Inductively Coupled Plasma (ICP) reactor

Goals: High plasma density
Separate control of physical and chemical etching

Schematic of ICP Chamber



Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.7.3.4 Photoresist Stripping

Source: AMAT - Microelectronics processing course

Key components of a microwave plasma asher including a 2.45-GHz microwave generator and process chamber.





Stripper rates for negative photoresist with different combinations of UV, ozone, and oxygen at 300 °C.

Advanced Integrated Circuit Technology

3.7.4 Process examples
3.7.4.1 Overview

A) Trench (Si): $Cl_2/Ar/N_2$ or Cl_2/HBr

$Si + 4Cl \rightarrow SiCl_4$ (bei T > - 40 °C) or

$Si + 4Br \rightarrow SiBr_4$ (bei T > +25 °C)



Source: "MNE 94" IBM, Siemens

B) Gate (Poly Si, Silicide): Cl_2/Ar, Cl_2/SF_6 or Cl_2/O_2

$Si + 4Cl \rightarrow SiCl_4$ (bei T > - 40 °C)

e.g. Tungsten silicide WSi_x:

$W + 6F \rightarrow WF_6$ (bei T > - 50 °C)

$W + 6Cl \rightarrow WCl_6$ (bei T > +90 °C) !



Source: SI 3/98 Lam Research

C) Via (oxidic films): C_4F_8/H_2 (O_2) or $CHF_3/C_2F_6/Ar$

$SiO_2 + 4F \rightarrow SiF_4 + O_2$ (at T > - 130 °C or

$SiO_2 + 4F + 2C \rightarrow SiF_4 + 2CO$ at T > - 130 °C)



Source: Etch Tech 4/96 Applied Materials

D) Interconnects (Al alloys): $BCl_3/Cl_2/N_2$

$Al + 3Cl \rightarrow AlCl_3$ (at T > + 60 °C)



Source: Etch Tech 7/96 Applied Materials

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.7.4.2 Dry Etching of Metals

Al (Si, Cu) Alloy

$AlCl_3$ is volatile above ~50 °C !
Al films are initially covered by native Al_2O_3, removal by ion bombardment
CuCl is volatile only above 250 °C, desorption needs additional energy at surface

Process control:

1. Phase: Prevailing ion bombardment for oxide removal

2. Phase: Prevailing chemical etching by Cl or Br radicals (from HCl, HBr)
   - Anisotropy has to be achieved by side-wall passivation
     → Polymerization is supported by addition of CH_4, $CHCl_3$, CHF_3
   - Soft ion bombardment to enable desorption of CuCl
     Problem: Selectivity to resist → Use *DUV hardened resist* or *hard masks*

3. Post-treatment: Immediate removal of Cl containing masks and polymers by fluorine treatment and intensive rinsing in water to prevent subsequent corrosion

TiW: CF_4/O_2 (isotropic) or CF_4

Mo: $CF_4/CBrF_3$

Au: $C_2Cl_2F_4$

W: CF_4/O_2; SF_6/Ar

ZfM Fraunhofer ENAS
Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.7.4.3 ILD Etching: Porous ULK Dual Damascene patterning

Patterning Scheme for JSR LKD5109 140 nm wire/280 nm pitch

❑ Dual Hard-mask, Partial Via First Approach in LKD 5109



- To reduce topography and
- To enable single layer resist

Source: LETI (ULISSE project)

ZfM Fraunhofer ENAS
Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Dual damascene LKD5109 140 nm wire/280 nm pitch



Source: LETI (ULISSE project)