3.6 Lithography and Mask Process

Outline

Status: 1.4.2012

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.6.1 Introduction

Purpose of Lithography:

- Pattern transfer from mask to wafer to form functional components
- Preliminary step for selective wafer treatment (e.g. doping)



© Infineon Technologies AG, 2005
Thomas Zell
Datum : 13.09.2005

Design Data Flow

Project Phase		Additional Structures	Data Format
Design	Chip: Functional description		VHDL, ...
Layout		Frame patterns, Test structures	GDSII
Layer Extraction			GDSII
Resolution Enhancement (RET)			GDSII



© AMTC GmbH & Co KG
Dr. Jan Hendrik Peters
Datum : 14.09.2004

Advanced Integrated Circuit Technology
5. Dresdner Sommerschule Mikroelektronik

Design Data Flow

Project Phase	Additional Structures	Data Format
Mask Rule Check (MRC)	Frame patterns, Test structures	GDSII
Mask Data-preparation(MDP, „Fracture“ 4x scaling)	Mixing in of Frame patterns, Test structures	MDP format (e.g. MEBES)
Mask Process Compensation, Process Bias, Pattern optimization	(automatic) generation of barcode, addition of alignment pattern	MDP format (e.g. VSB11)



Mask Fabrication

Lithographic process

ADVANCED MASK TECHNOLOGY CENTER
© AMTC GmbH & Co KG
Dr. Jan Hendrik Peters
Datum : 14.09.2004

Early Optical Lithography



Contact Printing — **Mask in direct contact with resist**
- Defects on Wafer and Mask
- Mask Lifetime

Proximity Printing — g ~ 10 µm — **Small Gap between Mask and Resist**
- Defects on Wafer
- Reduced Resolution

$$CD \cong \sqrt{\lambda g}$$

Projection Printing — **Mask Pattern projected by Lens on Resist**

Infineon technologies | TECHNISCHE UNIVERSITÄT DRESDEN | ZMD | AMD
© Infineon Technologies AG, 2005
Thomas Zell
Datum : 13.09.2005

Lithographic approaches



ZfM Fraunhofer ENAS
Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.



DUV wafer stepper PAS 5500/300

d_{min} = 0.25 µm

ASML Lithography

Excimer laser, DUV lenses from Zeiss (1996)

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.6.2 Lithographic Process

3.6.2.1 Overview

Wafer Prime (HMDS) — ARC Coating, ARC Bake

↓

Resist Coating

↓

***S**oft **B**ake, **P**ost **A**pply **B**ake*

↓

Exposure

↓

***P**ost **E**xposure **B**ake*

↓

Develop

↓

***H**ard **B**ake*

↓

(UV Harden)

Rework — **If Specifications are not met** → ARC Coating

↓

Pattern transfer (etching, implantation)

↓

Resist removal (stripping, dry, wet)



HMDS - Hexamethyldisilazan (Primer)
ARC - Anti-reflective coating

3.6.2.2 Resist

Type	Positive Optical Resist	Negative Optical Resist
Components		
– Matrix	nonvolac resin	cyclized synthetic rubber resin
– Sensitizer (PAC)	diazoquinones	bisarylzide
– Solvent	n-butyl acetate, xylene, etc.	aromatic solvent
– Developer	*Hydroxide*s	*organic solvents*

Mechanism

- Exposure to radiation leads to breakdown of PAC
- Dissolution rate in developer (hydroxide) changes

- Negative optical resist becomes insoluble in regions exposed to light
  - Photochemical reaction generates cross-linking to form 3D molecular network
  - New structure insoluble in developer (usually an organic solvent)

Detailed chemistry depends strongly on wavelength

PAC - photo-active compound

Resist removal (stripping)

Requirement: Complete removal of resist layers after patterning or implantation without damaging the underlying films

Approaches:

Weakly stressed resist:
Wet removal using
- acetone
- H_2O_2+ H_2SO_4
- hydroxyl amines

heavily stressed resist:
Dry removal (or dry + wet)

Dry resist removal using oxygen
(generation of CO, CO_2, H_2O)

- Plasma stripping in Barrel reactors



- Downstream stripping (less radiative damage)



- Plasma-free (ozone and UV) stripping



3.6.2.3 Exposure

Conceptual Design of Stepper/Scanner Optics



Illumination system
- source
- pupil shaping system
- homogenizer
- elements to eliminate temporal and spatial coherence
- energy sensor

Reticle
- fused Silica plate
- Cr patterns
- PSM materials and patterns
- pellicles

Projection system
- lens system
- TTL alignment optics
- variable aperture stop
- β half aperture angle, i.e. maximum acceptance angle that can be focused by the optical system

Wafer
- resists
- underlying thin films

Numerical Aperture NA = n sin β

n - refractive index, n = 1 for air, n = 1.4 for water @ 20 C and 193 nm
typical values for λ = 193 nm: NA = 0.85 (dry) NA = 1.2 (wet)
typical values for λ = 13.5 nm (EUV): NA = 0.25 ... 0.30

© Infineon Technologies AG, 2005
Thomas Zell
Datum : 13.09.2005

Criteria of imaging performance

Resolution



Fraunhofer diffraction: $\sin \alpha = 1.22\, \lambda / d$

Rayleigh's criterion defines two light points as resolved if the positions of both main maxima of intensity lay outside the range between the respective other main maximum and the related first diffraction minimum.

Equivalent formulation: The peak widths at half-maximum do not overlap.

Resolution limit = Minimum line width:

$$l_{min} = k_1 \cdot \frac{\lambda}{NA}$$

3 ways to reduce l_{min}:
- *reduce λ (→ DUV → EUV → X-ray)*
- *increase NA (immersion litho)*
- *reduce k_1 (RET)*

Rayleigh:	k_1 = 0.61	*depending on the optical system,*
without RET:	k_1 = 0.61 ... 0.8	*resist capability, tool control,*
now: λ = 193 nm NA ≈ 0.85 (dry)	k_1 ≈ 0.4	*reticle pattern adjustment,*
theoretical limit:	k_1 = 0.25	*process control, RET*

RET = Resolution enhancement Techniques

ZfM Fraunhofer ENAS
Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Lithography Trends





Numerical Aperature Trend for commercial exposure systems

k_1 trend

http://www.icknowledge.com/misc_technology/Immersion%20Lithography.pdf

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Depth of focus (DOF)

Criterion for depth of focus (DOF) is that two optical path lengths do not differ by more than λ / 4

$$DOF \approx \pm k_2 \cdot \frac{\lambda}{(NA)^2}$$

now: $k_2 \approx 1.0$
theoretical limit: k_2 = 0.5 (dense L/S pattern)



Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Advanced Integrated Circuit Technology

Technology Nodes and Lithography Wavelength



NGL - next generation lithography
IPL - ion projection lithography
DUV - deep ultraviolet
EPL - electron projection lithography
EUV - extreme ultraviolet

Advanced Integrated Circuit Technology

Light sources

- High pressure Hg arc lamp
  - g - line (436 nm)
  - h - line (405 nm)
  - i - line (365 nm)
- DUV laser (Excimer laser, excited dimer)
  - KrF (248 nm)
  - ArF (193 nm)
  - F_2 (157 nm), cancelled !
- EUV (13.5 nm)
  - laser- or discharge-produced plasmas (**Xe**,Sn,In)
  - electron-impact ionization (excitation) of atomic inner shells (e.g. L-shell of Si)

Hg lamp spectrum



Source: L.F.Thompson, C.G.Wilson, M.J.Bowden, Introduction to Microlithography, Am. Chem. Soc. 1983

Optic materials

Refractive optics



Light source	Optical system	NA	Resolution (nm)
i - line (365 nm)	special high-purity glass ~30 individual lens elements	0.45 - 0.65	> 280
KrF (248 nm)	fused silica ~30 individual lens elements	0.4 - 0.7	> 150
ArF (193 nm)	quartz glass calcium fluoride (single lenses)	0.65 - 0.93	> 55
	immersion	>1	> 45
EUV (13.5 nm)	reflective optics (mirrors only) vacuum		< 45

Immersion Lithography



Source: Geppert, L. **Chip making's wet new world** Spectrum, IEEE Volume 41, Issue 5, May 2004 Page(s): 29 - 33

3.6.3 Mask Manufacturing process

3.6.3.1 Overview



© AMTC GmbH & Co KG
Dr. Jan Hendrik Peters
Datum : 14.09.2004

5. Dresdner Sommerschule Mikroelektronik
Advanced Integrated Circuit Technology

3.6.3.2 e-Beam Writing







Writing Challenges

– High data volume for fracturing of design
  - Data volume expected increase approx. factor 10 from 110 nm to 65 nm designs
  - Fracturing time example: 90 nm design with 15 GB data volume 4 hours on 76 processors
  - Write time for complex masks 10-20 hours

ADVANCED MASK TECHNOLOGY CENTER
© AMTC GmbH & Co KG
Dr. Jan Hendrik Peters
Datum : 14.09.2004

3.6.3.3 Mask Inspection and Repair

Inspection techniques

- Die-to-Die
  - Compare identical designs on mask
- Die-to-Database
  - Compare design on mask to design in database
- Check printability of found defect with aerial image tool



Repair techniques



© AMTC GmbH & Co KG
Dr. Jan Hendrik Peters
Datum : 14.09.2004

3.6.3.4 Pellicle Mounting







Pellicle mounting line (AMTC)



Source: http://www.amtc-dresden.de/index_gallery.php

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.6.4 Resolution Enhancement Technologies (RET)

Resolution: $l_{min} = k_1 \cdot \frac{\lambda}{NA}$ *RET shift k_1 below the Rayleigh limit down towards 0.25*

3.6.4.1 Optical Proximity Correction (OPC)

Proximity Effects: Effects that lead to a difference of the designed features to the imaged structures due to the proximity of the structures

Cause: Different diffraction orders contribute to imaging

Result:
- line shortening
- dense/isolated vias
  - CD difference
  - process window impact





Number of Diffraction Orders determine Quality of reassembled Image

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Optical Proximity Correction is a pattern dependent technology bias

Correction of linewidth deviations depending on proximity to neighbours



OPC Curve



Leads to big CD Variation for nominally same Feature Size
Especially critical in Gate Level

Infineon technologies
92. VDE Symposium September 2002
Karl Heinz Küsters
MDC TDT
Memory Products
6. Dresdner Sommerschule Mikroelektronik

⇨ **Enhancement of pattern fidelity**
line mode, hammerheads, serifs

⇨ **Enhancement of process window for isolated lines and spaces**
assist-bars



Big data volume for mask generation



ADVANCED MASK TECHNOLOGY CENTER
© AMTC GmbH & Co KG
Dr. Jan Hendrik Peters
Datum : 14.09.2004

Optical proximity correction: structural adjustments

Infineon technologies
92. VDE Symposium September 2002

From Layout to wafer:

Structures on masks changed

to print the same structure on the wafer as in the layout of the circuit



Karl Heinz Küsters
MDC TDT
Memory Products

ZfM Fraunhofer ENAS
Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Optical proximity correction: assists / scatter bars

From Layout to wafer:

Assist structures on mask to improve image

Big Challenges for mask production !



Karl Heinz Küsters
MDC TDT
Memory Products

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.6.4.2 Off-Axis Illumination (OAI)

OAI is the use of an aperture to limit the light from an illumination system to only enter a lens system at an angle to the optical axis of the lens system.



By changing the illumination conditions the diffraction orders captured by the lens can be changed.

OAI is used with advanced exposure systems such as steppers and scanners to improve resolution at a given wavelength.

© Infineon Technologies AG, 2005
Thomas Zell
Datum : 13.09.2005



By choosing the appropriate illumination conditions resolution and process window can be optimized.

Shape	standard	quadrupole	annular	small sigma
Resolution & DOF	bad	considerably improved	improved	improved if applied with PSM
Pattern dependence	weak	strong	medium	

3.6.4.3 Phase Shift Masks (PSM)

Purpose: Enhanced contrast --> enhanced resolution --> improvement of process window

Basic principle: Introduction of a phase difference of 180º on specific parts of the mask structure



Kahng et. al., 1999 DAC

- The Phase Shifter reverses the sign of the electric field.
- The light diffracted into the nominally dark region will interfere destructively.
- So PSM can help in resolving the features which may be violating the minimum spacing design rule by assigning opposite phases to the conflicting features.

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Principle of Alternating Phase Shift Masks (AltPSM)



Required etch depth for 180° phase shift:

$$d = \frac{\lambda}{2\ (n-1)}$$

Other names for an alternating PSM:
- *strong PSM*
- *Levenson type PSM*

Benefit: Better resolution, enlargement of process latitude & DOF in lithography;

Application: Poly, AA, DT, metal levels

Principle of Halftone Phase Shift Masks (HTPSM)



Required thickness for 180° phase shift:

$$d = \frac{\lambda}{2\ (n-1)}$$

Benefit: Enlargement of process latitude in lithography; small improvement of resolution.

Application: Levels with contact-holes or similar structures.

Other names for an halftone PSM:
- attenuated PSM (AttPSM)
- embedded PSM
- weak PSM
- special: chromeless PSM (CPL)

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

PSM Types

Binary Masks | **Attenuated Phase-Shift Mask (AttPSM)** | **Alternating Phase-Shift Mask (AltPSM)**



Source: ASML

Special application:

Chromeless Phase Lithography (CPL)

- complex mask manufacturing process
- need for a second "Trim" reticle --> 2 Exposures

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

3.6.4.4 Double Exposure (DE)

Basic ideas: - Double patterning !
- Reduction of k_1 below the theoretical limit of 0.25 for a single print (pitch 100 nm, NA = 0.75, λ = 193 nm --> k_1 = 0.19)
- Separation of critical features aligned in X and in Y direction, resp., for improved OAI



Source: http://www.imec.be/wwwinter/mediacenter/en/SR2005/html/142317.html

Double patterning approach to obtain 100 nm pitch structures with 193 nm optical lithography. Cross-sections of trenches after the second patterning step and after metallization. Corresponding electrical results are shown left.

Double Dipole Lithography (DDL)

- special kind of DE



Double dipole lithography (DDL) breaks a mask into two layers, one with critical features aligned in the X axis, and one with critical features aligned in the Y axis.

Source: S. Hsu et al., "65 nm Full-Chip Implementation Using Double Dipole Lithography," *Proc. SPIE*, 2003, Vol. 5040, p. 215.

Only for internal use at TU Chemnitz for study purposes.
Unauthorized copying and distribution is prohibited.

Combination of RET Solutions

- This is what the designer drew
- Added ‘scattering bars’ and serifs to make the polygon print more exactly
- Added additional phase features to allow printing smaller features at the same wavelength



Accurate and flexible modeling is key!



(Courtesy ASML)