

Reliability Data Report Product Family R547

LTC4266 / LTC4270 / LTC4274 / LTC4359 / LTC4364 / LTC4365 / LTC4366



Reliability Data Report Report Number: R547 Report generated on: Wed Oct 31 11:44:12 PDT 2012

OPERATING LIFE TEST									
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE	NEWEST DATE	K DEVICE HRS	No. of FAILURES				
		CODE	CODE	(+125°C) ¹	2,3				
SSOP/TSSOP	231	0848	1150	231	0				
QFN/DFN	77	1047	1047	77	0				
Totals	308	-	-	308	0				
HIGHLY ACCELERATED STRESS TEST AT +131 DEG C / 85% RH									
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE	NEWEST DATE	K DEVICE HRS	No. of FAILURES				
		CODE	CODE	(+85°C) ⁴					
SSOP/TSSOP	51	1041	1041	144	0				
Totals	51	-	-	144	0				
PRESSURE COOKER TEST AT 15 PSIG , +121 DEG C									
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE	NEWEST DATE	K DEVICE HRS	No. of FAILURES				
I AGRAGE I II E	OAIIII EE OIEE			K BEVIOL IIIKO	No. of FAILORES				
SSOP/TSSOP	77	CODE 0829	CODE 0829	25	0				
Totals	77	- 0029	- 0029	25	0				
TEMP CYCLE FROM -65 TO 150 DEG C									
			NEWEST DATE	K DEVICE	No of EAU LIDEO				
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE	NEWEST DATE	K DEVICE	No. of FAILURES				
		CODE	CODE	CYCLES					
SSOP/TSSOP	223	0806	0838	187	0				
SOIC/SOT/MSOP	50	1152	1152	50	0				
Totals 273 237 0									
THERMAL SHO	OCK FROM -65	TO 150 DEG C							
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE	NEWEST DATE	K DEVICE	No. of FAILURES				
		CODE	CODE	CYCLES					
SSOP/TSSOP	153	0829	0838	153	0				
SOIC/SOT/MSOP	50	1152	1152	50	0				
Totals	203	-	-	203	0				
HIGH TEMPER	ATURE BAKE	AT 150 DEG C							
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE	NEWEST DATE	K DEVICE HRS	No. of FAILURES				
PACKAGE TIPE									
PACKAGE TIPE		CODE	CODE						
SSOP/TSSOP	100	CODE 0829	CODE 0838	100	0				

(1) Assumes Activation Energy = 0.7 Electron Volts
(2) Failure Rate Equivalent to +55 °C, 60% Confidence Level =5.95 FITS
(3) Mean Time Between Failure in Years = 19179.5

(4) Assumes 20X Acceleration from 85 °C to +131 °C Note 1: 1 FIT = 1 Failure in One Billion Hours.

Note 2: HAST, PCT, Temp Cycle & Thermal Shock are subjected to Preconditioning per J-STD-020.



Reliability Data Report Report Number: R547 Report generated on: Wed Oct 31 11:44:12 PDT 2012

HIGH TEMPERATURE BAKE AT 175 DEG C								
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE	NEWEST DATE	K DEVICE HRS	No. of FAILURES			
		CODE	CODE					
SSOP/TSSOP	95	0829	0838	95	0			
Totals	95	-	-	95	0			