



Paint Specifications For:



**2515 Hwy A1A
Cocoa Beach, Florida 32931**



Shawn Gooden 9/25/2026
Professional Coatings Representative
321-403-9305
shawn.k.gooden@sherwin.com



The Sherwin-Williams Company

Areas of Concern



Concern: Chalking paint.

Solution: Surface needs to be pressure washed with cleaning solution specified at a minimum psi of 3000. Scraping/sanding will be required for peeling/checked paint. Follow painting specifications listed in "Recommended Coatings Systems" section of specification.



Areas of Concern



Concern: Peeling paint (multiple layers).

Solution: Surface needs to be pressure washed with cleaning solution specified at a minimum psi of 3000 with the intention of removing all failing coating. Scraping/sanding will be required for peeling/checked paint. Follow painting specifications listed in "Recommended Coatings Systems" section of specification.



Areas of Concern



Concern: Rust.

Solution: All ferrous metals should be thoroughly cleaned and all loose rust or mill scale be removed by wire brush, scraper and/or power tool, such as an electric drill with wire brush attachment. Any rust spots or bare metal should receive the appropriate prime coat. Any hard, glossy surfaces should be dulled. Follow painting specifications listed in “Recommended Coatings Systems” section of specification.



The Sherwin-Williams Company

Areas of Concern



Concern: Stucco repairs.

Solution: Surface needs to be pressure washed with cleaning solution specified at a minimum psi of 3000. A full prime is required for all bare stucco/stucco repairs.



Areas of Concern



Concern: Peeling paint.

Solution: Surface needs to be pressure washed with cleaning solution specified at a minimum psi of 3000. Scraping/sanding will be required for peeling/chipped paint. Follow painting specifications listed in "Recommended Coatings Systems" section of specification.



The Sherwin-Williams Company

Scope

The work will consist of all preparation, painting, finishing work, clean up and related items necessary to complete work described in these specifications and listed in the remaining pages included with in.

A. Scope of Work

Without restricting the volume or generality of the above, the work to be performed shall include, but is not limited to the following:

1. Pressure washing all exposed surfaces to be painted at a minimum of 3000 psi with chemical injector and either bleach solution or Simple Green solution.
2. Caulking of all exposed cracks and voids around doors, windows, and other areas as necessary.
3. **Painting of: all building on property**
 - All exterior masonry/stucco surfaces (walls/ceilings/perimeter wall)
 - Decorative stucco (option to repair/resurface)
 - All railings/guardrails on property
 - Pool fence/railings
 - Entrance/Unit doors
 - Walkways/Stairs/Landings (previously painting)
 - Steel supports on balconies
 - Gutters/Soffits/Fascia/Downspouts
4. **Exclusions**
 - Shutter boxes & guides
 - Any surface not listed above



The Sherwin-Williams Company

B. Materials

1. All materials specified are from **The Sherwin-Williams Company.**
2. All paints shall be delivered to the job site in the original container with the manufacturer's label intact.
3. The paint shall be used and applied per label and data sheet instructions. The material shall not be thinned or modified in any way unless specified herein. Proper surface preparation and condition of surface shall be strictly adhered to.

C. Protection of Substrates not to be painted

1. Contractor shall protect his/her work at all times and shall protect all adjacent work and materials by suitable covering or other methods during progress of work. The contractor will protect all adjacent areas not to be painted by taking appropriate measures. Areas to be protected are windows, brick, surrounding lawn, trees, shrubbery, floor and steps. Upon completion of work, he/she shall remove all paint droppings and over-spray from floors, glass, concrete and other surfaces not specified to be painted.

D. Minimum Specifications

1. If instructions contained in this specification, bid documents or painting schedule are at variance with the paint manufacturer's instructions or the applicable standard, and codes listed, surfaces shall be prepared and paint applied to suit the higher standard, as determined by Sherwin-Williams, the customer or management representative.

E. Resolution of Conflicts

1. Contractor shall be responsible to requesting prompt clarification when instructions are lacking, when conflicts occur in the specifications and/or paint manufacturer's literature, or the procedures specified are not clearly understood. Any questions concerning these specifications should be clarified prior to commencing the job. Any changes to these specifications would require written approval by Sherwin-Williams, the customer or customer's representative.



The Sherwin-Williams Company

F. Coordination of Work

1. The general contractor and subcontractor shall be responsible for coordination of his work with the other crafts and contractors working on the same job and with the Management Company or owner.

G. Safety

1. All pertinent safety regulations shall be adhered to rigidly. In addition, all safety noted on the manufacturer's product data sheets and labels shall be observed. Material Safety Data Sheets and Product Data Sheets are available from your local Sherwin-Williams store or representative.

H. Jobsite Visitation

1. The contractor shall be responsible for visiting the job site and familiarizing himself with the job and working conditions.
2. All work during application is subject to inspection by the owner or his representative. Sherwin-Williams will also perform periodic site visits.
3. It will be the paint contractor's responsibility to own and use a wet film thickness gauge to check his application thickness as he proceeds.
4. When priming is complete, Sherwin-Williams will perform a site visit to determine if specifications were followed prior to final approval to move forward with the finish coat.
5. Any questions concerning these specifications should be clarified prior to commencing the job. Any changes to these specifications would require written approval of Sherwin-Williams and the owner or his representative.

I. Surface Preparation

1. Each surface shall be cleaned and prepared as specified. The painting contractor is responsible for the finish of his work. Should any surface be found unsuitable to produce a proper paint or sealant finish, the project representative shall be notified, in writing, and no materials shall be applied until the unsuitable surfaces have been made satisfactory. Commencing of work in a specific area shall be construed as acceptance of surfaces and thereafter as fit and proper to receive finish. Contractor shall be fully responsible for satisfactory work.



The Sherwin-Williams Company

2. All deteriorated substrates (i.e. wood, hardboard siding, T-111) shall be replaced. New substrates will be box primed (6 sides) before installation in accordance with specifications.
3. All exterior surfaces to be painted shall be pressure cleaned to remove all dirt, mildew, chalk paint, and any foreign materials deterrent to the new finish (see Pressure Washing).
4. Seal and caulk all cracks around windows, doors, boards and joists using a high grade acrylic caulk. All the caulking unable to perform for the length of the warranty period should be removed and replaced with caulking as specified. Allow caulking to cure for (8) eight hours in dry weather before paint is applied. NOTE: It is recommended to apply all primer first and then apply caulk before top coat is applied. Use Sherwin-Williams C1100A Acrylic Siliconized Caulk or equivalent.
5. Knots and pitch streaks shall be scraped, sanded and spot primed before full priming coat is applied. All nail holes or small openings shall be caulked after priming coat is applied. Any wood that is rotten, cracked, delaminated or has water damage should be replaced. Any loose or peeling paint should be removed by sanding and scraping. All hard, glossy surfaces should be sanded down to create a profile for new paint to adhere. Fill nail holes, imperfections and cracks with putty (color to match primer). Edges, corners and raised grain shall be eased by sanding. Caulk all joints between wood items with an approved caulk.
6. All stucco surfaces should be cleaned to remove all chalk, dirt, stains, efflorescence and other surface contaminants. These areas shall be pressure washed and scrubbed with a bleach and/or cleaning solution. After cleaning if there is still chalk evident this should be brought to the owner's attention in writing before any further work is done. Any areas of breakage shall be patched and dried before coatings are applied. Cracks should be repaired as follows: 1. Cracks less than 1/4" wide should be filled using Sherwin-Williams Brush Grade Elastomeric Patch. 2. Cracks wider than 1/4" should be cut and scraped to a "V" shape and filled with Sherwin-Williams Trowel Grade Elastomeric Patch.
7. All galvanized gutters and flashing should be thoroughly cleaned to remove loose and peeling paint. Any bare galvanized metal should be wiped down with a non-petroleum solvent cleaner.
8. All ferrous metals should be thoroughly cleaned and all loose rust or mill scale be removed by wire brush, scraper and/or power tool, such as an electric drill with wire brush attachment. Any rust spots or bare metal should receive the appropriate prime coat. Any hard, glossy surfaces should be dulled. Previously



The Sherwin-Williams Company

painted hand rails in sound condition should be washed down with a strong detergent-type cleaner such as Krud-Kutter, M1-House Wash or Simple Green.

J. Moisture

All areas that could cause paint failure due to moisture should be addressed and eliminated. This would include but is not limited to:

1. Gutters and downspouts not working properly.
2. Previous coats of paint not adhering properly.
3. Wood checking (cracks and splits in wood).
4. Deteriorated caulking.
5. Gaps between substrates.
6. Rotten wood.
7. Areas affected by water splashing.
8. Painting in inclement weather.
9. Painting an undry substrate.
10. Un-caulked nail holes.

K. Pressure Washing & Surface Preparation

1. Pressure wash or water blast to remove oil, grease, dirt, loose mill scale and loose paint by water at pressures of 2500-3000 p.s.i. at a flow of 4-14 gallons per minute. Power tool clean per SSPC-SP3 to remove loose rust and mill scale. Hand tool clean per SSPC-SP2 to sand all glossy surfaces to promote adhesion.
2. Remove mildew per the following:
 - a. Tools: Stiff brush or chemical injector power washer method.
 - b. Mix a solution of either Simple Green House and Siding Wash or KrudKutter House Wash per label instructions.
 - c. Use application methods described above until the surface is visibly wet.
 - d. In confined areas, use a brush to apply the solution.
 - e. After mildew spores have been destroyed and the stains cleaned, rinse with clean water to thoroughly remove the bleach solution. **Note:** If residue is left on the substrate problems may occur with the finish coat of paint.
 - f. Allow substrate to dry completely before painting.



The Sherwin-Williams Company

L. Application

1. Contractor shall be responsible for notification of Owner's Representative before beginning work if conditions substantially exceed Scope of Work.
2. Only skilled mechanics shall be employed. Applications may be by brush, roller or spray, upon acceptance from Owner.
3. At least one English speaking contractor's representative will be on the job at all times.
4. Contractor shall protect his/her work at all times and shall protect all adjacent work and materials by suitable covering or other method during progress of the work. Upon completion of work, he/she shall remove all paint and varnish spots from floors, glass and other surfaces. He shall remove from premises all rubbish and accumulated materials of whatever nature not caused by others and shall leave his part of work in a clean, orderly, and acceptable condition.
5. Remove and protect hardware, accessories, device plates, lighting fixtures, factory finished work and similar items or provide ample in-place protection. Upon completion of each space, carefully replace all removed items.
6. Cover all electrical panel box covers and doors before painting walls. Omit if covers have been previously painted.
7. Materials shall be applied under adequate illumination, evenly spread and flowed on smoothly to avoid runs, sags, holidays, brush marks, air bubbles and excessive roller stipple.
8. All coats shall be dry to manufacturer's instructions before applying succeeding coats.
9. Coverage and hide shall be complete. When color, stain, dirt, or undercoats show through final coat of paint, surface shall be covered by additional coats until paint film is of uniform finish, color, appearance and coverage (regardless of amount of coats specified).
10. All suction spots or "hot spots" in plaster or cement after application of first coat shall be touched up before applying second coat.
11. When spray painting is specified, contractor shall finish 100 square feet by spraying a sample of finish upon request of Owner. This shall be finished with materials specified and shall be called a Pilot Wall.



The Sherwin-Williams Company

12. Exterior doors shall have tops, bottoms, and side edges finished same as exterior faces of doors.
13. Building by building inspections will be made by the Owner or his representative. Sherwin-Williams will provide periodic site visits for the purpose of extending the material warranty.
14. All repairs, replacements and applications are to meet or exceed all manufacturer's and attached specifications and all applicable codes.

M. Workmanship & Application Conditions

1. Keep surfaces dust, dirt and debris free before and during painting.
2. Execute work in accordance with label directions. Coating application shall be made in conformance to this specification and to the manufacturer's paint instruction on the labels and product data sheets.
3. All work shall be accomplished by skilled workman familiar with and trained to do this type of work and they shall be further qualified to operate or use the equipment or rigging needed to accomplish this work.
4. All shrubbery, outside carpeting and sprinkler systems shall be fully protected against damage during each stage of the painting project.
5. Paint all previously painted surfaces to include but not be limited to; utilities and phone boxes (if allowed by local utility companies), ground transformers, stair systems, light poles and fixtures, pool fence, electrical boxes (meter boxes and A/C main disconnects) and underside of balconies.
6. All exterior substrates designated not to receive paint coatings shall be kept free of paint residue, i.e. windows, outdoor carpeting, walkways, etc.
7. Owner shall provide water and electricity from existing facilities.
8. Normal safety and "wet paint" signs, necessary lighting and temporary roping off around work areas shall be installed and maintained in accordance with OSHA requirements while the work is in progress.
9. A progress schedule shall be furnished by the contractor for approval and shall be based on the contract completion date. Contractor shall advise the Owner of those areas in which work is to be performed sufficiently in advance of the work schedule to permit the Owner to prepare for the work, advise residents, move vehicles, etc.



The Sherwin-Williams Company

10. Do not paint over any code required labels or any equipment identification, performance rating, name or nomenclature plates.

N. Weather

1. Surfaces must be clean and moisture free. Prime and paint as soon as possible. No painting shall be done immediately after a rain or foggy weather, or when the temperature is below 50 degrees F. substrate temperature must be 5 degrees F., or more above dew point temperature while painting and during coatings cure. Avoid painting surfaces while they are exposed to a full hot sun.
2. Stop exterior painting early enough to permit paint film to set up before condensation occurs (as caused by night temperature drops).

O. Color Schedule

1. To be approved by owners.
2. The owner and project coordinator should be aware that certain colors, especially darker tones, fade more rapidly than other colors, regardless of the product manufacturer, product type, or substrate to which the product is applied. It is advisable for the owner, project coordinator, and/or person responsible for color selection to consult with Sherwin-Williams early in the planning stage to assure the most durable combination of tinting formulation is used to achieve the desired color. Additionally, color selection affects the hiding ability of the finish coats. The specification is written intending for the finish coat to cover.

P. Warranty

1. In accordance with the attached specification and painting systems, The Sherwin-Williams Company will issue a seven or ten year warranty based upon product defect. A sample is available upon request.



The Sherwin-Williams Company

Recommended Coatings Systems

Thank you for the submittal of Sherwin-Williams products on the above referenced project. The Sherwin-Williams Co. certifies that the products we intend to furnish will meet or exceed the performance requirements of the job specifications.

Surface preparation, application methods, spreading rates, wet and dry film thicknesses will be determined by the attached specifications and our material data sheets, available at www.sherwin-williams.com, except as noted below.

Exterior System

All surface contamination, such as mildew, chalk, grease, dirt, grime, rust, efflorescence, old loose peeling paint, rotten wood and hard glossy surfaces needs to be removed by pressure washing, prep work and hand tool clean, before a new coating system can be applied. Be sure to read and follow the Data Pages before application.

Minimum recommended surface preparation:

SSPC-SP1 Remove all oil, grease, chalk and other surface contamination
SSPC-SP2 Remove all rotten wood, peeling paint and rust

Surface Cleaner: A-1 Beach, Simple Green House & Siding Cleaner, or KrudKutter Wash Cleaner

Caulking / Sealant: Elastomeric Patch, Shermax Urethanized Sealant, Loxon S1 Urethane Sealant.

Crack Repair:

Identify all cracks in the existing substrates and repair per manufacturer's recommendation

- A. For hairline cracks 1/16 inch or less wide - seal with Conseal Elastomeric Patching Material Brush Grade
- B. For cracks larger than 1/16 inch, route the crack open to a uniform size by mechanical methods. Clean out crack with water and allow to completely dry. Apply a fresh bead of Loxon S1 Urethane Sealant per the specifications. Be sure to feather edge the sealant beyond the edge of the crack.



The Sherwin-Williams Company

Recommended Coatings Systems

Masonry/Stucco Surfaces

A. Prime Coat: Loxon Clear or Pigmented Acrylic Masonry Conditioner, A24 series

Loxon Conditioner is a 100% acrylic emulsion conditioner that will penetrate and seal interior and exterior surfaces and bond light chalk to the surface. With excellent alkali and efflorescence resistance, this sealer allows new concrete, stucco, and other cementitious surfaces to be coated prior to a 30-day cure, and will adhere to new or existing concrete with a pH of 6 to 13.

B. Finish Coat: Super Paint 100% Acrylic Exterior Satin, A89 series (7 year)

SuperPaint Exterior Latex, with resistance to early dirt pick up, provides outstanding performance on properly prepared aluminum and vinyl siding, wood, hardboard, masonry, cement, brick, block, stucco, and metal down to a surface and air temperature of 35°F.

Or

B. Finish Coat (1 coat): Latitude 100% Acrylic Exterior Satin, K62 series (10 year)

Latitude™ Exterior Acrylic Satin gives painters more flexibility in their schedules and extends the painting season. Latitude is formulated with ClimateFlex Technology™, providing exceptional early moisture resistance and smooth application and appearance at extreme temperatures (application at 35°F-120°F (1.7°C - 48.8°C) air, surface and material temperatures) and is resistant to early dirt pick up. Latitude provides outstanding performance on properly prepared aluminum and vinyl siding, wood siding, clapboard, shakes, shingles, plywood, masonry, and metal. Key Attributes and Benefits: ClimateFlex Technology™ Excellent application, flow and leveling Great dirt pick up resistance.

Fiberglass or Wooden Doors

Prime Coat (as needed): Pro Industrial Pro-Cryl Universal Primer, B66 series

Pro Industrial Pro-Cryl® Universal Primer is an advanced technology, self cross-linking acrylic primer. It is rust inhibitive and was designed for both construction and maintenance applications. It can be used as a primer under water-based or solvent-based high performance topcoats.

B. Finish Coat (1 coat): Pro Industrial WB Urethane Alkyd Enamel, B53 series

Pro Industrial Waterbased Alkyd Urethane Enamel is a premium quality interior/exterior enamel formulated with a urethane modified alkyd resin system for high performance. It provides beauty and durability when applied to interior/exterior surfaces such as properly prepared drywall, wood, masonry and metal. It brings together the convenience and ease of use of a waterborne coating with the performance and coating characteristics of a traditional oil-based enamel.



The Sherwin-Williams Company

Recommended Coatings Systems

Metal Doors & Steel Supports

A. Prime Coat (as needed for rust): Pro Industrial Kem Kromik Universal Metal Primer, B50 series

KEM KROMIK UNIVERSAL METAL PRIMER is a rust inhibiting, modified phenolic alkyd resin primer designed for use over iron and steel substrates. Can be used as a universal primer under high performance topcoats. Suitable as a barrier coat over conventional coatings which would normally be attacked by strong solvents in high performance coatings. Recommended Spreading Rate per coat: Wet mils: 6.0-8.0 Dry mils: 3.2-4.2 Coverage sq. ft. per gallon: 202-265

B. Finish Coat (1 coat): Pro Industrial WB Urethane Alkyd Enamel, B53 series

Pro Industrial Waterbased Alkyd Urethane Enamel is a premium quality interior/exterior enamel formulated with a urethane modified alkyd resin system for high performance. It provides beauty and durability when applied to interior/exterior surfaces such as properly prepared drywall, wood, masonry and metal. It brings together the convenience and ease of use of a waterborne coating with the performance and coating characteristics of a traditional oil-based enamel. Recommended Spread Rate per coat: Wet mils: 4.0 - 5.0 Dry mils: 1.4 - 1.7 Coverage: 320 - 400 sq ft/gal

Garage Doors

A. Prime Coat (as needed for rust): Pro Industrial Kem Kromik Universal Metal Primer, B50 series

KEM KROMIK UNIVERSAL METAL PRIMER is a rust inhibiting, modified phenolic alkyd resin primer designed for use over iron and steel substrates. Can be used as a universal primer under high performance topcoats. Suitable as a barrier coat over conventional coatings which would normally be attacked by strong solvents in high performance coatings. Recommended Spreading Rate per coat: Wet mils: 6.0-8.0 Dry mils: 3.2-4.2 Coverage sq. ft. per gallon: 202-265

B. Finish Coat (1 coat): Pro Industrial WB Urethane Alkyd Enamel, B53 series

Pro Industrial Waterbased Alkyd Urethane Enamel is a premium quality interior/exterior enamel formulated with a urethane modified alkyd resin system for high performance. It provides beauty and durability when applied to interior/exterior surfaces such as properly prepared drywall, wood, masonry and metal. It brings together the convenience and ease of use of a waterborne coating with the performance and coating characteristics of a traditional oil-based enamel. Recommended Spread Rate per coat: Wet mils: 4.0 - 5.0 Dry mils: 1.4 - 1.7 Coverage: 320 - 400 sq ft/gal



The Sherwin-Williams Company

Recommended Coatings Systems

Gutters/Downspouts/Soffits/Fascia

A. Prime Coat: Loxon Clear or Pigmented Acrylic Masonry Conditioner, A24 series

Loxon Conditioner is a 100% acrylic emulsion conditioner that will penetrate and seal interior and exterior surfaces and bond light chalk to the surface. With excellent alkali and efflorescence resistance, this sealer allows new concrete, stucco, and other cementitious surfaces to be coated prior to a 30-day cure, and will adhere to new or existing concrete with a pH of 6 to 13.

B. Finish Coat: Super Paint 100% Acrylic Exterior Satin, A89 series

SuperPaint Exterior Latex, with resistance to early dirt pick up, provides outstanding performance on properly prepared aluminum and vinyl siding, wood, hardboard, masonry, cement, brick, block, stucco, and metal down to a surface and air temperature of 35°F.

Or

B. Finish Coat (1 coat): Latitude 100% Acrylic Exterior Satin, K62 series

Latitude™ Exterior Acrylic Satin gives painters more flexibility in their schedules and extends the painting season. Latitude is formulated with ClimateFlex Technology™, providing exceptional early moisture resistance and smooth application and appearance at extreme temperatures (application at 35°F-120°F (1.7°C - 48.8°C) air, surface and material temperatures) and is resistant to early dirt pick up. Latitude provides outstanding performance on properly prepared aluminum and vinyl siding, wood siding, clapboard, shakes, shingles, plywood, masonry, and metal. Key Attributes and Benefits: ClimateFlex Technology™ Excellent application, flow and leveling Great dirt pick up resistance.

If you have any questions regarding the specifications, please do not hesitate to contact me.

Respectfully,

Shawn Gooden

321-403-9305

Shawn.k.gooden@sherwin.com