

BS EN 338:2016



BSI Standards Publication

Structural timber — Strength classes

National foreword

This British Standard is the UK implementation of EN 338:2016. It supersedes BS EN 338:2009 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/518, Structural timber.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 83526 1

ICS 79.040

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2016.

Amendments/corrigenda issued since publication

Date	Text affected
<hr/>	

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 338

April 2016

ICS 79.040

Supersedes EN 338:2009

English Version

Structural timber - Strength classes

Bois de structure - Classes de résistance

Bauholz für tragende Zwecke - Festigkeitsklassen

This European Standard was approved by CEN on 30 January 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Content

	Page
European foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Symbols and abbreviations	5
5 Classification of structural timber	6
6 Allocation of a population to a strength class	10
6.1 Grading.....	10
6.1.1 Visual graded timber	10
6.1.2 Machine graded timber	10
6.2 Classification.....	10
6.2.1 Characteristic values.....	10
6.2.2 Allocation to a strength class	10
Bibliography.....	11

European foreword

This document (EN 338:2016) has been prepared by Technical Committee CEN/TC 124 “Timber structures”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2016, and conflicting national standards shall be withdrawn at the latest by October 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 338:2009.

Compared to EN 338:2009, the following modifications have been made:

- new table of strength classes for softwood species based on tension tests;
- extension with new classes in the table of strength classes for hardwood species based on edgewise bending tests;
- modification of some characteristic values for strength, stiffness and density;
- equations to determine the characteristic values of other strength properties from the grade determining properties has been transferred to EN 384.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

A strength class system groups together grades, species and sources with similar strength properties thus making them interchangeable. This then permits an engineer to specify a chosen strength class and use the characteristic strength values of that class in design calculations.

1 Scope

This European Standard establishes a system of strength classes for general use in design codes.

It gives characteristic strength and stiffness properties and density values for each class to which EN 14081-1 refers.

This standard is applicable to all softwood and hardwood timber for structural use, within the scope of EN 14081-1.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 384, *Structural timber — Determination of characteristic values of mechanical properties and density*

EN 14081 (all parts), *Timber structures — Strength graded structural timber with rectangular cross section*

3 Terms and definitions

For the purposes of this document, the following term and definition apply.

3.1

population

timber of one species or species combination and one source for which the strength, stiffness and density properties apply

4 Symbols and abbreviations

$E_{m,0,\text{mean}}$	mean characteristic value of modulus of elasticity in bending parallel to grain (in kN/mm ²);
$E_{t,0,\text{mean}}$	mean characteristic value of modulus of elasticity in tension parallel to grain (in kN/mm ²);
$E_{m,0,k}$	5-percentile characteristic value of modulus of elasticity in bending parallel to grain (in kN/mm ²);
$E_{t,0,k}$	5-percentile characteristic value of modulus of elasticity in tension parallel to grain (in kN/mm ²);
$E_{m,90,\text{mean}}$	mean characteristic value of modulus of elasticity in bending perpendicular to grain (in kN/mm ²);
$E_{t,90,\text{mean}}$	mean characteristic value of modulus of elasticity in tension perpendicular to grain (in kN/mm ²);
$f_{c,0,k}$	5-percentile characteristic value of compressive strength parallel to grain (in N/mm ²);
$f_{c,90,k}$	5-percentile characteristic value of compressive strength perpendicular to grain (in N/mm ²);
$f_{m,k}$	5-percentile characteristic value of bending strength (in N/mm ²);
$f_{t,0,k}$	5-percentile characteristic value of tensile strength parallel to grain (in N/mm ²);
$f_{t,90,k}$	5-percentile characteristic value of tensile strength perpendicular to grain (in N/mm ²);
$f_{v,k}$	5-percentile characteristic value of shear strength (in N/mm ²);

G_{mean}	mean characteristic value of shear modulus (in kN/mm ²);
ρ_k	5-percentile characteristic value of density (in kg/m ³);
ρ_{mean}	mean characteristic value of density (in kg/m ³)

5 **Classification of structural timber**

This standard provides for a number of strength classes, each designated by a number indicating the value of the edgewise bending or tension strength in N/mm².

For softwood species based on edgewise bending tests, the characteristic values of strength, stiffness and density for the strength classes Cxx, where xx refers to the 5-percentile characteristic bending strength value, are given in Table 1.

For softwood species based on tension tests, the characteristic values of strength, stiffness and density for the strength classes Txx, where xx refers to the 5-percentile characteristic tension strength value, are given in Table 2.

NOTE 1 Timber belonging to T classes is mainly intended for glulam and other cases where tension is the dominating load.

NOTE 2 The T classes correspond to classes L, LS or LD as in EN 14081-4 with some differences in tabulated properties and is also referred to in EN 14080.

For hardwood species based on edgewise bending tests, the characteristic values of strength, stiffness and density for the strength classes Dxx, where xx refers to the 5-percentile characteristic bending strength value, are given in Table 3.

NOTE 3 C and T classes may also be used for hardwoods with similar strength and density profiles such as e.g. poplar or chestnut.

The most common used strength classes in Europe are printed in bold.

Table 1 — Strength classes for softwood based on edgewise bending tests – strength, stiffness and density values

	Class	C14	C16	C18	C20	C22	C24	C27	C30	C35	C40	C45	C50
Strength properties in N/mm²													
Bending	$f_{m,k}$	14	16	18	20	22	24	27	30	35	40	45	50
Tension parallel	$f_{t,0,k}$	7,2	8,5	10	11,5	13	14,5	16,5	19	22,5	26	30	33,5
Tension perpendicular	$f_{t,90,k}$	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4
Compression parallel	$f_{c,0,k}$	16	17	18	19	20	21	22	24	25	27	29	30
Compression perpendicular	$f_{c,90,k}$	2,0	2,2	2,2	2,3	2,4	2,5	2,5	2,7	2,7	2,8	2,9	3,0
Shear	$f_{v,k}$	3,0	3,2	3,4	3,6	3,8	4,0	4,0	4,0	4,0	4,0	4,0	4,0
Stiffness properties in kN/mm²													
Mean modulus of elasticity parallel bending	$E_{m,0,mean}$	7,0	8,0	9,0	9,5	10,0	11,0	11,5	12,0	13,0	14,0	15,0	16,0
5 percentile modulus of elasticity parallel bending	$E_{m,0,k}$	4,7	5,4	6,0	6,4	6,7	7,4	7,7	8,0	8,7	9,4	10,1	10,7
Mean modulus of elasticity perpendicular	$E_{m,90,mean}$	0,23	0,27	0,30	0,32	0,33	0,37	0,38	0,40	0,43	0,47	0,50	0,53
Mean shear modulus	G_{mean}	0,44	0,50	0,56	0,59	0,63	0,69	0,72	0,75	0,81	0,88	0,94	1,00
Density in kg/m³													
5 percentile density	ρ_k	290	310	320	330	340	350	360	380	390	400	410	430
Mean density	ρ_{mean}	350	370	380	400	410	420	430	460	470	480	490	520
<p>NOTE 1 Values given above for tension strength, compression strength, shear strength, char. modulus of elasticity in bending, mean modulus of elasticity perpendicular to grain and mean shear modulus have been calculated using the equations given in EN 384.</p> <p>NOTE 2 The tension strength values are conservatively estimated since grading is done for bending strength.</p> <p>NOTE 3 The tabulated properties are compatible with timber at moisture content consistent with a temperature of 20 °C and a relative humidity of 65 %, which corresponds to a moisture content of 12 % for most species.</p> <p>NOTE 4 Characteristic values for shear strength are given for timber without fissures, according to EN 408.</p> <p>NOTE 5 These classes may also be used for hardwoods with similar strength and density profiles such as e.g. poplar or chestnut.</p> <p>NOTE 6 The edgewise bending strength may also be used in the case of flatwise bending.</p>													

Table 2 — Strength classes for softwood based on tension tests – strength, stiffness and density values

	Class	T 8	T 9	T 10	T 11	T 12	T 13	T 14	T	T 15	T 16	T 18	T 21	T 22	T 24	T 26	T 27	T 28	T 30
Strength properties in N/mm²																			
Bending	$f_{m,k}$	13,5	14,5	16	17	18	19,5	20,5	21	22	23	25,5	29	30,5	33	35	36,5	37,5	40
Tension parallel	$f_{t,0,k}$	8	9	10	11	12	13	14	14,5	15	16	18	21	22	24	26	27	28	30
Tension perpendicular	$f_{t,90,k}$	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4	0,4
Compression parallel	$f_{c,0,k}$	16	17	17	18	19	20	21	21	21	22	23	25	26	27	28	29	29	30
Compression perpendicular	$f_{c,90,k}$	2,0	2,1	2,2	2,2	2,3	2,4	2,5	2,5	2,5	2,6	2,7	2,7	2,7	2,8	2,9	2,9	2,9	3,0
Shear	$f_{v,k}$	2,8	3,0	3,2	3,4	3,6	3,8	4,0	4,0	4,0	4,0	4,0	4,0	4,0	4,0	4,0	4,0	4,0	4,0
Stiffness properties in kN/mm²																			
Mean modulus of elasticity parallel tension	$E_{t,0,mean}$	7,0	7,5	8,0	9,0	9,5	10,0	11,0	11,0	11,5	11,5	12,0	13,0	13,0	13,5	14,0	15,0	15,0	15,5
5 percentile modulus of elasticity parallel tension	$E_{t,0,k}$	4,7	5,0	5,4	6,0	6,4	6,7	7,4	7,4	7,7	7,7	8,0	8,7	8,7	9,0	9,4	10,1	10,1	10,4
Mean modulus of elasticity perpendicular	$E_{t,90,mean}$	0,23	0,25	0,27	0,30	0,32	0,33	0,37	0,37	0,38	0,38	0,40	0,43	0,43	0,45	0,47	0,50	0,50	0,52
Mean shear modulus	G_{mean}	0,44	0,47	0,50	0,56	0,59	0,63	0,69	0,69	0,72	0,72	0,75	0,81	0,81	0,84	0,88	0,94	0,94	0,97
Density in kg/m³																			
5 percentile density	ρ_k	290	300	310	320	330	340	350	350	360	370	380	390	390	400	410	410	420	430
Mean density	ρ_{mean}	350	360	370	380	400	410	420	420	430	440	460	470	470	480	490	490	500	520
NOTE 1 Values given above for bending strength, compression strength, shear strength, char. modulus of elasticity in tension, mean modulus of elasticity perpendicular to grain and mean shear modulus have been calculated using the equations given in EN 384.																			
NOTE 2 The bending strength values are conservatively estimated since grading is done for tension strength.																			
NOTE 3 The tabulated properties are compatible with timber at moisture content consistent with a temperature of 20 °C and a relative humidity of 65 %, which corresponds to a moisture content of 12 % for most species.																			
NOTE 4 Characteristic values for shear strength are given for timber without fissures, according to EN 408.																			
NOTE 5 These classes may also be used for hardwoods with similar strength and density profiles such as e.g. poplar or chestnut.																			
NOTE 6 The bending strength may be used in the case of edgewise or flatwise bending.																			

Table 3 — Strength classes for hardwoods based on edgewise bending tests – strength, stiffness and density values

	Class	D18	D24	D27	D30	D35	D40	D45	D50	D55	D60	D65	D70	D75	D80
Strength properties in N/mm²															
Bending	$f_{m,k}$	18	24	27	30	35	40	45	50	55	60	65	70	75	80
Tension parallel	$f_{t,0,k}$	11	14	16	18	21	24	27	30	33	36	39	42	45	48
Tension perpendicular	$f_{t,90,k}$	0,6	0,6	0,6	0,6	0,6	0,6	0,6	0,6	0,6	0,6	0,6	0,6	0,6	0,6
Compression parallel	$f_{c,0,k}$	18	21	22	24	25	27	29	30	32	33	35	36	37	38
Compression perpendicular	$f_{c,90,k}$	4,8	4,9	5,1	5,3	5,4	5,5	5,8	6,2	6,6	10,5	11,3	12,0	12,8	13,5
Shear	$f_{v,k}$	3,5	3,7	3,8	3,9	4,1	4,2	4,4	4,5	4,7	4,8	5,0	5,0	5,0	5,0
Stiffness properties in kN/mm²															
Mean modulus of elasticity parallel bending	$E_{m,0,mean}$	9,5	10,0	10,5	11,0	12,0	13,0	13,5	14,0	15,5	17,0	18,5	20,0	22,0	24,0
5 percentile modulus of elasticity parallel bending	$E_{m,0,k}$	8,0	8,4	8,8	9,2	10,1	10,9	11,3	11,8	13,0	14,3	15,5	16,8	18,5	20,2
Mean modulus of elasticity perpendicular	$E_{m,90,mean}$	0,63	0,67	0,70	0,73	0,80	0,87	0,90	0,93	1,03	1,13	1,23	1,33	1,47	1,60
Mean shear modulus	G_{mean}	0,59	0,63	0,66	0,69	0,75	0,81	0,84	0,88	0,97	1,06	1,16	1,25	1,38	1,50
Density in kg/m³															
5 percentile density	ρ_k	475	485	510	530	540	550	580	620	660	700	750	800	850	900
Mean density	ρ_{mean}	570	580	610	640	650	660	700	740	790	840	900	960	1020	1080

NOTE 1 Values given above for tension strength, compression strength, shear strength, char. modulus of elasticity in bending, mean modulus of elasticity perpendicular to grain and mean shear modulus, have been calculated using the equations given in EN 384.

NOTE 2 The tabulated properties are compatible with timber at moisture content consistent with a temperature of 20 °C and a relative humidity of 65 %, which corresponds to a moisture content of 12 % for most species.

NOTE 3 Characteristic values for shear strength are given for timber without fissures, according to EN 408.

NOTE 4 The edgewise bending strength may also be used in the case of flatwise bending.

6 Allocation of a population to a strength class

6.1 Grading

6.1.1 Visual graded timber

Visual graded timber shall be graded according to a grading standard that meets the requirements of EN 14081-1.

NOTE EN 1912 lists a number of visual grades and species that are allocated to the strength classes of this standard.

6.1.2 Machine graded timber

Machine graded timber shall meet the requirements of EN 14081 (all parts).

6.2 Classification

6.2.1 Characteristic values

The characteristic values of bending or tension strength, mean modulus of elasticity in bending or tension and density for the population concerned shall be determined in accordance with EN 384. Other strength and stiffness properties, as well as mean density values, are determined according to EN 384.

6.2.2 Allocation to a strength class

A population may be assigned to a strength class if its characteristic values of strength, mean modulus of elasticity and density equal or exceed the values for that strength class given in Table 1, 2 or 3.

Provided the settings are available in Approved Grading Reports, a grading machine may be set to grade directly to the strength class strength, stiffness and density values. Timber graded in this way should be referred to by the strength class number and marked according to EN 14081-1, EN 14081-2 and EN 14081-3.

Bibliography

- [1] EN 408, *Timber structures — Structural timber and glued laminated timber — Determination of some physical and mechanical properties*
- [2] EN 1912, *Structural Timber — Strength classes — Assignment of visual grades and species*
- [3] EN 14080, *Timber structures — Glued laminated timber and glued solid timber — Requirements*
- [4] EN 14358, *Timber structures — Calculation and verification of characteristic values*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK