Rustavi Metallurgical Plant

Rustavi Steel LLC

Mill Test Certificate № 826
EN 10204 / 3.1

Seller (Exporter)	Rustavi Steel LLC				
Consignee : **Address :** **Country :**	"FORPOST – M LTD" Dnipro, Dmytra Yavornytskoho avenue, 34/38a Ukraine				
Contract № :	№ 1008 (08.10.24) Specification № 17				
Description of goods:	Hot rolled seamless steel pipes	**HS Code**	73041930	**Standard**	EN 10210-1:2006
Freight car №	KE 7040 AP / AE 4070 XG	**Quantity of packages**	5	**Actual weight, t**	6.221

Package №	Heat №	Steel grade	Diameter, mm	Wall thickness, mm	Length of pipe, m	Quantity	Total length, m	Actual weight, t
2328, 2329, 2330, 2331, 2332	314682	S355J2H	298.5	8	11.63 – 11.91	9	106.66	6.221
					TOTAL:	9	106.66	**6.221**

Chemical composition (%)

Heat №	C x100	Mn x100	Si x100	S x1000	P x1000	Cr x100	Ni x100	Cu x100	Ti x1000	Al x1000	V x1000	Nb x1000	N x1000	As x1000	Mo x1000	B x1000	W x1000	CEV
314682	14	115	27	4	17	9	11	23	2	33	11	2	0	16	11	1	-	0.38

Mechanical properties

Heat № (Pipe sizes)	Tensile strength, R_m MPa	Yield strength, R_e MPa	Elongation A, (%)	Impact energy, KV_2, J t -20°C				Technological Test	Hydrostatic Test, MPa	NDT (Ultrasonic Test)	Heat-treatment Type
				1	2	3	Aver				
314682 (298.5x8)	551	371	30	81	94	79	85	ok	ok	ok	normalizing rolled

Semi-finished Material Information

Type	Heat Number	Manufacturer	Address	HS Code
Round Billet	314682	Rustavi Steel LLC	12, Gagarin str., 3700 Rustavi, Georgia	7207

CEV=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15

In compliance with the European Commission adopted Regulation (EU) 2023/1214 amending Regulation (EU) 833/2014 we prove and certify herewith that No steel inputs of Russian Federation origin and of the Republic of Belarus origin have been used for processing of products under this MTC

The raw round billets of HS 720719 have been produced by own melting shop, using Georgian steel scrap of HS 720441

Notes:

Tensile Test
Type of specimen – flat .Orientation of specimen – longitudinal.

Charpy Test

Orientation of specimen – transverse

Hydrostatic test
Testing pressure –71,4 bar. Holding time – 10 sec

NDT (UT)
Ultrasonic test was provided according to ISO 10893-10

Marking: Marking in accordance with the standard EN 10210-1 and the customer's requirements

Surface condition and dimensions of pipes - satisfactory.

Pipes are delivered with plain ends, pipe ends are cut square.

Pipes are absolutely free from cadmium

The delivered product corresponds to the requirements of Contract № 1008 (08.10.24). Specification № 17

CE 12 0045-CPR-1705	**RUSTAVI STEEL LLC** Gagarin Street 12, Rustavi 3700, Georgia **S355J2H EN 10210-1:2006** Hot-formed structural hollow sections Declaration of Performance № 1068
The Declaration of Perfomance (DoP) see here:	http://rmp.gc/assets/certificates/EN_10210_-_CE_Marking/5.pdf