PETROLEUM EQUIPMENT (THAILAND) CO., LTD.
บริษัท ปิโตรเลี่ยม อควปเม้นท์ (ไทยแลนด์) จำกัด

MILL TEST CERTIFICATE EN10204 3.1, GOST 10692

Customer			FORPOST-M LTD				Certificate №:		20250422005		PO:		PETH-3003-UA, SP.10					
Purchaser			FORPOST-M LTD				Date of Issue:		2025.04		Specification:		DSTU 8938:2019					
Product:			Hot rolled seamless carbon steel pipe				Length:		4--6 m		Flatten		GOOD					
No	Grade	Heat No	Dimension		Quantity		Chemical Composition								Physical Property			NDT/HP
			(mm) Diameter	(mm) Thickness	BUNDLES	Weight, tons	C	Si	Mn	P	S	Ni	Cr	Cu	TENSILE STRENGTH (Mpa)	YIELD STRENGTH (Mpa)	ELONGATION EL(%)	
1	45	B241022	121x30		1	1.705	0.45	0.27	0.6	0.011	0.005	0.01	0.013	0.007	605	340	20	NDT
2	45	A241023	127x25		2	3.438	0.45	0.27	0.6	0.011	0.005	0.01	0.013	0.007	605	340	20	NDT
3	20	D241223	180x20		2	7.26	0.19	0.27	0.51	0.011	0.006	0.01	0.013	0.007	485	280	31	NDT
4	45	B241221	219x30		2	6.43	0.45	0.27	0.6	0.011	0.005	0.01	0.013	0.007	605	340	20	NDT
5	20	D241016	219x45		2	8.83	0.21	0.26	0.48	0.013	0.005	0.009	0.012	0.006	479	279	32	NDT
6	20	B241017	245x25		2	7.86	0.19	0.27	0.51	0.011	0.006	0.01	0.013	0.007	485	280	31	NDT
7	20	C241018	273x45		10	12.01	0.21	0.26	0.48	0.013	0.005	0.009	0.012	0.006	479	279	32	NDT
8	20	B241018	457x20		2	2.538	0.2	0.26	0.47	0.012	0.006	0.009	0.011	0.007	481	280	30	NDT
9	20	A241020	480x20		2	2.639	0.21	0.26	0.48	0.013	0.005	0.009	0.012	0.006	479	279	32	NDT
10	20	C241020	530x25		2	2.648	0.2	0.26	0.47	0.012	0.006	0.009	0.011	0.007	481	280	30	NDT
Total:					27	55.358												

Surveyor:	We certify that all products has been manufactured, sampled, tested and inspected in accordance with the DSTU 8938:2019 and was found to meet the requirements. Residual Magnetism does not exceed 30 Gaus The test result is only responsible for sample	Inspector: Chief
		Stamp of Mill Inspector

PETROLEUM EQUIPMENT (THAILAND) CO., LTD. PETH PASS