Mill Test Certificate № 762

Seller (Exporter)	Rustavi Steel LLC
Consignee	"OKPOST – METTD"
Address	Dnipro, Dmytra Yavornytskoho avenue, 34/38,
Country	Ukraine
Contract № :	№ 1008 (08.10.24 r.), Specification № 13, 15, 16
Description of goods:	Hot rolled seamless steel pipes

Freight car №	a/m KE 7040 AP	AE 4070 XG	Quantity of packages	15	Actual weight, t	21.387

Package №	Heat №	Steel grade	Diameter, mm	Wall thickness, mm	Quantity	Actual weight, t	Actual weight, t
1538, 1539	314165	20	219	10	4	46.64	2.434
9644, 9653, 9655	312181	20	273	8	6	58.77	3.411
9661, 9662, 9663	309190	20	273	8	6	68.76	3.525
9672	311378	20	273	8	2	22.87	1.199
9680, 9681	312173	20	273	8	2	23.00	1.208
9367, 9368, 9419, 9420	313171	20	325	10	11	117.40	9.610
				TOTAL:	31	337.44	21.387

Chemical composition, (%)													
Heat №	C x100	Mn x100	Si x100	S x1000	P x1000	Cr x100	Ni x100	Cu x100	Ti x1000	Al x1000	V x1000	Nb x1000	N x1000
309190	18	61	29	8	11	8	15	22	1	36	9	2	6
311378	18	62	21	10	11	8	13	21	2	34	2	2	11
312173	18	64	23	9	17	13	10	20	1	32	2	2	5
312181	17	63	27	6	15	9	12	17	2	26	17	4	9
313171	17	65	27	7	15	5	16	20	3	33	18	3	0
314165	17	62	24	10	16	7	11	18	0	6	14	1	10

Mechanical properties						Flattening test
Heat № (Pipe sizes)	Tensile strength, MPa	Yield strength, MPa	Elongation (%)	Brinell hardness		
				Diameter of inprint, mm	Hardness number, HB	
314165 (219x10)	520	350	32	-	-	ok
312181 (273x8)	521	334	22	-	-	ok
309190 (273x8)	515	357	28	-	-	ok
311378 (273x8)	577	394	27	-	-	ok
312173 (273x8)	553	406	32	-	-	ok
313171 (325x10)	550	373	31	-	-	ok

Notes

Hydrostatic tes

For pipe 219x10 testing pressure 140 bar Holding time – 10 sec.
For pipe 273x8 testing pressure 90 bar Holding time – 10 sec.
For pipe 325x10 testing pressure 90 bar Holding time – 10 sec.
Paint markings made at the end of each pipe
Pipes made bevel cutting
Hydrostatic pressure sustainability guaranteed by production technology
Pipes completed in April, May 2025

TCD Certifier K. Khmaladze

Date: 30.06.2025