# PETROLEUM EQUIPMENT (THAILAND) CO., LTD.
# บริษัท ปิโตรเลี่ยม อควปเม้นท์ (ไทยแลนด์) จำกัด

## MILL TEST CERTIFICATE EN10204 3.1, GOST 10692

| Customer | | | FORPOST-M LTD | | | | Certificate №: | | 20250926001 | | | | PO: | | PETH-3003-UA, SP.12 | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Purchaser | | | FORPOST-M LTD | | | | Date of Issue: | | 2025.09.26 | | | | Specification: | | DSTU 8938:2019 | | | |
| Product: | | | Hot rolled seamless carbon steel pipe | | | | Length: | | 4--12 | | | | Flatten | | GOOD | | | |
| No | Grade | Heat No | Dimension | | Quantity | | Chemical Composition | | | | | | | | Physical Property | | | NDT/HP |
| | | | (mm) Diameter | (mm) Thickness | BUNDLES | Weight, tons | C | Si | Mn | P | S | Ni | Cr | Cu | TENSILE STRENGTH (Mpa) | YIELD STRENGTH (Mpa) | ELONGATION EL(%) | |
| 1 | 20# | C250613 | 70x16 | | 2 | 4.194 | 0.2 | 0.26 | 0.47 | 0.012 | 0.006 | 0.009 | 0.011 | 0.007 | 481 | 280 | 30 | NDT |
| 2 | 20# | E250514 | 83x16 | | 2 | 5.266 | 0.21 | 0.26 | 0.48 | 0.013 | 0.005 | 0.009 | 0.012 | 0.006 | 479 | 279 | 32 | NDT |
| 3 | 20# | D250519 | 83x22 | | 1 | 2.548 | 0.19 | 0.27 | 0.51 | 0.011 | 0.006 | 0.01 | 0.013 | 0.007 | 485 | 280 | 31 | NDT |
| 4 | 45# | B250602 | 83x22 | | 1 | 1.086 | 0.45 | 0.27 | 0.6 | 0.011 | 0.005 | 0.01 | 0.013 | 0.007 | 605 | 340 | 20 | NDT |
| 5 | 20# | C250614 | 89x20 | | 2 | 6.28 | 0.21 | 0.26 | 0.48 | 0.013 | 0.005 | 0.009 | 0.012 | 0.006 | 479 | 279 | 32 | NDT |
| 6 | 20# | E250515 | 89x25 | | 2 | 4.732 | 0.21 | 0.27 | 0.51 | 0.011 | 0.005 | 0.01 | 0.013 | 0.007 | 481 | 279 | 31 | NDT |
| 7 | 20# | D250520 | 127x30 | | 2 | 4.762 | 0.21 | 0.26 | 0.48 | 0.013 | 0.005 | 0.009 | 0.012 | 0.006 | 479 | 279 | 32 | NDT |
| 8 | 20# | B250603 | 140x30 | | 2 | 4.032 | 0.2 | 0.26 | 0.47 | 0.012 | 0.006 | 0.009 | 0.011 | 0.007 | 481 | 280 | 30 | NDT |
| 9 | 20# | C250615 | 273x45 | | 6 | 7.234 | 0.21 | 0.26 | 0.48 | 0.013 | 0.005 | 0.009 | 0.012 | 0.006 | 479 | 279 | 32 | NDT |
| 10 | 20# | E250516 | 273x50 | | 4 | 5.456 | 0.21 | 0.27 | 0.51 | 0.011 | 0.005 | 0.01 | 0.013 | 0.007 | 481 | 279 | 31 | NDT |
| 11 | 20# | D250521 | 299x50 | | 2 | 2.942 | 0.19 | 0.27 | 0.51 | 0.011 | 0.006 | 0.01 | 0.013 | 0.007 | 485 | 280 | 31 | NDT |
| 12 | 20# | B250604 | 530x20 | | 4 | 4.024 | 0.2 | 0.26 | 0.47 | 0.012 | 0.006 | 0.009 | 0.011 | 0.007 | 481 | 280 | 30 | NDT |
| 13 | 20# | C250616 | 530x60 | | 1 | 2.912 | 0.21 | 0.26 | 0.48 | 0.013 | 0.005 | 0.009 | 0.012 | 0.006 | 479 | 279 | 32 | NDT |
| 14 | 20# | E250517 | 95x16 | | 3 | 7.912 | 0.19 | 0.27 | 0.51 | 0.011 | 0.006 | 0.01 | 0.013 | 0.007 | 485 | 280 | 31 | NDT |
| 15 | 20# | D250522 | 180x20 | | 2 | 4.87 | 0.2 | 0.26 | 0.47 | 0.012 | 0.006 | 0.009 | 0.011 | 0.007 | 481 | 280 | 30 | NDT |
| 16 | 20# | B250605 | 180x30 | | 1 | 3.346 | 0.21 | 0.26 | 0.48 | 0.013 | 0.005 | 0.009 | 0.012 | 0.006 | 479 | 279 | 32 | NDT |
| 17 | 20# | C250617 | 530x12 | | 3 | 4.084 | 0.19 | 0.27 | 0.51 | 0.011 | 0.006 | 0.01 | 0.013 | 0.007 | 485 | 280 | 31 | NDT |
| 18 | 20# | E250518 | 630x10 | | 7 | 7.524 | 0.2 | 0.26 | 0.47 | 0.012 | 0.006 | 0.009 | 0.011 | 0.007 | 481 | 280 | 30 | NDT |
| Total: | | | | | 47 | 83.204 | | | | | | | | | | | | |

| Surveyor: | We certify that all products has been manufactured, sampled, tested and inspected in accordance with the DSTU 8938:2019 and was found to meet the requirements.<br>Residual Magnetism does not exceed 30 Gaus<br>The test result is only responsible for sample | Inspector: |
|---|---|---|
| | | Stamp of Mill Inspector |

PETROLEUM EQUIPMENT (THAILAND) CO., LTD. PET QC PASS