Next-Generation Quantum Biosensing: Intracellular Probing with Nitrogen-Vacancy Centers in Fluorescent Nanodiamonds

Shubhang S, Gururaja Rao
PES1UG23CS573, PES1UG23AM160
Course Code: UE23EC343BB1
6th Semester Elective

***Abstract*—**The precise measurement of physiological processes at the subcellular level remains a formidable challenge in biophysics. Traditional optical sensors, such as organic fluorophores and semiconductor quantum dots, are fundamentally limited by photobleaching, cytotoxicity, and a lack of multimodal sensing capabilities. This paper explores the paradigm shift brought about by quantum biosensing, specifically focusing on Nitrogen-Vacancy (NV) centers housed within Fluorescent Nanodiamonds (FNDs). We detail the quantum mechanical principles that allow FNDs to act as non-invasive, highly stable intracellular probes capable of room-temperature operation. By comprehensively examining the spin physics of the NV center, the requisite surface functionalization chemistries, and the integration of FNDs into biomimetic scaffolds, this paper outlines how quantum sensors are deployed for high-resolution nanoscale thermometry, electrophysiology, and paramagnetic chemical tracking. Finally, we analyze the current physical and biological limitations—such as colloidal aggregation, laser-induced thermal profiles, and optical tissue scattering—that must be resolved to facilitate the clinical translation of quantum magnetometry and biosensing.

***Index Terms*—Quantum Biosensing, Nitrogen-Vacancy Centers, Fluorescent Nanodiamonds, Optically Detected Magnetic Resonance, Nanoscale Thermometry, Magnetoneurography.**

I. INTRODUCTION

The history of molecular biology and biophysics is deeply intertwined with the development of imaging probes. The advent of Green Fluorescent Protein (GFP) and synthetic organic dyes allowed researchers to illuminate the inner workings of cells. However, as biological inquiry pushes deeper into the nanoscale, the physical limits of these classical probes have become apparent. Organic dyes inevitably succumb to photobleaching—a chemical degradation caused by prolonged laser exposure—which restricts long-term observation. Furthermore, semiconductor quantum dots (such as CdSe) exhibit intermittent blinking and inherent heavy-metal cytotoxicity, limiting their utility in living organisms.

To achieve continuous, real-time tracking of intracellular thermodynamics, electrophysiology, and chemical signaling, a sensor must be unconditionally stable, entirely biocompatible, and highly sensitive to its immediate environment. Fluorescent Nanodiamonds (FNDs) containing Nitrogen-Vacancy (NV) centers fulfill all of these criteria, representing a profound leap from classical fluorescence to quantum-mechanical biosensing [2], [4].

Unlike traditional probes that merely emit light to indicate spatial location, FNDs act as active, multimodal quantum sensors. Their optical emission is tied directly to their internal electron spin state, which is exquisitely sensitive to local magnetic fields, electric fields, and temperature variations [1], [2]. Because the diamond lattice is composed of tightly bound sp^3 carbon, FNDs are chemically inert and provoke minimal immune responses, allowing them to safely operate within the cytoplasm of living cells. This paper comprehensively reviews the physics, surface engineering, and deployment of FNDs as intracellular probes, establishing their role as the premier tool for next-generation nanoscale biophysics.

II. THE QUANTUM MECHANICS OF NV SENSING

The extraordinary utility of the NV center derives from its unique atomic structure and its corresponding energy level diagram, which allows for initialization, manipulation, and readout of quantum states at ambient biological temperatures.

A. Crystallographic Structure and Symmetry

An NV center is a point defect within the diamond lattice formed by a substitutional nitrogen atom sitting adjacent to a carbon vacancy. This arrangement creates a C_{3v} symmetry axis. While the NV center can exist in multiple charge states, it is the negatively charged state (NV^-) that is of primary interest for biosensing due to its spin-triplet ground state. The electronic structure consists of six electrons: five originating from the nitrogen and surrounding carbon atoms, and one captured from the lattice [4].

B. The Spin Hamiltonian and Zero-Field Splitting

The ground state of the NV^- center is a spin triplet ($^3A_2$) with $S = 1$. The quantum dynamics of this ground state, when exposed to the complex electromagnetic environment of a living cell, are governed by the effective spin Hamiltonian [4]:

$$H = D\left(S_z^2 - \frac{1}{3}S(S+1)\right) + \gamma_e \mathbf{B}\cdot\mathbf{S} + \mathbf{E}\cdot\mathbf{d} + \dots \quad (1)$$

where $D \approx 2.87$ GHz is the zero-field splitting (ZFS) parameter, S_z is the spin operator along the NV symmetry axis, γ_e is the electron gyromagnetic ratio (≈ 28 GHz/T), $\mathbf{B}$

is the local magnetic field, $\mathbf{E}$ is the local electric field, and $\mathbf{d}$ is the electric dipole moment.

At zero external magnetic field, the $m_s = \pm 1$ spin sublevels are degenerate and are separated from the lower-energy $m_s = 0$ state by the 2.87 GHz ZFS parameter. This microwave-frequency gap is the foundation of all NV-based measurements.

C. Optically Detected Magnetic Resonance (ODMR)

The ability to read these microscopic spin states without invasive electrical contacts is achieved through Optically Detected Magnetic Resonance (ODMR). When the FND is illuminated by a non-resonant green laser (typically 532 nm), the electrons are excited to a higher energy triplet state (^3E).

Crucially, the decay pathways back to the ground state are spin-dependent. Electrons in the $m_s = 0$ state primarily decay radiatively, emitting bright red fluorescence. However, electrons in the $m_s = \pm 1$ states have a high probability of undergoing non-radiative intersystem crossing through intermediate singlet states before eventually relaxing down into the $m_s = 0$ ground state [8].

This asymmetric decay has two profound consequences. First, continuous green laser illumination optically "polarizes" the NV center, forcing the spin population into the $m_s = 0$ state. Second, if a microwave field is applied to drive the spins from the bright $m_s = 0$ state into the darker $m_s = \pm 1$ states, the overall red fluorescence drops by up to 30%. By sweeping the microwave frequency and mapping the fluorescence intensity, researchers can pinpoint the exact resonance frequency. Because local temperature, voltage, and magnetic fields shift the Hamiltonian, these shifts are directly observed as changes in the ODMR optical fluorescence spectrum [7], [8].

D. Spectral Signatures of Charge States

The nitrogen-vacancy center can exist in multiple charge states within the diamond lattice, predominantly the neutral state (NV^0) and the negatively charged state (NV^-). While both states exhibit bright fluorescence under 532 nm laser excitation, their spectral signatures and quantum properties are fundamentally different. To explicitly observe and compare these differences, a room-temperature fluorescence spectrum was computationally simulated (see Fig. 1).

Two primary observations can be drawn from the spectral simulation:

- **Zero-Phonon Lines (ZPL):** The most distinct feature separating the two charge states is the location of the ZPL. The NV^0 state exhibits a sharp ZPL at 575 nm (2.156 eV), whereas the NV^- state exhibits a ZPL shifted further into the red spectrum at 637 nm (1.945 eV). These lines represent direct electronic transitions where no momentum (phonons) is exchanged with the diamond lattice.
- **Phonon Sidebands (PSB):** At ambient biological temperatures, the vast majority of photon emission (over 85%) does not occur at the ZPL. Instead, because the excited electrons couple strongly with the vibrational modes of the carbon lattice, the emission is shifted to lower energies. This forms a broad, skewed Phonon Sideband. The NV^0 PSB peaks near 600 nm, while the NV^- PSB peaks near 680 nm.



Fig. 1. Simulated room-temperature fluorescence spectra comparing the neutral (NV^0) and negatively charged (NV^-) states of the nitrogen-vacancy center. The sharp peaks represent the Zero-Phonon Lines (ZPL), while the broad distributions represent the Phonon Sidebands (PSB).

From a biosensing perspective, only the NV^- state possesses the $S = 1$ spin-triplet ground state required for ODMR [4]. Furthermore, because biological tissue heavily absorbs visible light (due to hemoglobin and lipids), the red-shifted emission profile of the NV^- state—which stretches into the 700–800 nm near-infrared optical window—is highly advantageous for *in vivo* signal collection compared to the yellow-orange emission of NV^0.

TABLE I
COMPARISON OF BIOLOGICAL IMAGING PROBES

Probe Type	Primary Limitation	FND Advantage
Organic Dyes	Photobleaching limits continuous use.	Infinite photostability.
Quantum Dots	Heavy metal toxicity and optical blinking.	Pristine carbon lattice ensures extreme biocompatibility.
Patch-Clamp	Highly invasive, disrupts cell membrane.	Optically read from a distance; zero physical contact required.
Bulk Diamond	Restricted to widefield external 2D mapping.	Nanoscale size allows endocytosis and true intracellular probing.

III. MATERIALS SCIENCE: ENGINEERING THE SENSOR

While the quantum physics of the NV center dictates its sensitivity, the physical properties of the nanodiamond dictate its viability in biological settings. Bare nanodiamonds extracted from industrial synthesis processes cannot be deployed directly into a cell.

A. Synthesis and Vacancy Migration

FNDs are typically synthesized via High-Pressure High-Temperature (HPHT) methods, which yield nanodiamonds with a high concentration of nitrogen impurities. To create the sensing centers, these diamonds are bombarded with high-energy electron irradiation (typically 2–3 MeV) to knock carbon atoms out of the lattice, creating vacancies. The material is subsequently annealed in a vacuum at temperatures exceeding $800°$C, providing the thermal energy required for the vacancies to migrate through the lattice and pair with the nitrogen impurities [2].

B. Overcoming the Protein Corona and Aggregation

When a raw FND is introduced into physiological environments, such as blood plasma or cell culture media, it immediately encounters a highly ionic, protein-rich fluid. Due to their high surface energy and reactive chemical dangling bonds, bare FNDs rapidly succumb to van der Waals forces and aggregate into massive clumps [4]. Furthermore, they attract a non-specific "protein corona"—a dense layer of host proteins that binds to the diamond, masking its sensing range and potentially triggering immune responses.

To overcome this, extensive surface functionalization is required. Applying thin steric coatings, such as polyethylene glycol (PEGylation), human serum albumin, or mesoporous silica shells, establishes electrostatic and steric repulsion, drastically improving colloidal stability. This functionalization is also the key to active targeting. By covalently conjugating specific targeting ligands—such as antibodies, transferrin, or nuclear localization sequence (NLS) peptides—researchers can direct the FNDs to specific subcellular addresses, such as the mitochondria or the nucleus [2].

C. Integration into Biomimetic 3D Scaffolds

A growing consensus in cellular biology is that flat, 2D glass substrates fail to accurately replicate the complex mechanical forces cells experience *in vivo*. To study cells under natural mechanical conditions while retaining quantum sensing capabilities, researchers have pioneered the integration of FNDs into biomimetic 3D scaffolds [3].

By electrospinning poly(lactic-co-glycolic acid) (PLGA) mixed with FNDs using optimized solvent ratios (such as a 2:1 chloroform-to-methanol blend), structural matrices that physically mimic the fibrillar architecture of the extracellular matrix can be created. Recent studies demonstrate that neural stem cells differentiating on these 3D scaffolds maintain high viability, while the embedded FNDs successfully retain their ODMR contrast, opening the door for quantum sensing in realistic tissue models [3].

IV. INTRACELLULAR SENSING APPLICATIONS

The deployment of functionalized FNDs has revolutionized several areas of intracellular measurement. By acting as highly localized quantum probes, FNDs bypass the physical limits of traditional bio-instrumentation.

A. Nanoscale Subcellular Thermometry

Intracellular temperature is a fundamental thermodynamic parameter that governs enzyme kinetics, gene expression, and metabolic rates. Traditional thermometry cannot resolve thermal gradients within a single cell. NV centers solve this problem via the lattice strain effect.

As the local temperature of the cytoplasm increases, the diamond lattice undergoes microscopic thermal expansion. This expansion alters the distance between the nitrogen atom and the vacancy, which modifies the electron-electron spin interaction. Consequently, the zero-field splitting parameter D shifts downward at a highly predictable rate of approximately -74 kHz/K [8].

Recent advancements have abandoned slow Continuous-Wave ODMR sweeps in favor of "differential" ODMR techniques. By rapidly interrogating only two specific microwave frequencies near the steepest slope of the resonance dip, researchers have tracked local thermal shifts with a sensitivity of $3\ \mathrm{K}/\sqrt{\mathrm{Hz}}$ inside living hippocampal neurons. This optimized pulse protocol drastically reduces the required laser exposure time, preventing the probe itself from heating and killing the host cell [8].

B. Paramagnetic Chemical Sensing and pH Dependencies

The ability to detect specific chemical species, such as transient free radicals or localized ions, is critical for understanding oxidative stress and cellular signaling. FNDs can monitor dynamic chemical environments through T_1 (spin-lattice) relaxometry [4].

When an NV center is optically polarized, it slowly relaxes back to its thermal equilibrium over a specific time, T_1. If fast-fluctuating magnetic noise—such as that generated by the unpaired electrons of paramagnetic molecules or ions—is present near the diamond surface, this relaxation process is dramatically accelerated.

Recent studies utilizing levitated microdroplets successfully deployed FNDs to quantify concentrations of paramagnetic Gadolinium (Gd^{3+}) ions [5]. A critical finding in these experiments is the heavy reliance on the local pH. The detection mechanism relies on the electrostatic binding of the target ion to the carboxylated surface of the nanodiamond. Under low-pH (acidic) conditions, these carboxylate groups become protonated, neutralizing their charge and preventing the Gd^{3+} ions from adsorbing. Thus, by monitoring changes in the T_1 relaxation time, FNDs act as dual-purpose sensors mapping both paramagnetic concentration and local pH fluctuations [5].

C. Electrophysiology and Bio-Membrane Mechanics

Cellular membranes are highly dynamic structures that regulate ion transport and maintain resting potentials essential for neural communication. Classical electrophysiology relies on the patch-clamp technique, which requires physically puncturing the cell membrane with a glass micropipette—an inherently destructive process.

TABLE II
QUANTUM SENSING MODALITIES AND APPLICATIONS

Target Parameter	Measurement Technique	Physical Mechanism
Temperature	Differential ODMR	Diamond lattice expansion (Zero-field shift)
Intracellular pH	T_1 Relaxometry	Protonation of surface functional groups
Free Radicals / Ions	T_1 Relaxometry	Acceleration of spin-lattice relaxation
Action Potentials	Spin-Echo / Ramsey	Weak magnetic field accumulation / Phase shift
Membrane Voltage	Stark Effect Mapping	Electric field shifting of energy levels

FNDs integrated into lipid bilayers and living cell membranes act as non-invasive, nanoscale electrometers [1]. Because the NV center lacks complete inversion symmetry, applied electric fields shift its spin states via the Stark effect. By tracking these shifts optically, researchers have successfully recorded the intense electrical potential drops across biological membranes, offering a non-destructive alternative for monitoring neuron excitation and ion channel flux in real time [1].

Furthermore, tracking the rotational dynamics of FNDs yields critical biomechanical data. Because the Zeeman splitting of the NV spectrum is heavily dependent on the alignment of the external magnetic field with the NV symmetry axis, researchers can track the exact 3D rotational orientation of the nanodiamond [4]. This capability has been used to study the torque and mechanical forces involved in endocytosis and complex intracellular transport pathways over several hours.

D. Magnetoneurography (MNG) and Neural Network Tracking

The ultimate frontier for quantum biosensing is the detection of the minute magnetic fields generated by traveling neural action potentials. These fields are vanishingly small, often measuring below 1 nanoTesla (nT).

While bulk diamond geometries are primarily utilized for widefield neural mapping, advanced pulsed microwave sequences (such as Hahn-echo and dynamical decoupling) applied to NV centers have proven capable of isolating these weak signals from environmental noise [2], [7]. By employing magnetic gradiometry—where two adjacent NV sensing volumes are measured simultaneously to cancel out common-mode background noise—researchers have successfully detected simulated muscular action potentials with amplitudes as low as ~ 2 nT in unshielded environments [7].

However, detecting single traveling action potentials in deep mammalian brain slices remains challenging. Computational simulations of the auditory brainstem pathway reveal that while optogenetic stimulation (using ChR2 ion channels) prevents the electromagnetic artifacts associated with electrical stimulation, it yields highly unsynchronized neural firing, resulting in peak magnetic fields of only ~ 0.1 nT [6]. Resolving such weak signals *in vivo* requires continued advancements in both sensor isotopic purity and pulse sequence engineering.

V. LIMITATIONS AND TRANSLATIONAL CHALLENGES

Despite the extraordinary theoretical promise and the rapid pace of biophysical breakthroughs, several severe practical limitations must be addressed before FNDs achieve routine clinical integration.

A. Laser-Induced Phototoxicity and Thermal Management

The very mechanism that makes NV sensing possible—optical initialization and readout—is also its greatest biological liability. Reading the NV spin state requires high-power continuous or pulsed green laser excitation (532 nm). Prolonged optical exposure naturally deposits significant thermal energy into the surrounding biological fluid. If not aggressively mitigated by heat sinks, total-internal-reflection geometries, or ultra-short duty cycles, this poses a persistent risk of thermal phototoxicity, fundamentally limiting the duration of continuous *in vivo* measurements [6], [8].

B. Optical Tissue Windows and Deep-Tissue Scattering

The most profound limitation of FNDs is their inability to operate deep within mammalian tissue. Biological tissue, rich in water, lipids, and hemoglobin, heavily scatters and absorbs light. The 532 nm excitation wavelength and the $637 - 800$ nm fluorescence emission of the NV center fall directly within high-absorption regions, outside the optimal Near-Infrared (NIR-II) optical tissue windows [4]. Consequently, deep-organ quantum sensing is nearly impossible with current free-space optical setups, restricting *in vivo* applications to shallow depths or transparent organisms like *C. elegans*. Overcoming this will require the development of highly advanced, biocompatible fiber-optic micro-endoscopes capable of delivering microwaves and collecting single photons from deep within the brain or deep tissues.

C. Particle Variability and Standardization

Unlike synthetic molecules which are completely identical, FNDs are manufactured via top-down milling of bulk diamond or bottom-up detonation. This results in massive particle-to-particle variability. No two nanodiamonds are exactly alike; variations in crystal size, jagged morphology, and the precise number of internal NV centers dictate that each individual nanoscale probe possesses a unique calibration curve. Achieving quantitative accuracy requires the painstaking calibration of every individual FND prior to measurement, presenting a massive bottleneck for high-throughput commercial or clinical adoption [2].

VI. CONCLUSION

The integration of Nitrogen-Vacancy centers into biological systems represents one of the most significant advances in modern biophysics. As detailed throughout this review, Fluorescent Nanodiamonds are uniquely equipped for high-resolution intracellular probing. Driven by their innate carbon

biocompatibility, infinite photostability, and remarkable spin-based sensitivity, FNDs empower researchers to track subcellular thermodynamics, monitor bio-membrane voltages, and observe dynamic chemical shifts with unprecedented spatial and temporal resolution.

While practical engineering hurdles remain formidable—namely the physical limits of deep-tissue light scattering, the complexities of colloidal aggregation in whole blood, and the thermal management of laser excitation—the theoretical foundation of quantum biosensing is unequivocally established. Ongoing improvements in surface chemistry, the development of isotopic engineering to enhance spin coherence times, and the implementation of advanced noise-cancellation gradiometry are steadily overcoming these barriers, positioning NV-based Fluorescent Nanodiamonds as the premier quantum tool for the future of life-science measurement.

REFERENCES

[1] Y. Tan, X. Hu, Y. Hou, and Z. Chu, "Emerging Diamond Quantum Sensing in Bio-Membranes," *Membranes*, vol. 12, no. 957, 2022.

[2] M. Niora *et al.*, "Bio-sensing with NV-centers in diamond," *J. Phys. Photonics*, vol. 8, no. 012007, 2026.

[3] J. C. Price *et al.*, "Quantum sensing in a physiological-like cell niche using fluorescent nanodiamonds embedded in electrospun polymer nanofibers," *Optics and Photonics Research Group*.

[4] T. Zhang *et al.*, "Toward Quantitative Bio-sensing with Nitrogen-Vacancy Center in Diamond," *ACS Sensors*, vol. 6, pp. 2077–2107, 2021.

[5] E. K. Brown *et al.*, "Quantum sensing of paramagnetic analytes by nanodiamonds in levitated microdroplets and aqueous solutions," *Chemical Science*, vol. 16, 2025.

[6] M. Karadas *et al.*, "In-vitro Recordings of Neural Magnetic Activity From the Auditory Brainstem Using Color Centers in Diamond: A Simulation Study," *Front. Neurosci.*, vol. 15, no. 643614, 2021.

[7] C. Zhang *et al.*, "Optimizing NV magnetometry for Magnetoneurography and Magnetomyography applications," *Front. Neurosci.*, vol. 16, no. 1034391, 2023.

[8] G. Petrini *et al.*, "Monitoring cells local temperature variation using nitrogen-vacancy (NV) centers in nanodiamonds," *INRIM*, 2022.