

	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16								
A	技术要求: Specifications: 1.天然胶,硬度:55±3 shore A,参照标准DBL 5558-45; Nature rubber with 55±3 shore A,according to the spec.DBL 5558-45. 2.由索格菲完成粘接工序; The gluing is made by Sogefi. 3.粘接准备事项 Bush status before for gluing on stab bar: 3.1 内表面需保持清洁,索格菲粘接前无需处理措施 3.2 衬套出模后6个月可粘接; 3.3 采用脱模剂必须与索格菲粘接工艺兼容; 3.1 The internal surface of the bush must be clean and can receive the Sogefi glue without surface preparation. 3.2 The gluing operation can be made 6 months maximum after moulding. 3.3 The release agent used for bushes must be compatible with the Sogefi glue. 4.特殊性参照标准 I-O2-P-01-01:Special characteristics as I-O2-P-01-01: 关键特性标识Critical: 重要特性标识Important: 橡胶尺寸公差参照 NF/T47-001 M3级执行; General tolerances on rubber M3 as norm NF/T47.001. 5.追溯性标识:字高2.5mm,字深0.2mm; Traceability:characters height 2.5mm,characters deep 0.2mm. 6.刚度采用卡箍和夹具完成(见附表): Stiffness are checked with serial brackets and rigid blocks to meet the specification(see table). 6.1.z&x向静刚度:加载±1mm,速度:10mm/min,循环4次,计算±0.5mm时的刚度; 6.2.扭转刚度:加载±20°,速度:60°/min,循环4次,计算±5°时的刚度; 6.1.Radial static stiffness Kz&x:Load ±1mm for 4 cycles, speed:10mm/min, check at ±0.5mm. 6.2.Torsional stiffness Kty:Load ±20° for 4 cycles,speed:60°/min,check at ±5°. 7.索格菲试验项目(Sogefi test); 7.1 噪音实验:在80℃*4周和120℃*24h环境下对3根老化前后产品分别做噪音实验,测试角度:9.4°&18.8°,5种温度(-30℃,-20℃,-10℃,0℃,+10℃,+20℃),5次循环,不可察觉的噪音为合格; 7.2 拔脱实验:80%的粘接效果为合格(新件);70%的粘接效果为合格(疲劳件); 7.3 环境试验:在110℃环境下,扭转9.4°,持续100小时,z&x向静刚度损失<10%,且粘接面积>70%为合格; 7.1 Noisy test:control before and after aging test on 3bars for 4 weeks at 80°c and 24h at 120°c,test angle(9.4°&18.8°),5 temperatures(-30℃,-20℃,-10℃,0℃,+10℃,+20℃),evaluation on 5 cycles,not noticeable noise=OK; 7.2 Destructive tests:80% rubber adhesion for new bush; 70% rubber adhesion after fatigue; 7.3 Ambient test: Preload bars as 9.4° angle for 100h at 110℃,the test is ok if the stiffness loss in z&x < 10% between before and after and peeling ok > 70%. 8.○为工序、出厂检验尺寸。 ○is marked for inspection dimensions.									来历 From			客户版本号 Customer Version	变更标记 Marking	区域 Position	变更事项 Modification			中鼎版本号 ZD Version	日期 Date	责任人 Resp.			
B													19388-E			初始图纸Initial drawing			A	2024.09.29	范康祺			
C																								
D																								
E																								
F																								
G																								
H																								
I																								
J																								
K																								
L																								

Upper bracket	19387		Stiffness requirement				
Lower bracket	19385						
Bar dia.	Bush dia	Identification	Gauge	Ks-Z(N/mm)	Ks-X(N/mm)	Ks-Y(N/mm)	Ty(Nm/°)
Ø20.0	Ø19.5	A	Bracket	1500±15%	1250±15%	550±15%	2max
			Block				

NF/T 47-001 CLASS M3								
	≤6.3	≤10	≤16	≤25	≤40	≤63	≤100	≤160
F	±0.20	±0.20	±0.25	±0.35	±0.40	±0.50	±0.70	±0.80
C	±0.25	±0.35	±0.40	±0.50	±0.70	±0.80	±1.00	±1.30

投影法 Projection method		比例Scale		质量Weight(g)	材质Material	产品号ZD production code
第一画法First angle projection		1:1		35.7g	R6938-H55	C114231-CPSJ
热处理-表面处理Heat Treatment-Surface Treatment						名称Part name
						稳定杆衬套 (后稳定杆衬套) (Rear stab bar bush)
批准 Approval	标准化 Standards	审批 Review	校对 Check	设计 Design	项目组 Team	图号Drawing No
				范康祺 0240929	稳定杆系统 Stab Bar system	19388-200 (WFG58)
标记SIGN		S	A	B	共 1 张 第 1 张	
安徽中鼎密封件股份有限公司						A3