

1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	
技术要求: Specifications:									来历 From	客户版本号 Customer Version	变更标记 Marking	区域 Position	变更项目 Modification	中鼎版本号 ZD Version	日期 Date	责任人 Resp.
1.天然胶或产品硬度:55±3 shore A,参照标准DBL 5558-45; Nature rubber or bush hardness: 55±3 shore A,according to the spec.DBL 5558-45.										19388-E			初始图纸Initial drawing	A	2024.12.12	范康祺
2.由索格菲完成粘接工序; The gluing is made by Sogefi.																
3.粘接准备事项 Bush status before for gluing on stab bar:																
3.1 内表面需保持清洁,索格菲粘接前无需处理措施																
3.2 衬套出模后6个月可粘接;																
3.3 采用脱模剂必须与索格菲粘接工艺兼容;																
3.1 The internal surface of the bush must be clean and can receive the Sogefi glue without surface preparation.																
3.2 The gluing operation can be made 6 months maximum after moulding.																
3.3 The release agent used for bushes must be compatible with the Sogefi glue.																
4.特殊性参照标准 I-O2-P-01-01:Special characteristics as I-O2-P-01-01:																
关键特性标识Critical:																
重要特性标识Important:																
橡胶尺寸公差参照 NF/T47-001 M3级执行; General tolerances on rubber M3 as norm NF/T47.001.																
5.追溯性标识:字高2.5mm,字深0.2mm; Traceability:characters height 2.5mm,characters deep 0.2mm.																
6.刚度采用卡箍和夹具完成(见附表): Stiffness are checked with serial brackets and rigid blocks to meet the specification(see table).																
6.1.z&x向静刚度:加载±1mm,速度:10mm/min,循环4次,计算±0.5mm时的刚度;																
6.2.扭转刚度:加载±20°,速度:60°/min,循环4次,计算±5°时的刚度;																
6.1.Radial static stiffness Kz&x:Load ±1mm for 4 cycles, speed:10mm/min, check at ±0.5mm.																
6.2.Torsional stiffness Kty:Load ±20° for 4 cycles,speed:60°/min,check at ±5°.																
7.索格菲试验项目(Sogefi test);																
7.1 噪音实验:在80℃*4周和120℃*24h环境下对3根老化前后产品分别做噪音实验,测试角度:9.4°&18.8°,5种温度(-30℃,-20℃,-10℃,0℃,+10℃,+20℃),5次循环,不可察觉的噪音为合格;																
7.2 拔脱实验:80%的粘接效果为合格(新件);70%的粘接效果为合格(疲劳件);																
7.3 环境试验:在110℃环境下,扭转9.4°,持续100小时,z&x向静刚度损失<10%,且粘接面积>70%为合格;																
7.1 Noisy test:control before and after aging test on 3bars for 4 weeks at 80°C and 24h at 120°C,test angle(9.4°&18.8°),5 temperatures(-30°C,-20°C,-10°C,0°C,+10°C,+20°C),evaluation on 5 cycles,not noticeable noise=OK;																
7.2 Destructive tests:80% rubber adhesion for new bush; 70% rubber adhesion after fatigue;																
7.3 Ambient test: Preload bars as 9.4° angle for 100h at 110°C,the test is ok if the stiffness loss in z&x < 10% between before and after and peeling ok > 70%.																
8.○为工序、出厂检验尺寸。 ○is marked for inspection dimensions.																

Upper bracket	19387			Stiffness requirement				
Lower bracket	19385							
Bar dia.	ØID	Identification	Color dot	Gauge	Ks-Z(N/mm)	Ks-X(N/mm)	Ks-Y(N/mm)	Ty(Nm/°)
Ø20	Ø19.5	A	White	Bracket	1500±15%	1250±15%	550±15%	2max
				Block				
Ø22.2	Ø21.7	B	Yellow	Bracket	2300±15%	1800±15%	550±15%	2max
				Block				
Ø23.8	Ø23.3	AB	Blue	Bracket	3200±15%	2350±15%	550±15%	2max
				Block				
Ø24.7	Ø24.2	AC	Green	Bracket	4050±15%	2800±15%	550±15%	2max
				Block				

NF/T 47-001 CLASS M3								
	≤6.3	≤10	≤16	≤25	≤40	≤63	≤100	≤160
F	±0.20	±0.20	±0.25	±0.35	±0.40	±0.50	±0.70	±0.80
C	±0.25	±0.35	±0.40	±0.50	±0.70	±0.80	±1.00	±1.30

投影法 Projection method		比例 Scale	质量 Weight(g)	材质 Material	产品号 ZD production code
第一角法 First angle projection		1:1	19.8g(ref.)	R6938-H55	C114341-CPSJ
热处理·表面处理 Heat Treatment·Surface Treatment				名称 Part name	
				稳定杆衬套下衬套 (后稳定杆衬套)	
批准 Approval	标准化 Standards	审批 Review	校对 Check	设计 Design	项目组 Team
范康祺 20241212			稳定杆系统 Stab Bar system		
标记 SIGN		S	共 1 张 第 1 张		
		安徽中鼎密封件股份有限公司			A3

图号 Drawing No		Z6012597 (WFG58)