


	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16																																							
A	技术要求: Specifications:									来历 From	客户版本号 Customer Version	变更标记 Marking	区域 Position	变更事项 Modification		中鼎版本号 ZD Version	日期 Date	责任人 Resp.	A																																				
B	1.天然胶,硬度:55±3 shore A,参照标准DBL 5558-45; Nature rubber with 55±3 shore A,according to the spec.DBL 5558-45.									初始图纸Initial drawing									A	2024.12.11	范康祺	B																																	
C	2.由索格菲完成粘接工序; The gluing is made by Sogefi.																					C																																	
D	3.粘接准备事项 Bush status before for gluing on stab bar:																					D																																	
E	3.1 内表面需保持清洁,索格菲粘接前无需处理措施																					E																																	
F	3.2 衬套出模后6个月可粘接;																					F																																	
G	3.3 采用脱模剂必须与索格菲粘接工艺兼容;																					G																																	
H	3.1 The internal surface of the bush must be clean and can receive the Sogefi glue without surface preparation.																					H																																	
I	3.2 The gluing operation can be made 6 months maximum after moulding.																					I																																	
J	3.3 The release agent used for bushes must be compatible with the Sogefi glue.																					J																																	
K	4.特殊特性参照标准 I-02-P-01-01:Special characteristics as I-02-P-01-01:																					K																																	
L	关键特性标识Critical:																					L																																	
	重要特性标识Important:																																																						
	橡胶尺寸公差参照 NF/T47-001 M3级执行; General tolerances on rubber M3 as norm NF/T47.001.																																																						
	5.追溯性标识:字高2.5mm,字深0.2mm;																																																						
	Traceability:characters height 2.5mm,characters deep 0.2mm.																																																						
	6.刚度采用卡箍和夹具完成(见附表): Stiffness are checked with serial brackets and rigid blocks to meet the specification(see table).																																																						
	6.1.z&x向静刚度:加载±1mm,速度:10mm/min,循环4次,计算±0.5mm时的刚度;																																																						
	6.2.扭转刚度:加载±20°,速度:60°/min,循环4次,计算±5°时的刚度;																																																						
	6.1.Radial static stiffness Kz&x:Load ±1mm for 4 cycles, speed:10mm/min, check at ±0.5mm.																																																						
	6.2.Torsional stiffness Kty:Load ±20° for 4 cycles,speed:60°/min,check at ±5°.																																																						
	7.索格菲试验项目(Sogefi test);																																																						
	7.1 噪音实验:在80℃*4周和120℃*24h环境下对3根老化前后产品分别做噪音实验,测试角度:9.4°&18.8°,5种温度(-30℃,-20℃,-10℃,0℃,+10℃,+20℃),5次循环,不可察觉的噪音为合格;																																																						
	7.2 拔脱实验:80%的粘接效果为合格(新件);70%的粘接效果为合格(疲劳件);																																																						
	7.3 环境试验:在110℃环境下,扭转9.4°,持续100小时,z&x向静刚度损失<10%,且粘接面积>70%为合格;																																																						
	7.1 Noisy test:control before and after aging test on 3bars for 4 weeks at 80°c and 24h at 120°c,test angle(9.4°&18.8°),5 temperatures(-30℃,-20℃,-10℃,0℃,+10℃,+20℃),evaluation on 5 cycles,not noticeable noise=OK;																																																						
	7.2 Destructive tests:80% rubber adhesion for new bush; 70% rubber adhesion after fatigue;																																																						
	7.3 Ambient test: Preload bars as 9.4° angle for 100h at 110℃,the test is ok if the stiffness loss in z&x < 10% between before and after and peeling ok > 70%.																																																						
	8.○为工序,出厂检验尺寸.																																																						
	○is marked for inspection dimensions.																																																						
																																																							
	<table><tr><td>Upper bracket</td><td colspan="2">19387</td><td colspan="6" rowspan="2">Stiffness requirement</td></tr><tr><td>Lower bracket</td><td colspan="2">19385</td></tr><tr><td>Bar dia.</td><td>Bush dia</td><td>Identification</td><td>Gauge</td><td>Ks-Z(N/mm)</td><td>Ks-X(N/mm)</td><td>Ks-Y(N/mm)</td><td>Ty(Nm/°)</td></tr><tr><td rowspan="2">Ø23.8</td><td rowspan="2">Ø23.3</td><td rowspan="2">AB</td><td>Bracket</td><td>3200±15%</td><td>2350±15%</td><td>550±15%</td><td>2max</td></tr><tr><td>Block</td><td></td><td></td><td></td><td></td></tr></table>									Upper bracket	19387		Stiffness requirement						Lower bracket	19385		Bar dia.	Bush dia	Identification	Gauge	Ks-Z(N/mm)	Ks-X(N/mm)	Ks-Y(N/mm)	Ty(Nm/°)	Ø23.8	Ø23.3	AB	Bracket	3200±15%	2350±15%	550±15%	2max	Block																	
Upper bracket	19387		Stiffness requirement																																																				
Lower bracket	19385																																																						
Bar dia.	Bush dia	Identification	Gauge	Ks-Z(N/mm)	Ks-X(N/mm)	Ks-Y(N/mm)	Ty(Nm/°)																																																
Ø23.8	Ø23.3	AB	Bracket	3200±15%	2350±15%	550±15%	2max																																																
			Block																																																				
	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16																																							

NF/T 47-001 CLASS M3								
	≤6.3	≤10	≤16	≤25	≤40	≤63	≤100	≤160
F	±0.20	±0.20	±0.25	±0.35	±0.40	±0.50	±0.70	±0.80
C	±0.25	±0.35	±0.40	±0.50	±0.70	±0.80	±1.00	±1.30

投影法 Projection method	第一画法First angle projection	比例Scale	1:1	质量Weight(g)	19g	材质Material	R6938-H55	产品号ZD production code	C114342-CPSJ
热处理·表面处理Heat Treatment·Surface Treatment						名称Part name			稳定杆衬套下衬套 (后稳定杆衬套) (Rear stab bar bush)
批准 Approval	标准化 Standards	审批 Review	校对 Check	设计 Design	项目组 Team	图号Drawing No			
						Z6012511 (WFG58)			
标记SIGN						S	A	B	共 1 张 第 1 张
						安徽中鼎密封件股份有限公司			