

	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16												
A										来历	客户版本号	变更标记	区域	变更事项		中鼎版本号	年月日	变更者	A									
B														首次下发		A	20250217	范康祺	B									
C	技术要求: Specifications: 1.天然胶,硬度:60±3 shA,参照标准DBL 5558-45; Nature rubber according to DBL 5558-45. 2.耐臭氧实验参照标准ISO 1431-1 A法,参照标准DBL 5555 0级无裂纹; Ozone test according ISO 1431-1 operation mode A, grade 0 no cracking according DBL 5555. 3.自然老化参照标准DIN EN ISO 4892-2(850h,65±3℃,HR 60% min,61±2W/mm2/), 参照标准DBL 5555 0级无裂纹; Artificial weathering in accordance with DIN EN ISO 4892-2/ 850h/65±3℃/HR 60% min/61±2W/mm2/ ,grade 0 no cracking according DBL 5555 4.由索格菲完成粘接工序; The gluing is made by Sogefi. 5.粘接准备事项Bush status before for gluing on stab bar: ·内表面需保持清洁,索格菲粘接前无需处理措施; ·衬套出模后6个月可粘接; ·采用脱模剂必须与索格菲粘接工艺兼容; ·The internal surface of the bush must be clean and can receive the Sogefi glue without surface preparation. ·The gluing operation can be made 6 months maximum after moulding. ·The release agent used for bushes must be compatible with the Sogefi glue. 6.特殊特性参照标准IGR-D-20/0: Special characteristics as IGR-D-20/0: 关键特性标识Critical: ▽ 重要特性标识Important: ▽ 橡胶尺寸公差参照NF/T47-001 M3级执行; General tolerances on rubber M3 as norm NF/T47.001. 7.追溯性标识:字高2.5mm,字深0.2mm; Traceability:characters height 2.5mm,characters deep 0.2mm. 8.刚度采用刚性夹具完成: 8-1.Z向静刚度:加载±5000N,速度:30mm/min,循环3次,计算±3000N时的刚度; 8-2.Z向动刚度:振幅±0.025mm,频率15到150Hz,增幅5Hz,计算100Hz时的刚度; 8-3.轴向刚度:加载±500N,速度:20mm/min,循环3次,计算±500N时的刚度; 8-4.扭转刚度:加载±25°,速度60°/min,循环3次,计算±3°时的刚度; Stiffness are checked with rigid blocks to meet the specification. 8-1.Radial static stiffness Kz:Load ±5000N for 3 cycles,speed:30mm/min,check at±3000N. 8-2.Radial dynamic stiffness Kdz:Amplitude ±0.025mm,frequency:15 to 150Hz,amplification:5Hz,check at 100Hz. 8-3.Axial stiffness:Load ±500N for 3 cycles,speed:20mm/min,check at±500N. 8-4.Torsional stiffness Kty:Load ±25° for 3 cycles,speed:60°/min,check at ±3°. 9.其他试验参照索格菲试验计划; The rest tests refer to Sogefi test plan. 10. ○ 为工序,出厂检验尺寸。 ○ is marked for inspection dimensions.																											
D																												D
E																												E
F																												F
G																												G
H																			H									
I																			I									
J																			J									
K																			K									
L																			L									

索格菲杆径调教								
杆径	∅A							
31.7	31.2							
30.5	30.5							

NF/T 47-001 CLASS M3								
	≤6.3	≤10	≤16	≤25	≤40	≤63	≤100	≤160
F	±0.20	±0.20	±0.25	±0.35	±0.40	±0.50	±0.70	±0.80
C	±0.25	±0.35	±0.40	±0.50	±0.70	±0.80	±1.00	±1.30

投影法	第一画法	比例	1:1	质量(g)	0.00g	材质	30R7770-H60	产品号	20C114429-CPSJ		
热处理:表面处理						名称				前稳定杆衬套 (前稳定杆衬套)	
批准	标准化	审批	校对	设计	项目组	图号				18861-D30.5 (WFG58)	
图样标记						S	共 1 张 第 1 张			安徽中鼎密封件股份有限公司	A3