

	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16			
A									来历		客户版本号	变更标记	区域	变更事项		中鼎版本号	年月日	变更者	A
													首次下发		A	20250218	范康祺		
B																			B
C																			C
D																			D
E																			E
F																			F
G																			G
H																			H
I																			I
J																			J
K																			K
L																			L

技术要求:
Specifications:
1.天然胶,硬度:60±3 shA,参照标准DBL 5558-45;
Nature rubber according to DBL 5558-45.
2.耐臭氧实验参照标准ISO 1431-1 A法,参照标准DBL 5555 0级无裂纹;
Ozone test according ISO 1431-1 operation mode A,
grade 0 no cracking according DBL 5555.
3.自然老化参照标准DIN EN ISO 4892-2(850h,65±3℃,HR 60% min,61±2W/mm2/),
参照标准DBL 5555 0级无裂纹;
Artificial weathering in accordance with DIN EN ISO 4892-2/
850h/65±3℃/HR 60% min/61±2W/mm2/ ,grade 0 no cracking according DBL 5555
4.由索格菲完成粘接工序;
The gluing is made by Sogefi.
5.粘接准备事项Bush status before for gluing on stab bar:
·内表面需保持清洁,索格菲粘接前无需处理措施;
·衬套出模后6个月可粘接;
·采用脱模剂必须与索格菲粘接工艺兼容;
·The internal surface of the bush must be clean and can receive the Sogefi
glue without surface preparation.
·The gluing operation can be made 6 months maximum after moulding.
·The release agent used for bushes must be compatible with the Sogefi glue.
6.特殊特性参照标准IGR-D-20/0:
Special characteristics as IGR-D-20/0:
关键特性标识Critical:
重要特性标识Important:
橡胶尺寸公差参照NF/T47-001 M3级执行;
General tolerances on rubber M3 as norm NF/T47.001.
7.追溯性标识:字高2.5mm,字深0.2mm;
Traceability:characters height 2.5mm,characters deep 0.2mm.
8.刚度采用刚性夹具完成:
8-1.Z向静刚度:加载±5000N,速度:30mm/min,循环3次,计算±3000N时的刚度;
8-2.Z向动刚度:振幅±0.025mm,频率0到600Hz,增幅5Hz,计算100Hz时的刚度;
8-3.轴向刚度:加载±500N,速度:20mm/min,循环3次,计算±500N时的刚度;
8-4.扭转刚度:加载±25°,速度60°/min,循环3次,计算±3°时的刚度;
Stiffness are checked with rigid blocks to meet the specification.
8-1.Radial static stiffness Kz:Load ±5000N for 3 cycles,speed:30mm/min,
check at±3000N.
8-2.Radial dynamic stiffness Kdz:Amplitude ±0.025mm,frequency:
0 to 600Hz,amplification:5Hz,check at 100Hz.
8-3.Axial stiffness:Load ±500N for 3 cycles,speed:20mm/min,check at±500N.
8-4.Torsional stiffness Kty:Load ±25° for 3 cycles,speed:60°/min,check at ±3°.
9.其他试验参照索格菲试验计划;
The rest tests refer to Sogefi test plan.
10. 为工序、出厂检验尺寸。
is marked for inspection dimensions.

索格菲杆径调教	
杆径	Ø
17.2	16.7
16.5	16

投影法		第一画法		比例	1:1	质量(g)	0.00g	材质	30R7770-H60	产品号	20C114430-CPSJ	
热处理·表面处理								名称				
								后稳定杆衬套 (后稳定杆衬套)				
批准	标准化	审批	校对	设计	项目组	图号						
						18682-D16.5 (WFG58)						
图样标记						S	共 1 张 第 1 张				安徽中鼎密封件股份有限公司	A3