

技术要求: Specifications:

- 天然胶,硬度:60±5 shore A,参照标准RENAULT 30-00-118;
Nature rubber with 60±5 shore A,according to the spec.RENAULT 30-00-118.
- 由索格菲完成粘接工序; The gluing is made by Sogefi.
- 粘接准备事项 Bush status before for gluing on stab bar:
 - 内表面需保持清洁,索格菲粘接前无需处理措施
 - 衬套出模后6个月可粘接;
 - 采用脱模剂必须与索格菲粘接工艺兼容;

3.1 The internal surface of the bush must be clean and can receive the Sogefi glue without surface preparation.

3.2 The gluing operation can be made 6 months maximum after moulding.

3.3 The release agent used for bushes must be compatible with the Sogefi glue.
- 特殊特性参照标准 I-02-P-01-01:Special characteristics as I-02-P-01-01:
关键特性标识Critical:
重要特性标识Important:
橡胶尺寸公差参照 NF/T47-001 M3级执行; General tolerances on rubber M3 as norm NF/T47.001.
- 追溯性标识:字高2.5mm,字深0.2mm;
Traceability:characters height 2.5mm,characters deep 0.2mm.
- 刚度采用卡箍和夹具完成(见附表): Stiffness are checked with serial brackets and rigid blocks to meet the specification(see table).
- 索格菲试验项目(Sogefi test);
 - 噪音实验:在80℃*4周和120℃*24h环境下对3根老化前后产品分别做噪音实验,测试角度:9.4° &18.8° ,5种温度(-30℃,-20℃,-10℃,0℃,+10℃,+20℃),5次循环,不可察觉的噪音为合格;
 - 拔脱实验:80%的粘接效果为合格(新件);70%的粘接效果为合格(疲劳件);
 - 环境试验:在110℃环境下,扭转9.4° ,持续100小时,z&x向静刚度损失<10%,且粘接面积>70%为合格;


7.1 Noisy test:control before and after aging test on 3bars for 4 weeks at 80° c and 24h at 120° c,test angle(9.4° &18.8°),5 temperatures(-30℃,-20℃,-10℃,0℃,+10℃,+20℃),evaluation on 5 cycles,not noticeable noise=OK;

7.2 Destructive tests:80% rubber adhesion for new bush; 70% rubber adhesion after fatigue;

7.3 Ambient test: Preload bars as 9.4° angle for 100h at 110℃,the test is ok if the stiffness loss in z&x < 10% between before and after and peeling ok > 70%.
- ☐为工序、出厂检验尺寸。
☐is marked for inspection dimensions.

CHARACTERTISTICS TABLE					REQUEST	STATIC STIFFNESS			
PART NUMBER	ARA REFERENCE	STAB BAR DIAMETER ØD	INTERNAL BUSHING DIAMETER Ød*	CODIFICATION	DIRECTION	RADIAL Z	TORSION Y	RADIAL X	AXIAL Y
					LOAD SPEED	10mm/min	60° /min	10mm/min	20mm/min
					LOAD	±1mm	±16°	±1mm	±2mm
					CHECK	±0.6mm	±9°	±0.6mm	±1.2mm
TBD	19241-330	33	32.2	A	UNITS	N/mm	N. m/°	N/mm	N/mm
					ARA RIGID BLOCK	TBD	TBD	TBD	TBD
					SERIAL BRACKET	6500±15%	6500±15%	430±15%	2.5±15%

No.	客户版本号 (CUSTOMER VERSION)	No.	变更标记 (MARK CHANGE)	更改内容(CHANGE CONTENT)	中鼎版本号 (ZD version)	日期 (DATE)	责任人 (RESPONSIBLE)
				Initial Release(初始版本)	A	20250915	马传德



DIN ISO 3302-1 Class M3										
	≤4	≤6.3	≤10	≤16	≤25	≤40	≤63	≤100	≤160	> 160
F	±0.25	±0.25	±0.30	±0.40	±0.50	±0.60	±0.80	±1.00	±1.30	±0.8%
C	±0.40	±0.40	±0.50	±0.60	±0.80	±1.00	±1.30	±1.60	±2.0	±1.3%

第一角画法 (FIRST ANGLE PROJECTION)		比例(SCALE) 1:1		重量(WEIGHT) TBDg		材料(MATERIAL) NR+BR (R6934)		产品号(PRODUCT NO.) C114718-CPSJ						
热处理·表面处理(HEAT TREATMENT·SURFACE TREATMENT)							名称(NAME) 前下稳定杆衬套 (前稳定杆衬套)							
批准 (APPROVAL)	标准化 (STD.)	审核 (AUDITOR)	校对 (CHECKER)	设计 (DESIGNER)	项目组 (PROJECT TEAM)	图号(PART NO.) Z6012800 (WYDL30)								
SIGN(标记)		PAGES(共 1 张) OF(第 1 张)		ZHONGDING SEALING PARTS CO.,LTD 中鼎密封件股份有限公司										