AASHTO T340-10: Standard Method of Test for Determining Rutting Susceptibility of Hot Mix Asphalt (HMA) Using the Asphalt Pavement Analyzer (APA)

Project Name:		**Institution:**	
Mix Type:		**Date Tested:**	
Test Temperature (C):		**Technician:**	

Sample	Air Voids (%)	Left Rut Depth (mm)	Middle Rut Depth (mm)	Right Rut Depth (mm)	Average Rut Depth (mm)	Standard Deviation	COV (%)
Sample #1		2.26	2.25		**2.26**	**0.01**	**0.30**

APA Intermediate Course (PG64-22) Criteria ≤	**7**	**mm Rutting**
APA Surface Course (PG76-22) Criteria ≤	**4**	**mm Rutting**

