AASHTO Designation: TP 105-13

Standard Method of Test for Determining the Fracture Energy of Asphalt Mixtures Using the Semicircular Bend Geometry (SCB)

Project Name:		**Institution:**	
Mix Type:		**Date Tested:**	
Test Temperature:		**Technician:**	

Specimen ID	Air Voids (%)	Thickness (mm)	Radius (mm)	Notch Length (mm)	Peak Load (kN)	Time At Peak (s)	Uc (mm)	Stiffness (kN/m)	K_{IC} (MPa*m$^{.5}$)	Fracture Energy (J/m^2)	CMOD Slope (mm/s)
1		25.0	75.0	15.0	2.4	301.7	1.466	2752.7	0.747	1586	5.00E-04
2		25.0	75.0	15.0	3.8	123.9	1.177	2967.7	1.148	1355	4.93E-04
3		25.0	75.0	15.0	2.9	452.1	1.286	2889.4	0.885	1385	5.00E-04
Average		**25.0**	**75.0**	**15.0**	**3.0**	**292.6**	**1.310**	**2870.0**	**0.926**	**1442**	**4.98E-04**
Std Dev		**0.0**	**0.0**	**0.0**	**0.7**	**164.3**	**0.146**	**108.8**	**0.204**	**126**	**3.93E-06**
COV (%)		**0.0**	**0.0**	**0.0**	**22.0**	**56.1**	**11.1**	**3.8**	**22.0**	**8.7**	**0.8**

Cold SCB

