ASTM D7313-13

Standard Test Method for Determining Fracture Energy of Asphalt-Aggregate Mixture Using the Disk-Shaped Compact Tension Geometry

Project Name:		**Institution:**	
Mix Type:		**Date Tested:**	
Test Temperature:		**Technician:**	

Specimen ID	Air Voids (%)	Diameter (mm)	Thickness (mm)	Ligament (mm)	Peak Load (kN)	Displacement at Peak (mm)	Time at Peak Load (sec)	Fracture Energy (J/m^2)	CMOD Slope (mm/s)
1		150.00	50.00	83.00	2.606	0.194	11.40	601.1	0.0170
2		150.00	50.00	83.00	2.410	0.197	11.60	452.8	0.0170
3		150.00	50.00	83.00	2.606	0.194	11.40	601.1	0.0170
Average		**150.00**	**50.00**	**83.00**	**2.540**	**0.195**	**11.47**	**551.6**	**0.017**
Std Dev		**0.00**	**0.00**	**0.00**	**0.113**	**0.002**	**0.12**	**85.6**	**0.000**
COV (%)		**0.0**	**0.0**	**0.0**	**4.5**	**1.0**	**1.0**	**15.5**	**0.0**

