
AASHTO T324-17
Standard Method of Test for Hamburg Wheel-Track Testing of Compacted Asphalt Mixtures

Project Name:		**Institution:**	
Mix Type:		**Date:**	
Test Temp:		**Technician:**	

Wheel	Average Rutting at 20,000 cycles (mm):	Average Creep Slope (mm/cycle):	Average Stripping Slope (mm/cycle):	Stripping Inflection Point (cycles):
Left	4.03	1.08E-04	1.46E-04	
Right	3.38	4.92E-05	1.02E-04	16197
Average	**3.7**	**7.84E-05**	**1.24E-04**	**16197**
Std Dev	**0.5**	**4.13E-05**	**3.10E-05**	
COV (%)	**12.5**	**52.7**	**25.1**	



AASHTO T324-17
Standard Method of Test for
Hamburg Wheel-Track Testing of
Compacted Asphalt Mixtures

