AASHTO TP 124

Standard Method of Test for Determining the Fracture Potential of Asphalt Mixtures Using Semicircular Bend Geometry (SCB) at Intermediate Temperatures

Project Name:		**Institution:**	
Mix Type:		**Date Tested:**	
Test Temperature:	25C	**Technician:**	

Specimen ID	Air Voids (%)	Thickness (mm)	Ligament Length (mm)	Max Load (kN)	Fracture Energy, G_f (J/m^2)	Slope (kN/mm)	Flexibility Index (FI)
1A		50.00	58.00	3.31	2201.6	-3.01	7.32
1B		50.00	58.00	3.46	2009.5	-3.76	5.34
2A		50.00	58.00	3.52	2473.5	-3.41	7.26
2B		50.00	58.00	3.34	2413.2	-3.68	6.56
Average		**50.00**	**58.00**	**3.41**	**2274.4**	**-3.46**	**6.6**
Std Dev		**0.0**	**0.0**	**0.1**	**211.7**	**0.3**	**0.9**
COV (%)		**0.0**	**0.0**	**3.0**	**9.3**	**-9.8**	**13.9**

Intermediate Temperature SCB

