According to EN 10204 - 3.1 for Mechanical

and Chemical

Our ref

Test # AE220407

Date 20-Oct-2022

То

Quantity - 3000 Kg

PRODUCT INFORMATION

OK Tigrod NiCrMo-3 1.6x1000mm 5kg	Lot: PVW1410388	Art No.	198416R150

CHEMICAL - WIRE COMPOSITION (%)

C(%)	Mn(%)	Fe(%)	P(%)	S(%)	Si(%)	Cu(%)	Ni(%)	AI(%)	Ti(%)	Cr(%)	Nb+Ta(%)	Mo(%)
0.004	0.01	0.24	0.003	0.001	0.07	0	64.6	0.13	0.23	21.94	3.54	8.7

MECHANICAL PROPERTIES OF THE WELD METAL As Welded

Rp0.2 (Mpa)	Rm (MPa)	EI (%)	Temp (°C)	Impact toughness					
531	531 777 47		-196	Energy (J)	132	138	140	Avg	137
,				Lateral Expansion (mm)			2.03	2.07	2.20

Notes:

Radiographic examination acc. to ASME Sect II Part C SFA/AWS A5.14: : Acceptable result

Schedule K S3 Tested as per Lot Class:

Made in Czech Republic

REFERENCES

Data Sheet: Reg No. EN009651 AWS/ASME SFA A5.14: ERNiCrMo-3

Report Number: D912452



ESAB Middle East FZE

Technical Department Rajesh Babu Quality & Product Specialist



CLASSIFICATIONS

ذات مسؤولية محدودة تأسست بموجب القانون رقم 9 لسنة 1992 Formed pursuant to law No. 9 of 1992 with limited liability

> إيساب الشرق الأوسط م ح **ESAB MIDDLE EAST FZE**