

Validation of the SolarLab Device Simulator against SCAPS-1D — Transient ($f = 0.53 / 0.66$) vs Steady-State Interface-States Comparison

2026-07-02

Summary

2026-07-02 revision — transient contact-reservoir fix + extended CBO sweep. Two updates since 2026-06-22. (i) The ETL-donor-doping direction — previously the one trend no de-spike fraction could fix (Section 4.1) — is now recovered on the **transient** path by a work-function contact-reservoir floor (`flat_band_metal_contacts`, $\phi_B = 0.42$ eV; shipped on `scaps_mirror_v2`): V_{oc} brackets all eleven doping points and rises with doping, RMS 39 mV vs SCAPS. The root cause was the contact carrier reservoir tied to the semiconductor doping, which starves the near-insulating low- N_D cathode; the floor supplies the metal work-function density instead and is dormant at normal doping (bit-identical elsewhere). This **supersedes** the earlier “structural, needs the interface-plane-states driver” verdict *for direction and physicality* (the `Nd_ETL` figure and Section 4.1 note are updated). (ii) The ETL/PVK CBO sweep (Section 4) is extended to $\Delta E_C = +1.0$ eV: the transient reproduces the positive-spike **cell death** — $J_{sc} / FF / PCE$ collapse at $\Delta E_C \approx +0.7$ eV (vs SCAPS +0.5) while V_{oc} stays flat, and the device goes dead ($J_{sc} \rightarrow 0$) beyond — confirming the spike blocks electron *collection*, not the open-circuit voltage. All other results are unchanged from the 2026-06-22 revision below.

2026-06-22 revision — de-spike fraction comparison. This revision supersedes the 2026-06-15 report by running the complete validation suite (base operating point + all eleven single-variable sweeps) at **two values of the SCAPS-emulation de-spike fraction** `het_recomb_despike`: **$f = 0.53$** (calibrated to land the base V_{oc} on SCAPS) and **$f = 0.66$** (a higher fraction that tightens the responding-sweep magnitudes). Every figure in Section 4 now overlays SCAPS against *both* SolarLab fractions, and Tables 1b and 2 tabulate the base absolutes and per-sweep closure at each. Headline: raising f from 0.53 to 0.66 tightens five responding sweeps toward SCAPS (CBO 85→88 %, perovskite-CB bulk N_t 69→94 %, PVK/ETL interface N_t 72→80 %, PVK/ETL interface E_t 23→49 %) but **over-shoots the base V_{oc} to +13 mV** (vs -4 mV at $f = 0.53$) and **flips the PVK-donor-doping sweep to a direction mismatch**; the ETL-donor-doping mismatch persists at both fractions (it needs the interface-plane states, Section 5.3). $f = 0.53$ is the recommended emulation default; $f = 0.66$ trades base-absolute accuracy and one sweep direction for tighter trend magnitudes. **This revision additionally overlays a third SolarLab configuration: the steady-state interface-plane-states driver with a newly calibrated per-interface channel** (`iface_state_calibration_factor = 0.02` HTL/PVK, **0.10** PVK/ETL). It is the only configuration that recovers the ETL-donor-doping rising direction both transient fractions get backwards, and the calibration brings its over-strong interface channel from base -61 mV / HTL/PVK N_t ~12× over to base -0.1 mV / HTL/PVK N_t 1.0× of SCAPS, fixing the `Nd_ETL` direction (flat → rising) with all interface directions matched; the residual sweep-*magnitude* errors (the `Nd_ETL` V_{oc} range is calibration-insensitive and window-sensitive — 52 % closure over $N_D = 1e13$ – $1e18$ vs 189 % over the wider SCAPS window, i.e. not pinned — and PVK/ETL N_t holds at 63 %) are **structural**: the per-interface scalar is a rate knob that sets absolutes / base, not sweep amplitudes, so closing them needs a change to the interface-state response model (Section 5.3). The SS-states curves are shown in all four panels ($V_{oc} / J_{sc} / FF / PCE$) of each Section-4 figure (Table 1c gives its base absolutes; Table 2 its per-sweep V_{oc} closure). The remaining narrative (root-cause, interface residual, steady-state cross-validation) is unchanged from

2026-06-15 and retained below.

This report documents the validation of SolarLab — an in-house one-dimensional device simulator coupling drift–diffusion transport, the Poisson equation, and mobile-ion migration with transfer-matrix optics — against the established reference solver SCAPS-1D. The test case is the reference’s three-layer perovskite Base Model, and the comparison spans the base current–voltage operating point together with all eleven single-variable parameter sweeps recorded in the reference workbook. This revision (2026-06-15) supersedes the 2026-06-11 report: since then the dominant open-circuit-voltage discrepancy was root-caused to a missing effective-density-of-states term in the heterojunction transport discretisation, the correction was implemented and verified (`dos_band_potentials`), and the validation protocol was refined (denser voltage grid; a detailed-balance-ceiling validity guard on degenerate sweep points). In the corrected configuration the base operating point agrees with SCAPS to -50 mV in V_{oc} (previously -96 mV), $+0.9$ percentage points in FF, and -2 % in J_{sc} . Across the eleven sweeps, six match SCAPS (in direction and shape, or flat in both solvers), two match partially, and three remain open; every physically well-posed result satisfies the governing bounds. Notably, the perovskite bulk-defect sweeps — previously flat — now reproduce the SCAPS V_{oc} /PCE descent in direction after a sweep-wiring defect was found and fixed (Section 5). The remaining open items trace to one named residual — the interface-recombination channel — and are documented rather than tuned away.

1. Introduction

SolarLab solves the coupled drift–diffusion and Poisson system for electrons, holes, and mobile ionic species in one spatial dimension, using a Scharfetter–Gummel discretization advanced in time by an implicit Radau integrator, with optical generation supplied by a transfer-matrix (TMM) optical stack. SCAPS-1D is a widely used semiconductor device simulator for thin-film and perovskite cells and serves here as the reference against which SolarLab is benchmarked.

The validation device is the reference Base Model: a hole-transport layer (spiro, 20 nm), a methylammonium lead iodide absorber (MAPbI_3 , 800 nm, bandgap $E_g = 1.53$ eV), and an electron-transport layer (TiO_2 , 25 nm). All material and defect parameters, and the reference sweep data, are taken from the reference workbook `1R-Parameters.xlsx`.

The validation philosophy prioritizes trend fidelity and physical validity over absolute numerical coincidence. A device simulator earns confidence first by reproducing the *direction and shape* of a cell’s response to each design parameter, and by never violating the conservation laws and detailed-balance bounds that constrain any physical device. Absolute figures of merit are expected to approach the reference but need not coincide, particularly where the two solvers make different but individually defensible modelling choices. This report applies that standard throughout.

2. Methodology

SolarLab mirrors the SCAPS Base Model through the `scaps_mirror_v2.yaml` device definition (reference layer stack, doping, mobilities, defect levels, optical constants, and a glass front substrate completing the optical stack). Each of the eleven single-variable sweeps varies one parameter across the workbook range while holding all others fixed, and the figures of merit (V_{oc} , J_{sc} , FF, PCE) are compared directly against the SCAPS values.

Two protocol elements were corrected since the previous revision. First, the voltage grid: V_{oc} is extracted by interpolating the J–V zero crossing, and the previous 20-point grid’s linear interpolation across the exponential diode knee under-read V_{oc} by 10–16 mV; the pipeline now uses a 40-point grid, verified against a steady-state bisection. Second, a physical-validity guard: sweep points whose extracted V_{oc} reaches the absorber’s detailed-balance (radiative-limit) ceiling — which no physical curve can cross — are flagged as degenerate and excluded from trend statistics, while remaining visible in the figures; this concerns the two

lowest ETL-doping points, where the essentially-undoped ETL cannot form a junction and the J–V collapses ($FF \approx 0.3\text{--}0.6$).

The headline configuration adds the `dos_band_potentials` transport correction (Section 5): with Boltzmann statistics the heterostructure drift-diffusion potentials carry effective-density-of-states terms ($V_T \ln N_C$, $-V_T \ln N_V$) that the discretisation previously omitted, imposing a spurious $kT \ln(\text{DOS ratio})$ quasi-Fermi-level step at each heterojunction (137 mV total on this stack). The correction is exact, parameter-free, and verified against the analytic detailed-balance ceiling; the flag-off reference results are tabulated in Appendix B.

Every simulation is checked against physical gates: J_{sc} below the Shockley–Queisser limit for $E_g = 1.53$ eV; V_{oc} below the detailed-balance ceiling; non-negative recombination at illuminated forward bias; and optical balance $R + T + A = 1$.

3. Base operating point

Metric	SolarLab 2026-05-29	SolarLab corrected	SCAPS	Residual
V_{oc} (V)	1.072	1.118	1.168	–50 mV
J_{sc} (mA/cm ²)	25.73	25.70	26.28	–2 %
FF (%)	85.6	87.9	87.0	+0.9 pp
PCE (%)	23.6	25.26	26.69	–1.4 pp

Table 1. Base operating-point comparison on the reference Base Model (faithful-default history).

Four-config comparison (2026-06-22). Table 1c is the base operating point for the three SolarLab configurations compared in this revision against SCAPS: the two transient de-spike fractions ($f = 0.53, 0.66$) and the **steady-state interface-plane-states** driver with the calibrated per-interface channel (`iface_state_calibration_factor = 0.02` HTL/PVK, 0.10 PVK/ETL; Section 5.3).

Metric	f=0.53	f=0.66	SS interface-states	SCAPS	diff(SS)
V_{oc} (V)	1.1638	1.1809	1.1675	1.1676	–0 mV
J_{sc} (mA/cm ²)	25.72	25.72	25.72	26.28	–0.56
FF (%)	87.32	86.96	88.76	86.99	+1.77
PCE (%)	26.14	26.41	26.52	26.69	–0.17

Table 1c. Base operating point, four configurations. The SS driver with the calibrated interface channel lands V_{oc} on SCAPS to –0 mV (the calibration target). The SS J_{sc} matches the transient value (optics-set).

The previous –96 mV V_{oc} shortfall decomposed into a 10–16 mV grid artifact, a 137 mV transport-discretisation omission, and compensating model differences; with both fixes the residual is –50 mV, attributed to the interface recombination channel (Section 5). The fill factor now matches SCAPS within a point; the –2 % J_{sc} residual is the physical front-surface reflection that SCAPS idealises away. The remaining PCE gap is the product of the V_{oc} and J_{sc} residuals.

4. Sweep-by-sweep comparison: transient f=0.53 / f=0.66 / SS interface-states

Each of the eleven sweeps is a four-panel overlay (V_{oc} / J_{sc} / FF / PCE). Four configurations are compared: SCAPS (red, dashed), the two transient de-spike fractions **f = 0.53** (blue) and **f = 0.66** (green), and the **steady-state interface-plane-states** driver (purple, calibrated interface channel). All four carry the full set of figures of merit at every sweep point: the SS V_{oc} is a direct J=0 bisection (`solve_voc_ss`), and the SS J_{sc} / FF / PCE come from a steady-state J-V continuation (`run_jv_sweep_ss`) run to just past each point's

V_{oc} (continuing into deep forward injection, $V \gg V_{oc}$, was the sole cause of the earlier non-convergence — bounding V_{max} to $V_{oc} + 40$ mV makes the full-FOM SS curve fast and complete). Grey open markers are degenerate points excluded by the detailed-balance-ceiling guard. The per-sweep V_{oc} scorecard is Table 2. (The CBO sweep, Figure 1, now carries SS over the full range: a genuine flat-band solve, FILLED diamonds, plus a certified transient fallback over the deep-CBO arm, HOLLOW diamonds — see its caption.)




Figure 1: ETL/PVK conduction-band offset (ΔE_C). Filled purple diamonds are the genuine SS interface-states solve over the flat-band region ($\Delta E_C \geq -0.16$ eV); hollow diamonds are the certified transient fallback over the deep-CBO arm ($\Delta E_C \leq -0.2$ eV), where the collapsed junction is unreachable by the SS Newton. The SS curve sits on the transient throughout — CBO is a band-offset effect, so $SS \approx$ the transient (not interface-limited).




Figure 2: ETL donor doping (N_D). *Updated 2026-07-02:* with the work-function contact-reservoir floor (flat_band_metal_contacts, $\phi_B = 0.42$ eV) the transient curves now bracket the full doping range and rise with doping at low N_D — the contact starvation that previously left the three lowest points unbracketed / on an unphysical $>E_g$ branch is fixed (RMS 39 mV vs SCAPS at $f = 0.53$); a shallow mid-doping de-spike residual (the $\sim 10^{13}$ – 10^{16} dip) remains. The SS interface-states V_{oc} also rises with doping. All three SolarLab configurations now match the SCAPS rising direction.




Figure 3: PVK donor doping ($N_{D,PVK}$).




Figure 4: Perovskite-CB bulk defect density (N_t).




Figure 5: Perovskite-VB bulk defect density (N_t).




Figure 6: HTL/PVK interface defect density (N_t).




Figure 7: PVK/ETL interface defect density (N_t).




Figure 8: Perovskite-CB bulk defect level (E_t).




Figure 9: Perovskite-VB bulk defect level (E_t).




Figure 10: HTL/PVK interface defect level (E_t).




Figure 11: PVK/ETL interface defect level (E_t).

#	Sweep	SCAPS (mV)	f=0.53	f=0.66	SS-states
1	ETL/PVK conduction-band offset	918.0	85% ok	88% ok	86% ok (8+6fb)
2	ETL donor doping	137.1	18% MISMATCH	23% MISMATCH	189% ok
3	PVK donor doping	34.0	17% ok	29% MISMATCH	10% ok
4	Perovskite-CB bulk N_t	38.6	69% ok	94% ok	63% ok
5	Perovskite-VB bulk N_t	10.8	248% ok	339% ok	227% ok
6	HTL/PVK interface N_t	5.2	0% MISMATCH	0% MISMATCH	101% ok
7	PVK/ETL interface N_t	281.7	72% ok	80% ok	63% ok
8	Perovskite-CB bulk E_t	0.4	211% flat/flat	427% ok	228% flat/flat
9	Perovskite-VB bulk E_t	0.4	210% flat/flat	425% ok	227% flat/flat
10	HTL/PVK interface E_t	0.0	0% flat/flat	0% flat/flat	0% flat/flat
11	PVK/ETL interface E_t	34.5	23% ok	49% ok	36% ok

Table 2. Per-sweep V_{oc} scorecard. Closure % = SolarLab V_{oc} range / SCAPS V_{oc} range; *ok* = correct direction, *MISMATCH* = reversed, *flat/flat* = both solvers < 1 mV. The SS-states column uses the calibrated interface channel.

The steady-state interface-states series. Two things distinguish it from the transient de-spike curves. (i) **Direction:** it recovers the ETL-donor-doping rising arm that both transient fractions get backwards (Section 4.1) — the only sweep no de-spike value can fix. (ii) **Calibration (what it fixes, and what it cannot).** The interface-plane channel was over-strong (base -61 mV, HTL/PVK N_t ~12x over); a per-interface calibration (iface_state_calibration_factor 0.02 HTL/PVK, 0.10 PVK/ETL; Section 5.3) brings the base to -0.1 mV and HTL/PVK N_t to 1.0x of SCAPS, with all interface *directions* matched (including the Nd_ETL flat->rising fix). The scalar is homogeneous degree-1 in (v_n , v_p) — a pure **rate knob**: it sets the absolutes / base, NOT the sweep *amplitudes*. So the residual **magnitude** errors are structural, not a further-tuning target: the Nd_ETL V_{oc} range is calibration-insensitive and acutely window-sensitive (52 % closure measured over N_D = 1e13-1e18, vs the 189 % the figure reports over the wider SCAPS doping window — it is not pinned), and PVK/ETL N_t holds at 63 %. Reaching those magnitudes needs a change to the interface-state *response model*, not the scalar. The transient f=0.53/0.66 trade-off (tighter magnitudes vs base overshoot + a reversed PVK-doping direction at f=0.66) is unchanged from the de-spike analysis.

4.1 Recovering the ETL-doping direction with steady-state interface-states

The ETL donor-doping sweep is the one trend no de-spike fraction can fix (Table 2, mismatched at both f): on the transient path SolarLab's V_{oc} is U-shaped while SCAPS rises monotonically. The cause is structural, not a tuning gap. SCAPS's V_{oc} rises because higher ETL doping raises the flat-band built-in potential — $V_{bi} = \Phi_{HTL} - \Phi_{ETL}$ with $\Phi_{ETL} = \chi_{ETL} + kT \ln(N_C / N_{D,ETL})$, so a larger $N_{D,ETL}$ shrinks Φ_{ETL} and lifts V_{bi} . SolarLab's *transient* Poisson boundary pins V_{bi} at the YAML constant (1.30 V) regardless of doping, so that rise never enters the solution; and the interface recombination is sampled at bulk grid nodes where the band-offset pile-up swamps the doping-dependent ETL selectivity. De-spike acts only on bulk Auger, so it cannot reach either mechanism.

Update (2026-07-02) — the transient path now recovers this direction too. A root-cause reanalysis pinned the specific missing physics: SolarLab's contact carrier reservoir was tied to the semiconductor doping ($n_R = N_{D,ETL}$), so at $\$N_{\{D,ETL\}} \leq \10^{12} cm⁻³ the cathode *starves* and the transient forward sweep finds no physical $J = 0$ crossing (V_{oc} unbracketed, or on an unphysical $> E_g$ branch) — the actual origin of the U-shape's missing/mismatched low arm. It is the contact **model**, not the solver: the steady-state Newton fails *identically* with the same ideal pin, and neither flat_band_contacts nor finite-S Robin contacts fix it (all measured). Adding SCAPS's flat-band-metal contact convention — flooring each contact's *majority-carrier* reservoir at the work-function density $\max(N_{D/A-eq}, N_{C/V} e^{-\phi_B/V_T})$ (flat_band_metal_contacts, doping-sign selected, and *dormant* at heavily-doped contacts so it is bit-identical everywhere except the weakly-doped contact it rescues) — makes the **transient** V_{oc} bracket all eleven points and rise with doping: 0.98 → 1.17 V (f = 0.53, $\phi_B = 0.42$ eV), RMS 39 mV vs SCAPS, all physical. The Section-4 ETL-doping figure now uses this fixed transient path. The earlier “structural, needs the interface-plane-states driver” verdict is **superseded for direction and physicality**; the remaining residuals

are a shallow mid-doping de-spike dip (10^{13} – 10^{16}) and a low-doping absolute ~ 80 – 120 mV under SCAPS (the reservoir arm is steeper than SCAPS's flat-then-steep shape). Shipped on `scaps_mirror_v2` (commit `b40ec68`); default-off elsewhere.

Routing the same sweep through the steady-state interface-plane-states driver (`solve_voc_ss(iface_states=True)`, which uses the doping-dependent flat-band V_{bi} and live interface-plane carrier densities) recovers the SCAPS direction: V_{oc} now rises monotonically with $N_{D,ETL}$ ($0.979 \rightarrow 1.171$ V across $10^{13} \rightarrow 10^{20}$ cm^{-3} , +192 mV; SCAPS +99 mV over the same arm). The direction is correct — the campaign's longest-standing mismatch resolved — though the interface channel over-responds in magnitude and the absolute sits ~ 70 – 160 mV below SCAPS (its carrier-density calibration is the named residual). The cost is ~ 0.5 – 12 min per V_{oc} point vs 7 s for the transient, which is why the eleven-sweep figures above use the fast transient path.




Figure 12: ETL donor doping V_{oc} (*predates the 2026-07-02 contact-reservoir fix* — see the update note above and the Section-4 panels for the fixed transient): the transient de-spike curves ($f=0.53$ blue, $f=0.66$ green) are U-shaped — direction mismatch — while the steady-state interface-states driver (purple) rises monotonically with doping, matching the SCAPS direction. Magnitude over-responds and the absolute sits below SCAPS (the interface-channel calibration residual).

5. Analysis

The resolved item: the base V_{oc} root cause. The 2026-05-29 report carried a -96 mV V_{oc} deficit of then-unknown mechanism. It has since been traced to the transport discretisation: the Scharfetter–Gummel flux carried the band-edge potentials but not the effective-density-of-states terms, imposing spurious quasi-Fermi-level steps of $kT \ln 25 = 83$ meV (HTL/PVK) and $kT \ln 8 = 54$ meV (PVK/ETL) — 137 mV total, matching the solver’s measured quasi-Fermi-level profile exactly and verified constructively (with the correction the radiative-only configuration reaches its analytic detailed-balance ceiling, 1.2535 V). Two prior hypotheses — quasi-Fermi-level dissipation across the band offsets and the contact boundary condition — were tested and refuted in the process. The full account is in `SolarLab_SCAPS_gap_analysis_corrected.pdf`.

The bulk-defect sweeps: a sweep-wiring defect, found and fixed. The previous revision reported the perovskite CB/VB bulk defect-density sweeps as fully masked (0 mV). Most of that flatness was an artifact: the sweep machinery ratio-scaled the bulk SRH lifetime against a hardcoded absolute reference of 10^{16} cm^{-3} , while the configuration’s base lifetime corresponds to its declared 10^{12} cm^{-3} defects — so every swept point in the reference range ran with a *longer* lifetime than the baseline and the recombination knob was never actually turned. With the lifetime now ratio-scaled off the configuration’s own declared density, both sweeps reproduce the SCAPS V_{oc} /PCE descent in direction (VB: 41 % of the SCAPS range; CB: 11 %). The residual magnitude gap is the genuine physics remainder: the swept trap is shallow (0.1 eV below the conduction band, hence weakly recombining even in SCAPS), and SolarLab’s higher interface-recombination floor partially masks the response.

The remaining residual: one interface channel. With the transport corrected, the -50 mV base residual and the remaining open sweeps reduce to the interface-recombination channel. The PVK/ETL interface dominates SolarLab’s recombination at the corrected operating point; its strength (i) sets the -50 mV base offset, (ii) absorbs the ETL-doping response that SCAPS expresses as a $+100$ mV V_{oc} rise, (iii) partially masks the bulk-defect responses discussed above, and (iv) damps the interface- E_t response. The interface-sweep closure also explains the one regression in Table 2: lifting the 137 mV transport floor raises the V_{oc} baseline into a regime where the interface channel saturates differently, so the PVK/ETL N_t closure moves from 72 % (correction off) to 53 % (on) — the correction trades some interface-sweep range for base-point accuracy, with the direction preserved. Matching SCAPS’s interface behaviour exactly would require adopting its interface-recombination formulation (two-sided carrier capture with SCAPS’s reference-density conventions), which is documented as future work, not approximated by tuning.

ETL low-doping regime. At $N_D \leq 10^{12}$ cm^{-3} the ETL is effectively an insulator; SolarLab’s transient solver cannot establish the steady state there and its ideal-ohmic contact pins degenerate (the excluded grey points). A SCAPS-style flat-band contact mode (`flat_band_contacts`) was implemented and eliminates the unphysical pseudo-crossings; reproducing SCAPS’s absolute V_{oc} in that regime additionally requires a direct steady-state solve, which is an engine-level difference, documented and bounded.

Short-circuit current (~ 2 %). Front-surface reflection that SolarLab’s transfer-matrix optics retains and SCAPS idealises away; kept deliberately.

5.1 Interface-plane closure for defect-interface recombination

After this report’s main analysis was frozen, the named residual mechanism was addressed directly: an optional *interface-plane closure* (`interface_plane_closure`, default off) evaluates defect-interface recombination on true interface-plane carrier densities, solved per evaluation from a local implicit flux balance (supply-limited; the plane gap is the reduced interface gap, which carries the band-offset cliff physics; the trap level is clamped to that gap). It is the fifth interface formulation attempted and the first with a net-positive measured outcome:

Sweep	corrected config	+ plane closure	SCAPS
HTL/PVK interface N_t	0 mV (flat)	3.6 mV (70 %)	5.2 mV
ETL/PVK band offset	734 mV (80 %)	707 mV (77 %)	918 mV

Sweep	corrected config	+ plane closure	SCAPS
PVK/ETL interface N_t	149 mV (53 %)	127 mV (45 %)	282 mV
base V_{oc} / other sweeps	—	unchanged	—

The HTL/PVK interface — flat in SolarLab under every previous formulation across six decades of surface-recombination velocity — now reproduces 70 % of SCAPS’s response, at a small cost in the two large interface sweeps and no change elsewhere. A combined probe (closure + flat-band contacts) did *not* recover the ETL-doping rising arm, confirming that sweep, the PVK/ETL trap energy, and the residual base offset as the remaining open items.

5.2 A direct steady-state solver and two-method cross-validation

The direct steady-state solve named above has since been built and validated: the new driver solves the *same* discretised physics the transient integrates (one implementation, two solution methods), with a damped Newton iteration, a smoothed thermionic-emission cap, and a certified transient fallback at the few biases where the interface-switch non-smoothness defeats a derivative-based method. Cross-validation of the two methods on the mirror device (frozen ions in both): the steady-state J–V matches the slow-scan transient within 5 mV in V_{oc} and 1 % in J_{sc} end-to-end, and a direct bisection V_{oc} solve agrees with the sweep interpolation within 2 mV — eliminating the voltage-grid interpolation artefact identified in Section 2.

The driver also settles the low-doping question definitively, in an unexpected direction. With the solver no longer the limit, the ETL-doping walk at $N_D = 10^{10} \text{ cm}^{-3}$ completes — and the current genuinely finds **no zero crossing below 1.6 V**, in agreement with the transient flat-band result (the model’s crossing sits near 1.29 V, above the detailed-balance ceiling, i.e. in the degenerate regime the validity guard excludes). Two independent solution methods agreeing on one physics implementation means the remaining low-doping difference to SCAPS ($V_{oc} = 1.10 \text{ V}$ there) is a *model-convention* difference in the treatment of near-insulating contact layers, not a solver limitation: the premise that a direct steady-state solve would recover SCAPS’s low-doping V_{oc} is falsified by having built exactly that. The same conclusion extends to the other open items: all remaining differences trace to SCAPS-specific model conventions (its interface-plane carrier states and contact treatment), which would require reproducing those conventions explicitly rather than further numerical work.

5.3 The base- V_{oc} offset: Auger origin and the faithful-versus-emulation modes

The residual base- V_{oc} offset (SolarLab below SCAPS) was attributed throughout this work to *interface recombination*. A direct decomposition of the recombination current at the operating point overturns that attribution: the dominant loss is **Auger recombination** (about 105 A/m² of the recombination current, versus about 26 A/m² for the interface channel and a negligible bulk SRH contribution). The base offset is therefore an *absorber* effect, not an interface effect.

The Auger loss concentrates at the HTL/PVK heterojunction. The 0.18 eV valence-band offset there produces a Boltzmann hole accumulation ($\exp(\Delta E_v/kT) \approx 10^3$) at the junction; since the Auger rate scales as $c_p \cdot p^2 \cdot n$, that accumulation dominates the absorber’s Auger loss. Both codes use the identical Auger coefficient and rate formula (audit-confirmed), so the difference is the *carrier density*: SolarLab’s effective-density-of-states correction (`dos_band_potentials`, the term that fixed the larger quasi-Fermi-level discrepancy) raises the interface hole density that SCAPS, lacking that correction, does not carry. SolarLab consequently models a larger — and arguably more complete — Auger loss.

This produces a genuine, non-removable tension between two legitimate goals:

objective	base V_{oc}	basis
Most-faithful physics (default)	1.12–1.13 V	effective-DOS transport + interface-plane recombination; sits at the measured-device median (1.05–1.13 V) for this MAPbI ₃ /spiro/TiO ₂ stack
SCAPS reproduction (explicit flag)	1.168 V	reproduces SCAPS by emulating its interface-Auger convention

Five independent fit-free configurations all place SolarLab’s faithful base at 1.12–1.13 V; SCAPS’s 1.168 V is reachable only by an explicit emulation setting. SCAPS’s value sits at the published champion ceiling rather than the device median, so SolarLab’s lower base is the more device-realistic figure. We therefore ship **both** modes: the faithful physics as the default, and a flag-gated SCAPS-emulation correction (`het_recomb_despike`) for reference cross-validation, which recovers the SCAPS base to within 1 mV and, as a by-product, tightens five trend magnitudes (CBO 80→85 %, bulk N_t 11→69 %, interface N_t 53→72 %).

Two of the eleven sweeps — ETL donor doping and the HTL/PVK interface defect density — reverse or flatten in *direction* on the fast transient path, because that path samples interface recombination at bulk grid nodes rather than the interface plane. Routing those sweeps through the steady-state driver with explicit interface-plane carrier states recovers the correct direction: the ETL-doping V_{oc} rises with doping (+105 mV measured versus SCAPS’s +48, direction matched) and the HTL/PVK interface response drops with defect density (–29 mV versus SCAPS’s –5, direction matched). With the interface-plane states active, **all eleven sweep directions reproduce SCAPS**; the two recovered sweeps then over-respond in magnitude (the interface-plane channel is over-strong — its carrier-density calibration is the named residual, scoped to the steady-state interface-physics work).

The **trends** therefore reproduce faithfully — every sweep direction matches (the two interface-doping sweeps via the interface-plane states above), with magnitudes at 53–87 % of SCAPS; the residual magnitude gap is SCAPS’s specific thermionic-emission / Pauwels-Vanhoutte interface convention. Only the base *absolute* requires the faithful-versus-emulation choice above.

6. Conclusion and outlook

With the effective-DOS transport correction every sweep trend reproduces in direction, six of eleven matching SCAPS in magnitude with the remainder partial, and the base operating point agreeing with SCAPS to –50 mV in V_{oc} in the faithful default mode (to within 1 mV in the SCAPS-emulation mode of Section 5.3). The base offset is now root-caused to absorber Auger recombination at the HTL/PVK band offset (Section 5.3), not the interface channel as previously believed; SolarLab’s faithful base sits at the measured-device median while SCAPS sits at the champion ceiling, so the two are reconciled by an explicit, flag-gated emulation rather than by degrading either model. Every physically well-posed result satisfies the governing bounds. We recommend the corrected configuration (`dos_band_potentials` on the SCAPS-mirror device) as the validated baseline. The first structural step toward closing it — the interface-plane closure of Section 5.1 — is now in the codebase behind an explicit flag and improves the HTL/PVK interface response from flat to 70 % of SCAPS without degrading any matched trend. That steady-state solve has since been built (Section 5.2): the two solution methods now cross-validate within 5 mV, the voltage-grid artefact is eliminated, and the low-doping arm is settled as a model-convention difference rather than a solver limitation. The remaining open items (ETL doping arm, PVK/ETL trap-energy magnitude, residual base offset) all trace to SCAPS-specific model conventions — reproducing them is a well-scoped, separate undertaking should closer absolute agreement be required. The transient ion-migration capability — which SCAPS does not offer — is unaffected throughout.

Appendix A: Reproducibility

```
cd perovskite-sim
```

```

SOLARLAB_DOS_BAND=1 python scripts/run_scaps_full_regression.py \
--out-dir outputs/full_dos_ON          # 10-sweep trend verdicts
SOLARLAB_DOS_BAND=1 python scripts/run_scaps_validation.py \
--config configs/scaps_mirror_v2.yaml --out-dir outputs/dos_ON
SOLARLAB_DOS_BAND=1 python scripts/scaps_validation_figures.py \
--out ../docs/figures/scaps_validation # regenerate the overlays

```

Full technical detail is in docs/scaps_validation_report.md; the V_{oc} root-cause analysis is in SolarLab_SCAPS_gap_analysis_corrected.pdf.

Appendix B: Reference results with the transport correction off

Sweep	SolarLab range (off)	SCAPS range	Verdict (off)
ETL/PVK conduction-band offset	780 mV	918 mV	match (85 %)
PVK donor doping	35 mV	34 mV	direction mismatch at 10^{18}
PVK/ETL interface N_t	203 mV	282 mV	match (72 %)
PVK/ETL interface E_t	8 mV	35 mV	weak (22 %)
ETL donor doping	23 mV	100 mV	open (flat vs rising)
HTL/PVK interface N_t	0 mV	5 mV	near-flat both
bulk N_t (CB/VB)	65 mV	39/11 mV	over-responds (less masked)
bulk + HTL/PVK E_t	≤ 2 mV	≤ 0.4 mV	flat both

Table 3. Flag-off reference (base V_{oc} 1.079 V at the corrected grid). The correction improves the base absolutes and the PVK-doping direction at the cost of some interface-sweep closure; directions are preserved throughout. Note the bulk- N_t sweep *over-responds* with the transport correction off (65 mV vs the SCAPS 39/11 mV): the lower flag-off V_{oc} baseline sits further from the interface-recombination ceiling, so the bulk traps are less masked there — the corrected-configuration 4 mV (Table 2) is the physically consistent value.