No.	Status	Date
HIS-2010-0318-DFR-1	Issued	2010-09-13

Daily Field Report 1 - UT Thickness Survey - Regenerator Overhead and 4-RA-104 New Spool Baseline

Scope and Responsibilities

Kevin Doucette performed a UT thickness survey on the regenerator overhead and a new spool baseline for the rich side of the L/R exchanger. The scope of work was executed under the authority of QSCP-WP-2010-09130 for three lines located within the ATU-100.

The survey was conducted in accordance with QSCP-NDT-001 Rev 1 and HIS-UT-002 Rev 1. Kevin Doucette acted as the lead UT technician, ensuring all measurements adhered to the specified requirements for CMLs at fittings and scanning at elbows and tees.

Equipment and Calibration

Thickness measurements were performed using a Krautkramer DMS 2 0317. The instrument's calibration is verified by HIS-CAL-10-087.

Calibration was performed using HIS-STB-02 in accordance with ASTM E797 to ensure accuracy of the waveform display and thickness readings.

Regenerator Overhead Survey

UT thickness measurements were taken on 3-RV-101, an A106 Gr.B line with an OD of 88.9 mm and a nominal thickness of 7.62 mm. The design limits for this line are 345 kPa(g) and 121 °C.

Measurements were also performed on 2-RV-102, an A106 Gr.B line with an OD of 60.3 mm and a nominal thickness of 5.54 mm. The design limits for this line are 345 kPa(g) and 121 °C.

L/R Exchanger Baseline

A baseline thickness survey was conducted on the new spool for 4-RA-104, the rich side of the L/R exchanger. This A106 Gr.B line has an OD of 114.3 mm and a nominal thickness of 8.56 mm.

The design limits for 4-RA-104 are 862 kPa(g) and 127 °C. All baseline readings were recorded to establish the initial thickness for future corrosion rate and remaining life calculations.

Sign-off	Name	Function	Date	Signature
Prepared	Kevin Doucette	lead UT technician, SNT-TC-1A UT Level II	2010-09-13	_____