No.	Status	Date
HIS-2011-0207-DFR-1	Issued	2011-02-17

Daily Field Report 1 - UT Thickness Survey - ATU-100 Sour Gas and Rich Amine

Scope and Responsibilities

Kevin Doucette, acting as lead UT technician, performed a thickness survey on six lines within the ATU-100. The primary objective was to execute ultrasonic thickness measurements on sour gas and rich amine piping to monitor wall loss and ensure asset integrity.

All activities were conducted under the authority of QSCP-WP-2011-02171. The technician is responsible for the accurate acquisition of thickness data and the identification of any readings falling below the established retirement thickness.

Applicable Procedures and Standards

The inspection was performed under the site-specific requirements of QSCP-NDT-001 Rev 2, which incorporates the CUI program, including insulation removal and inspection-port requirements. The general methodology followed HIS-UT-002 Rev 1.

Measurement techniques and data acquisition were conducted in accordance with ASTM E797. All thickness readings were compared against the design minimums specified for the respective piping circuits.

Equipment and Calibration

Thickness measurements were obtained using a Krautkramer DMS 2 0317. The instrument's validity was verified via HIS-CAL-10-087, confirming the annual gauge calibration.

Field calibration and standardization were performed using the HIS-STB-02 calibration block to ensure measurement accuracy prior to the commencement of the survey.

Inspection Summary - Sour Gas Inlet

UT thickness measurements were taken on 6-SG-101 and 6-SG-102. Both lines are A106 Gr.B with an outer diameter of 168.3 mm and a nominal thickness of 7.11 mm.

The survey monitored these lines against a design pressure of 1965 kPa(g) and a design temperature of 66 °C, with a retirement thickness (t-min) of 3.56 mm.

Inspection Summary - Rich Amine

UT thickness measurements were taken on 4-RA-101 and 4-RA-102. Both lines are A106 Gr.B with an outer diameter of 114.3 mm and a nominal thickness of 8.56 mm.

The survey monitored these lines against a design pressure of 862 kPa(g) and a design temperature of 82 °C, with a retirement thickness (t-min) of 3.81 mm.

Sign-off	Name	Function	Date	Signature
Prepared	Kevin Doucette	lead UT technician, SNT-TC-1A UT Level II	2011-02-17	_____