No.	Status	Date
HIS-2011-0207-DFR-2	Issued	2011-02-18

Daily Field Report 2 - UT Thickness Survey - ATU-100 Sour Gas and Rich Amine

Scope and Responsibilities

Kevin Doucette, acting as lead UT technician, performed ultrasonic thickness measurements on piping within the ATU-100. The objective was to execute a thickness survey on 6 lines as authorized under QSCP-WP-2011-02171.

The inspection was conducted in accordance with the site-specific requirements of QSCP-NDT-001 Rev 2 and the corporate methodology detailed in HIS-UT-002 Rev 1. All measurements were performed to the standards defined in ASTM E797.

Equipment and Calibration

Thickness data was acquired using a Krautkramer DMS 2 0317. The instrument's accuracy and validity were verified against HIS-CAL-10-087.

Field calibration and standardization were performed using the HIS-STB-02 calibration block to ensure measurement precision prior to the survey of the piping circuits.

Inspection of Line 6-RA-103

Ultrasonic thickness measurements were taken on 6-RA-103, the rich amine header. This A106 Gr.B line has a nominal thickness of 10.97 mm and a minimum allowable thickness of 4.57 mm.

The survey was conducted considering the design limits of 862 kPa(g) and 82 °C. All readings were compared against the retirement thickness of 4.57 mm to determine if an NCR was required.

Inspection of Line 4-RA-104

Thickness measurements were performed on 4-RA-104, the L/R exchanger rich side. This A106 Gr.B line has a nominal thickness of 8.56 mm and a minimum allowable thickness of 3.81 mm.

The survey accounted for the design limits of 862 kPa(g) and 127 °C. Data was collected to evaluate the remaining life based on the 3.81 mm retirement thickness.

Sign-off	Name	Function	Date	Signature
Prepared	Kevin Doucette	lead UT technician, SNT-TC-1A UT Level II	2011-02-18	_____