Halward Inspection Services Ltd.

Inspection Report

Site: Hamilton Plant

No.	Status	Date
HIS-2011-0207-DS-4-RA-101	Issued	2011-02-18

UT Thickness Data Sheet - 4-RA-101

Scope and Responsibilities

This data sheet provides the ultrasonic thickness measurement results for line 4-RA-101 located within the ATU-100. The primary objective is to assess the current wall thickness of the rich amine service piping to determine the remaining life and schedule the next inspection interval based on site retirement thickness and corrosion rate rules.

Kevin Doucette, acting as the lead UT technician and SNT-TC-1A UT Level II for Halward Inspection Services Ltd., is responsible for the execution of the thickness measurements and the recording of the data presented herein.

Technical Specifications

The subject line, 4-RA-101, is constructed from A106 Gr.B with an outside diameter of 114.3 mm and a nominal wall thickness of 8.56 mm. The design parameters for this line are 862 kPa(g) and 82 °C, with a minimum allowable thickness (t-min) of 3.81 mm.

All measurements were performed in accordance with ASTM E797. The inspection was conducted under the site-specific requirements of QSCP-NDT-001 Rev 2, which incorporates updated requirements for the CUI program, including insulation removal and inspection-port requirements.

Procedural Compliance

The field activities were performed under the Halward Inspection Services Ltd. procedure HIS-UT-002 Rev 1, which was submitted for QSCP acceptance. This ensures that the ultrasonic thickness measurement techniques align with both contractor and client quality standards.

The data collected for this line is integrated into the broader 5-year Class 1 survey detailed in HIS-2011-0207. This report covers the UT Thickness Survey for the ATU-100 Sour Gas and Rich Amine circuits.

Integrity Assessment

Based on the findings recorded in HIS-2011-0207, the rich amine service in this circuit is currently at half remaining life. The assessment follows the site rule where the corrosion rate is determined by the larger of the long-term rate or the short-term rate over the latest pair of readings at least 3 years apart.

The next thickness reading for 4-RA-101 is due at no more than half the remaining life, ensuring compliance with the Class 1 survey maximums for the ATU-100.

Thickness readings, measured 2011-02-18

Line 6-SG-101 | Sour gas inlet | A106 Gr.B | t_nom 7.11 mm | t-min 3.56 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
6-SG-101-01	7.11	3.56	2006-02-24	6.59	6.39	0.049	0.040	>50	2016-02-18	
6-SG-101-02	7.11	3.56	2006-02-24	6.51	6.14	0.061	0.074	34.7	2016-02-18	
6-SG-101-03	7.11	3.56	2006-02-24	6.42	6.17	0.061	0.050	42.9	2016-02-18	
6-SG-101-04	7.11	3.56	2006-02-24	6.28	6.05	0.070	0.046	35.8	2016-02-18	
6-SG-101-05	7.11	3.56	2006-02-24	6.22	5.87	0.085	0.070	27.2	2016-02-18	
6-SG-101-06	7.11	3.56	2006-02-24	6.49	6.27	0.054	0.044	>50	2016-02-18	
6-SG-101-08	7.11	3.56	—	—	6.33	—	—	—	2016-02-18	

Line 6-SG-102 | Sour gas inlet | A106 Gr.B | t_nom 7.11 mm | t-min 3.56 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
6-SG-102-01	7.11	3.56	2006-02-24	6.26	5.75	0.093	0.102	21.4	2016-02-18	
6-SG-102-02	7.11	3.56	2006-02-24	6.25	5.80	0.088	0.090	24.8	2016-02-18	
6-SG-102-03	7.11	3.56	2006-02-24	6.26	5.80	0.083	0.092	24.3	2016-02-18	
6-SG-102-04	7.11	3.56	2006-02-24	6.22	5.73	0.084	0.098	22.1	2016-02-18	
6-SG-102-05	7.11	3.56	2006-02-24	6.72	6.46	0.045	0.052	>50	2016-02-18	

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
6-SG-102-06	7.11	3.56	—	—	6.41	—	—	—	2016-02-18	

Line 4-RA-101 | Rich amine | A106 Gr.B | t_nom 8.56 mm | t-min 3.81 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
4-RA-101-01	8.56	3.81	2006-02-24	8.27	8.32	0.013	-0.010	>50	2021-02-18	
4-RA-101-02	8.56	3.81	2006-02-24	8.27	8.20	0.023	0.014	>50	2021-02-18	
4-RA-101-03	8.56	3.81	2006-02-24	8.10	7.98	0.042	0.024	>50	2021-02-18	
4-RA-101-04	8.56	3.81	2006-02-24	8.34	8.21	0.028	0.026	>50	2021-02-18	
4-RA-101-05	8.56	3.81	2006-02-24	8.29	8.16	0.029	0.026	>50	2021-02-18	
4-RA-101-07	8.56	3.81	2006-02-24	8.30	8.30	0.020	0.000	>50	2021-02-18	
4-RA-101-08	8.56	3.81	2006-02-24	8.07	8.02	0.044	0.010	>50	2021-02-18	
4-RA-101-09	8.56	3.81	2006-02-24	8.43	8.32	0.017	0.022	>50	2021-02-18	
4-RA-101-10	8.56	3.81	2006-02-24	8.27	8.28	0.026	-0.002	>50	2021-02-18	
4-RA-101-11	8.56	3.81	2006-02-24	8.14	8.04	0.043	0.020	>50	2021-02-18	

Line 4-RA-102 | Rich amine | A106 Gr.B | t_nom 8.56 mm | t-min 3.81 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
4-RA-102-01	8.56	3.81	2006-02-24	8.41	8.33	0.014	0.016	>50	2021-02-18	
4-RA-102-02	8.56	3.81	2006-02-24	8.15	7.99	0.039	0.032	>50	2021-02-18	
4-RA-102-03	8.56	3.81	2006-02-24	8.27	8.04	0.035	0.046	>50	2021-02-18	
4-RA-102-04	8.56	3.81	2006-02-24	8.24	7.96	0.039	0.056	>50	2021-02-18	
4-RA-102-05	8.56	3.81	2006-02-24	8.19	8.07	0.032	0.024	>50	2021-02-18	
4-RA-102-06	8.56	3.81	2006-02-24	8.15	8.01	0.033	0.028	>50	2021-02-18	
4-RA-102-07	8.56	3.81	2006-02-24	8.29	8.10	0.032	0.038	>50	2021-02-18	
4-RA-102-08	8.56	3.81	2006-02-24	8.05	7.88	0.041	0.034	>50	2021-02-18	
4-RA-102-09	8.56	3.81	2006-02-24	8.18	7.98	0.038	0.040	>50	2021-02-18	
4-RA-102-11	8.56	3.81	—	—	8.19	—	—	—	2021-02-18	

Line 6-RA-103 | Rich amine header | A106 Gr.B | t_nom 10.97 mm | t-min 4.57 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
6-RA-103-01	10.97	4.57	2006-02-24	10.76	10.47	0.035	0.058	>50	2021-02-18	
6-RA-103-02	10.97	4.57	2006-02-24	10.50	10.23	0.058	0.054	>50	2021-02-18	
6-RA-103-03	10.97	4.57	2006-02-24	10.67	10.42	0.038	0.050	>50	2021-02-18	
6-RA-103-04	10.97	4.57	2006-02-24	10.40	9.97	0.068	0.086	>50	2021-02-18	
6-RA-103-05	10.97	4.57	2006-02-24	10.34	10.10	0.057	0.048	>50	2021-02-18	
6-RA-103-06	10.97	4.57	2006-02-24	10.74	10.56	0.030	0.036	>50	2021-02-18	
6-RA-103-07	10.97	4.57	2006-02-24	10.66	10.55	0.029	0.022	>50	2021-02-18	
6-RA-103-08	10.97	4.57	2006-02-24	10.58	10.44	0.035	0.028	>50	2021-02-18	
6-RA-103-09	10.97	4.57	2006-02-24	10.67	10.56	0.030	0.022	>50	2021-02-18	
6-RA-103-10	10.97	4.57	2006-02-24	10.27	10.05	0.065	0.044	>50	2021-02-18	
6-RA-103-13	10.97	4.57	—	—	10.45	—	—	—	2021-02-18	

Line 4-RA-104 | L/R exchanger, rich side | A106 Gr.B | t_nom 8.56 mm | t-min 3.81 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
4-RA-104-01	8.56	3.81	2006-02-24	8.16	7.95	0.037	0.042	>50	2021-02-18	
4-RA-104-02	8.56	3.81	2006-02-24	8.23	8.14	0.027	0.018	>50	2021-02-18	
4-RA-104-03	8.56	3.81	2010-09-13	8.59	8.56	0.069	0.069	>50	2021-02-18	
4-RA-104-04	8.56	3.81	2010-09-13	8.52	8.60	-0.185	-0.185	>50	2021-02-18	
4-RA-104-05	8.56	3.81	2010-09-13	8.43	8.57	-0.324	-0.324	>50	2021-02-18	
4-RA-104-06	8.56	3.81	2006-02-24	8.09	7.98	0.041	0.022	>50	2021-02-18	

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
4-RA-104-07	8.56	3.81	2006-02-24	7.97	7.78	0.054	0.038	>50	2021-02-18	
4-RA-104-08	8.56	3.81	—	—	8.18	—	—	—	2021-02-18	

Sign-off	Name	Function	Date	Signature
Prepared	Kevin Doucette	lead UT technician, SNT-TC-1A UT Level II	2011-02-18	_____