No.	Status	Date
LNDE-FN-20241025-031-DFR-1	Issued	2024-11-04

Daily Field Report 1 - Field Notes - ATU-100 UT Thickness Survey, WO-20241025-031

Scope of Work and Responsibilities

Marcus Chen, acting as lead UT technician, commenced the five-year ultrasonic thickness survey within the ATU-100 unit. The primary objective is the measurement of 150 CMLs to assess wall loss and determine remaining life in accordance with site asset-integrity rules.

All field activities are performed under the authority of QSCP-WP-2024-11021. Marcus Chen is responsible for the execution of measurements and the verification of equipment calibration throughout the shift.

Technical Standards and Procedures

Thickness measurements are conducted in accordance with QSCP-NDT-001 Rev 3 and the general requirements of ASTM E797. The survey follows the specific CML-id formats and digital export requirements mandated by the revised site procedure.

Safety compliance is maintained as per the requirements detailed in LNDE-JSA-20241025-031. All site-specific safety protocols for the ATU-100 area have been implemented prior to the start of work.

Equipment and Calibration

The survey utilizes two Olympus 38DL PLUS gauges. Calibration was verified using LNDE-CAL-2024-0847 for unit 2847193 and LNDE-CAL-2024-0848 for unit 2901456.

Field standardization was performed using LNDE-CS-001, a 4-step carbon steel calibration block ranging from 0.100 to 0.400 in, to ensure measurement accuracy across the expected wall thickness range.

Daily Field Activities

UT thickness measurements were performed on the sour gas inlet lines 6-SG-101 and 6-SG-102. These A106 Gr.B lines have a nominal thickness of 7.11 mm and a retirement thickness of 3.56 mm.

Measurements were also completed on the treated gas line 8-TG-101, which has a nominal thickness of 8.18 mm and a t-min of 4.06 mm. All readings are being recorded against the established CMLs for the five-year survey.

Daily Field Activities (Continued)

The survey progressed to the lean amine supply lines 4-LA-101 and 4-LA-102. Both lines are A106 Gr.B with a nominal thickness of 6.02 mm and a t-min of 3.18 mm.

Data collection for these lines is ongoing. All readings are being compared to previous survey data to calculate short-term and long-term corrosion rates as per site rules.

Sign-off	Name	Function	Date	Signature
Prepared	Marcus Chen	lead UT technician, SNT-TC-1A UT/MT/PT/VT Level II; CAN/CGSB-48.9712 UT Level II	2024-11-04	_____