No.	Status	Date
LNDE-FN-20241025-031-DFR-3	Issued	2024-11-06

Daily Field Report 3 - Field Notes - ATU-100 UT Thickness Survey, WO-20241025-031

Scope and Responsibilities

Marcus Chen, acting as lead UT technician, performed ultrasonic thickness measurements on specified piping within the ATU-100. The scope of work is governed by the requirements of QSCP-WP-2024-11021 for the five-year survey of 150 CMLs.

All field activities were executed in accordance with the safety controls outlined in LNDE-JSA-20241025-031. Technical execution followed the site NDE procedure QSCP-NDT-001 Rev 3 and the general requirements of ASTM E797.

Equipment and Calibration

Thickness measurements were obtained using Olympus 38DL PLUS 2847193 and Olympus 38DL PLUS 2901456. Instrument accuracy was verified per LNDE-CAL-2024-0847 and LNDE-CAL-2024-0848.

Calibration was performed using LNDE-CS-001 for carbon steel components and LNDE-SS-003 for stainless steel components. The stainless-steel velocity setting was applied for all A312 TP316 measurements.

Field Measurements - Regenerator Overhead

UT thickness readings were collected for 3-RV-101 (A106 Gr.B, OD 88.9 mm). Measurements were compared against the t-min of 3.56 mm.

UT thickness readings were collected for 2-RV-102 (A106 Gr.B, OD 60.3 mm). Measurements were compared against the t-min of 2.79 mm.

Field Measurements - Reflux Lines

UT thickness readings were collected for 3-RF-101 (A312 TP316, OD 88.9 mm). Measurements were compared against the t-min of 2.41 mm.

UT thickness readings were collected for 2-RF-102 (A312 TP316, OD 60.3 mm). Measurements were compared against the t-min of 2.16 mm.

Sign-off	Name	Function	Date	Signature
Prepared	Marcus Chen	lead UT technician, SNT-TC-1A UT/MT/PT/VT Level II; CAN/CGSB-48.9712 UT Level II	2024-11-06	_____