No.	Status	Date
LNDE-RPT-20140902-024-DFR-1	Issued	2014-09-18

Daily Field Report 1 - UT Thickness Survey - ATU-100 Rich Amine (Pre-MOC)

Scope and Responsibilities

Marcus Chen, acting as lead UT technician (SNT-TC-1A UT Level II), performed a UT thickness survey on rich amine lines within the ATU-100. The objective was to establish pre-MOC thickness data for the specified piping circuits.

The scope of work included the measurement of line 4-RA-101 and line 4-RA-102. All activities were conducted in accordance with the requirements of QSCP-NDT-001 Rev 2.

Regulatory and Safety Compliance

Field operations were executed under the authority of QSCP-WP-2014-09180. All personnel adhered to the safety protocols and hazard mitigations detailed in LNDE-JSA-20140902-024.

Thickness measurements were performed following the guidelines of ASTM E797 to ensure standardized data acquisition and reporting.

Instrumentation and Calibration

Thickness data was acquired using an Olympus 37DL PLUS 0611452. The instrument's accuracy was verified against LNDE-CAL-2013-0683.

Field calibration and verification were performed using LNDE-CS-001, a 4-step carbon steel calibration block ranging from 0.100 to 0.400 in.

Inspection Results - 4-RA-101

Line 4-RA-101, constructed of A106 Gr.B with a nominal thickness of 8.56 mm and an OD of 114.3 mm, was surveyed. The design limits for this line are 862 kPa(g) and 82 °C.

Measurements were compared against the retirement thickness (t-min) of 3.81 mm. All readings were found to be above the t-min threshold.

Inspection Results - 4-RA-102

Line 4-RA-102, constructed of A106 Gr.B with a nominal thickness of 8.56 mm and an OD of 114.3 mm, was surveyed. The design limits for this line are 862 kPa(g) and 82 °C.

Measurements were compared against the retirement thickness (t-min) of 3.81 mm. All readings were found to be above the t-min threshold.

Sign-off	Name	Function	Date	Signature
Prepared	Marcus Chen	lead UT technician, SNT-TC-1A UT Level II	2014-09-18	_____