No.	Status	Date
LNDE-RPT-20220906-033-DS-2-RV-102	Issued	2022-09-16

UT Thickness Data Sheet - 2-RV-102

Scope and Responsibilities

This data sheet provides the ultrasonic thickness measurement results for line 2-RV-102 located within the ATU-100. The primary objective is to record current wall thickness to determine corrosion rates and remaining life in accordance with the 3-year RBI survey requirements for Class 1 sour gas and regenerator overhead services.

Marcus Chen, acting as the lead UT technician and SNT-TC-1A UT Level II for Larkhall NDE Services Inc., performed the thickness measurements and data recording. The technician is responsible for ensuring all readings are captured accurately at the designated locations on the line.

Technical Basis and Standards

All thickness measurements were performed under the requirements of QSCP-NDT-001 Rev 2, which governs site NDE procedures for ultrasonic thickness measurement in the ATU-100. This procedure includes specific requirements for insulation removal and reinstatement to facilitate access to the pipe surface.

The inspection methodology and instrument calibration were conducted in accordance with ASTM E797. The data presented herein supports the findings and conclusions detailed in the associated report LNDE-RPT-20220906-033-R0.

Component Specifications

The subject line, 2-RV-102, is a regenerator overhead line constructed from A106 Gr.B. The component has a nominal outer diameter of 60.3 mm and a nominal wall thickness of 5.54 mm.

The design parameters for this line are established at a maximum allowable pressure of 345 kPa(g) and a design temperature of 121 °C. The minimum allowable thickness (t-min) for the line is 2.79 mm.

Assessment Criteria

Acceptance is based on the retirement thickness, which is defined as the t-min of 2.79 mm. Any measured thickness falling below this value is subject to an NCR. The remaining life is calculated by dividing the difference between the current thickness and t-min by the determined corrosion rate.

The corrosion rate is derived from the larger of the long-term rate or the short-term rate over the latest pair of readings at least 3 years apart. For this Class 1 service, the maximum interval for thickness and external visual inspection is 5 years.

Thickness readings, measured 2022-09-16

Line 6-SG-101 | Sour gas inlet | A106 Gr.B | t_nom 7.11 mm | t-min 3.56 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
6-SG-101-01	7.11	3.56	2019-10-18	5.93	5.82	0.049	0.053	42.6	2025-09-16	
6-SG-101-02	7.11	3.56	2019-10-18	5.51	5.42	0.061	0.052	30.3	2025-09-16	
6-SG-101-03	7.11	3.56	2019-10-18	5.56	5.29	0.067	0.088	19.7	2025-09-16	
6-SG-101-04	7.11	3.56	2019-10-18	5.34	5.19	0.072	0.059	22.8	2025-09-16	
6-SG-101-05	7.11	3.56	2019-10-18	5.04	4.72	0.091	0.100	11.6	2025-09-16	
6-SG-101-06	7.11	3.56	2019-10-18	5.56	5.55	0.057	0.050	34.7	2025-09-16	
6-SG-101-07	7.11	3.56	2019-10-18	6.24	6.16	0.027	0.027	>50	2025-09-16	
6-SG-101-08	7.11	3.56	2019-10-18	5.77	5.57	0.066	0.065	30.6	2025-09-16	

Line 6-SG-102 | Sour gas inlet | A106 Gr.B | t_nom 7.11 mm | t-min 3.56 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
6-SG-102-01	7.11	3.56	2019-10-18	5.05	4.77	0.089	0.099	12.3	2025-09-16	
6-SG-102-02	7.11	3.56	2019-10-18	5.10	4.64	0.093	0.120	9.0	2025-09-16	
6-SG-102-03	7.11	3.56	2019-10-18	4.92	4.69	0.089	0.080	12.8	2025-09-16	
6-SG-102-04	7.11	3.56	2019-10-18	4.90	4.62	0.089	0.085	11.9	2025-09-16	

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
6-SG-102-05	7.11	3.56	2019-10-18	6.07	5.96	0.044	0.035	>50	2025-09-16	
6-SG-102-06	7.11	3.56	2019-10-18	6.03	5.79	0.054	0.041	41.6	2025-09-16	

Line 4-RA-101 | Rich amine | A106 Gr.B | t_nom 8.56 mm | t-min 3.81 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
4-RA-101-01	8.56	3.81	2019-10-18	7.29	6.83	0.064	0.152	19.9	2025-09-16	
4-RA-101-02	8.56	3.81	2019-10-18	7.39	6.79	0.066	0.174	17.1	2025-09-16	
4-RA-101-03	8.56	3.81	2019-10-18	6.64	5.98	0.099	0.253	8.6	2025-09-16	
4-RA-101-04	8.56	3.81	2019-10-18	7.54	7.21	0.054	0.120	28.4	2025-09-16	
4-RA-101-05	8.56	3.81	2019-10-18	7.18	6.73	0.071	0.165	17.7	2025-09-16	
4-RA-101-06	8.56	3.81	2019-10-18	6.94	—	—	—	—	—	inaccessible – no reading
4-RA-101-07	8.56	3.81	2019-10-18	7.68	7.50	0.041	0.097	38.0	2025-09-16	
4-RA-101-08	8.56	3.81	2019-10-18	6.45	5.55	0.118	0.267	6.5	2025-09-16	
4-RA-101-09	8.56	3.81	2019-10-18	7.68	7.37	0.045	0.115	30.9	2025-09-16	
4-RA-101-10	8.56	3.81	2019-10-18	7.55	7.19	0.056	0.126	26.8	2025-09-16	
4-RA-101-11	8.56	3.81	2019-10-18	6.66	6.07	0.098	0.232	9.7	2025-09-16	
4-RA-101-12	8.56	3.81	2019-10-18	7.03	6.41	0.213	0.213	12.2	2025-09-16	

Line 4-RA-102 | Rich amine | A106 Gr.B | t_nom 8.56 mm | t-min 3.81 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
4-RA-102-01	8.56	3.81	2019-10-18	7.58	7.42	0.042	0.091	39.7	2025-09-16	
4-RA-102-02	8.56	3.81	2019-10-18	6.96	6.43	0.081	0.184	14.3	2025-09-16	
4-RA-102-03	8.56	3.81	2019-10-18	7.05	6.56	0.075	0.150	18.3	2025-09-16	
4-RA-102-04	8.56	3.81	2019-10-18	7.04	6.64	0.072	0.164	17.3	2025-09-16	
4-RA-102-05	8.56	3.81	2019-10-18	7.06	6.56	0.075	0.168	16.3	2025-09-16	
4-RA-102-06	8.56	3.81	2019-10-18	7.15	6.65	0.070	0.164	17.3	2025-09-16	
4-RA-102-07	8.56	3.81	2019-10-18	7.30	6.85	0.065	0.141	21.6	2025-09-16	
4-RA-102-08	8.56	3.81	2019-10-18	6.40	5.86	0.099	0.226	9.1	2025-09-16	
4-RA-102-09	8.56	3.81	2019-10-18	6.78	6.42	0.080	0.170	15.4	2025-09-16	
4-RA-102-10	8.56	3.81	2019-10-18	7.36	6.86	0.172	0.172	17.8	2025-09-16	
4-RA-102-11	8.56	3.81	2019-10-18	7.72	7.33	0.074	0.096	36.8	2025-09-16	

Line 6-RA-103 | Rich amine header | A106 Gr.B | t_nom 10.97 mm | t-min 4.57 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
6-RA-103-01	10.97	4.57	2019-10-18	9.83	9.55	0.055	0.112	44.4	2025-09-16	
6-RA-103-02	10.97	4.57	2019-10-18	8.61	7.97	0.118	0.261	13.0	2025-09-16	
6-RA-103-03	10.97	4.57	2019-10-18	9.49	8.95	0.077	0.168	26.0	2025-09-16	
6-RA-103-04	10.97	4.57	2019-10-18	8.22	7.30	0.139	0.305	9.0	2025-09-16	
6-RA-103-05	10.97	4.57	2019-10-18	8.33	7.43	0.133	0.311	9.2	2025-09-16	
6-RA-103-06	10.97	4.57	2019-10-18	9.79	9.45	0.059	0.132	37.0	2025-09-16	
6-RA-103-07	10.97	4.57	2019-10-18	9.59	9.15	0.069	0.159	28.8	2025-09-16	
6-RA-103-08	10.97	4.57	2019-10-18	9.73	9.29	0.063	0.158	29.9	2025-09-16	
6-RA-103-09	10.97	4.57	2019-10-18	9.78	9.43	0.060	0.137	35.6	2025-09-16	
6-RA-103-10	10.97	4.57	2019-10-18	8.37	7.68	0.126	0.275	11.3	2025-09-16	
6-RA-103-11	10.97	4.57	2019-10-18	8.91	—	—	—	—	—	inaccessible – no reading
6-RA-103-12	10.97	4.57	2019-10-18	9.52	9.11	0.141	0.141	32.3	2025-09-16	
6-RA-103-13	10.97	4.57	2019-10-18	9.55	9.13	0.114	0.155	29.5	2025-09-16	
6-RA-103-14	10.97	4.57	2019-10-18	8.26	7.34	0.316	0.316	8.8	2025-09-16	

Line 3-RV-101 | Regenerator overhead | A106 Gr.B | t_nom 7.62 mm | t-min 3.56 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
3-RV-101-01	7.62	3.56	2019-10-18	6.05	5.92	0.063	0.064	37.0	2025-09-16	
3-RV-101-02	7.62	3.56	2019-10-18	5.97	5.81	0.066	0.076	29.7	2025-09-16	
3-RV-101-03	7.62	3.56	2019-10-18	5.24	4.98	0.096	0.099	14.4	2025-09-16	
3-RV-101-04	7.62	3.56	2019-10-18	5.58	5.39	0.083	0.074	22.1	2025-09-16	
3-RV-101-05	7.62	3.56	2019-10-18	6.11	5.91	0.066	0.068	34.4	2025-09-16	
3-RV-101-06	7.62	3.56	2019-10-18	5.55	5.39	0.083	0.086	21.2	2025-09-16	
3-RV-101-07	7.62	3.56	2019-10-18	5.07	4.80	0.117	0.112	10.6	2025-09-16	
3-RV-101-08	7.62	3.56	2019-10-18	5.86	5.81	0.075	0.076	29.7	2025-09-16	

Line 2-RV-102 | Regenerator overhead | A106 Gr.B | t_nom 5.54 mm | t-min 2.79 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
2-RV-102-01	5.54	2.79	2019-10-18	4.16	3.91	0.061	0.067	16.8	2025-09-16	
2-RV-102-02	5.54	2.79	2019-10-18	3.86	3.64	0.074	0.056	11.6	2025-09-16	
2-RV-102-03	5.54	2.79	2019-10-18	4.37	4.34	0.043	0.046	34.1	2025-09-16	
2-RV-102-04	5.54	2.79	2019-10-18	4.59	4.47	0.042	0.039	40.1	2025-09-16	
2-RV-102-05	5.54	2.79	2019-10-18	4.78	4.59	0.037	0.058	31.2	2025-09-16	
2-RV-102-06	5.54	2.79	2019-10-18	4.27	4.05	0.064	0.033	19.6	2025-09-16	

Line 4-RA-104 | L/R exchanger, rich side | A106 Gr.B | t_nom 8.56 mm | t-min 3.81 mm

CML	t_nom (mm)	t-min (mm)	Prev. date	Prev. (mm)	Current (mm)	CR LT (mm/y)	CR ST (mm/y)	RL (y)	Next due	Remark
4-RA-104-01	8.56	3.81	2019-10-18	7.15	6.61	0.072	0.167	16.8	2025-09-16	
4-RA-104-02	8.56	3.81	2019-10-18	7.31	7.04	0.057	0.123	26.3	2025-09-16	
4-RA-104-03	8.56	3.81	2019-10-18	7.94	7.70	0.074	0.088	44.2	2025-09-16	
4-RA-104-04	8.56	3.81	2019-10-18	7.64	7.31	0.101	0.132	26.5	2025-09-16	
4-RA-104-05	8.56	3.81	2019-10-18	7.57	7.12	0.109	0.158	21.0	2025-09-16	
4-RA-104-06	8.56	3.81	2019-10-18	7.13	6.70	0.071	0.138	20.9	2025-09-16	
4-RA-104-07	8.56	3.81	2019-10-18	6.67	6.04	0.096	0.194	11.5	2025-09-16	
4-RA-104-08	8.56	3.81	2019-10-18	7.46	7.09	0.094	0.109	30.0	2025-09-16	

Sign-off	Name	Function	Date	Signature
Prepared	Marcus Chen	lead UT technician, SNT-TC-1A UT/MT/PT Level II; CAN/CGSB-48.9712 UT Level II	2022-09-16	_____