No.	Status	Date
LNDE-RPT-20251103-041-DFR-1	Issued	2025-11-03

Daily Field Report 1 - UT Re-measurement - 2-RF-102

Scope and Responsibilities

The scope of work for this shift consisted of a UT thickness survey on line 2-RF-102 located within ATU-100. Sarah Thompson acted as the UT technician responsible for the execution of measurements and data collection.

All activities were performed in accordance with the requirements of QSCP-NDT-001 Rev 4 and the guidelines established in ASTM E797.

Safety and Authorization

Work was authorized under the permit QSCP-WP-2025-11036. All site safety requirements and hazard mitigations were addressed as per the JSA LNDE-JSA-20251103-041.

The technician verified that all site-specific safety protocols for the Amine Treating Unit were implemented prior to commencing the survey on 2-RF-102.

Equipment and Calibration

Thickness measurements were performed using the Olympus 38DL PLUS 2901456, which was calibrated on-site per LNDE-CAL-2025-0961. The instrument was verified using the LNDE-CS-001 and LNDE-SS-003 calibration blocks.

The technician also referenced LNDE-CAL-2025-0812 for the Olympus 38DL PLUS 2847193 to ensure consistent equipment performance and certification standards.

Execution and Technical Details

The survey targeted line 2-RF-102, constructed from A312 TP316 with a nominal thickness of 3.91 mm. Sarah Thompson applied the stainless-steel velocity setting on the gauge to ensure measurement accuracy for this material grade.

Measurements were taken to validate current wall thickness against the t-min of 2.16 mm. All data was collected in accordance with the revised procedures for CML-id validation and data export specified in QSCP-NDT-001 Rev 4.

Sign-off	Name	Function	Date	Signature
Prepared	Sarah Thompson	UT technician, SNT-TC-1A UT Level II	2025-11-03	_____