No.	Status	Date
LNDE-RPT-20260803-034-DFR-1	Issued	2026-08-03

Daily Field Report 1 - UT Baseline - Replacement Spools on 4-RA-101 and 2-RF-102

Scope and Responsibilities

Larkhall NDE Services Inc. was mobilized to the ATU-100 to perform a UT thickness baseline survey on replacement spools for lines 4-RA-101 and 2-RF-102. The primary objective is to establish initial thickness data for these new components to support future asset integrity monitoring.

Marcus Chen, acting as the lead UT technician, is responsible for the execution of the measurements and data validation. All field activities were conducted in accordance with the site safety requirements and the specific tasks outlined in the project scope.

Regulatory and Procedural Compliance

The thickness measurements were performed under the requirements of QSCP-NDT-001 Rev 4. All ultrasonic testing procedures and instrument applications were carried out in alignment with the guidelines specified in ASTM E797.

Work was authorized under the permit QSCP-WP-2026-08032. Prior to the commencement of NDE activities, a safety review was completed as per the job safety analysis LNDE-JSA-20260803-034.

Equipment and Calibration

Thickness measurements on 4-RA-101 were performed using the Olympus 38DL PLUS 2847193, which was verified against the calibration certificate LNDE-CAL-2025-0812. Calibration was performed using the 4-step carbon steel calibration block LNDE-CS-001.

For the measurements on 2-RF-102, the Olympus 38DL PLUS 2901456 was utilized, with calibration verified via LNDE-CAL-2025-0961. The instrument was calibrated using the calibration block LNDE-SS-003 to ensure accuracy for the stainless-steel velocity setting.

Field Execution - 4-RA-101

The baseline survey for the rich amine line 4-RA-101 was completed. The technician verified the nominal thickness of 8.56 mm against the design minimum of 3.81 mm.

All readings were recorded at the designated locations. No readings below the retirement thickness were observed during this baseline survey.

Field Execution - 2-RF-102

The baseline survey for the reflux line 2-RF-102 was performed using the stainless-steel velocity setting. The nominal thickness of 3.91 mm was verified against the design minimum of 2.16 mm.

The measurements were completed and validated. All recorded thicknesses for the replacement spool on 2-RF-102 meet the minimum requirements.

Sign-off	Name	Function	Date	Signature
Prepared	Marcus Chen	lead UT technician, SNT-TC-1A UT/MT/PT/VT Level II; CAN/CGSB-48.9712 UT Level II	2026-08-03	_____