No.	Status	Date
LNDE-RPT-96-014-DFR-1	Issued	1996-03-06

Daily Field Report 1 - Baseline Ultrasonic Thickness Survey - ATU-100

Scope of Work

Grace Okafor performed a baseline ultrasonic thickness survey on piping within the ATU-100. The objective was to establish initial wall thickness measurements for the specified lines prior to startup.

All activities were conducted in accordance with QSCP-NDT-001 Rev 0 and the requirements of ASTM E797. Work was authorized under the cold work permit QSCP-WP-1996-00412.

Equipment and Calibration

Thickness measurements were obtained using a Panametrics 26DL PLUS 9411820. The instrument's current calibration status is verified by LNDE-CAL-1996-0031.

Field standardization was performed using a 4-step carbon steel calibration block, 0.100-0.400 in, LNDE-CS-001 to ensure measurement accuracy across the required range.

Inspection Results - Sour and Treated Gas

Baseline readings were recorded for the sour gas inlet lines 6-SG-101 and 6-SG-102, both A106 Gr.B with a nominal thickness of 7.11 mm and a t-min of 3.56 mm.

The treated gas line 8-TG-101, A106 Gr.B with a nominal thickness of 8.18 mm and a t-min of 4.06 mm, was also surveyed.

Inspection Results - Amine Services

Measurements were taken on lean amine supply lines 4-LA-101 and 4-LA-102, both A106 Gr.B with a nominal thickness of 6.02 mm and a t-min of 3.18 mm.

The lean amine header 6-LA-103, A106 Gr.B with a nominal thickness of 7.11 mm and a t-min of 3.56 mm, was surveyed.

The rich amine line 4-RA-101, A106 Gr.B with a nominal thickness of 8.56 mm and a t-min of 3.81 mm, was surveyed.

Sign-off	Name	Function	Date	Signature
Prepared	Grace Okafor	UT technician, SNT-TC-1A UT Level II	1996-03-06	_____